

SUPPLEMENTARY REPORT ON CHESHIRE'S PROSPECT, FINGAL.

The following are the assay results of the sample taken :-

Sample		Gold oz./ton	Silver oz./ton
Shaft S.E. end 7' depth	1	Trace	Trace
Shaft S.E. end 9' depth	2	"	"
Shaft N.W. end 8' depth	3	"	"
Trench 15' N.W. of shaft	4	"	"
General sample from bottom of shaft	5	0 ozs. 5 dwts. 5 grs.	0 ozs. 5 dwts. 5 grs.
Bottom of shaft	6	Trace	0 ozs. 2 dwts. 14 grs.

It is to be noted that only a trace of gold was obtained from the five samples broken out of the reef. The other sample (No. 5) consisted of numerous small loose pieces taken from the bottom of the shaft. Sample No. 6 was from the mineralized quartz at the bottom. These results are not as good as anticipated from the fact that gold was visible in some of the mineralized quartz and that good prospects could be washed from loose material and also from crushed quartz.

However the quartz is well mineralized and some of it apparently contains a small amount of gold. A small amount of prospecting work is perhaps justified to prove the extent and mode of occurrence of the gold-bearing shoot if such exists.

Sgd. P.B. Nye
GOVERNMENT GEOLOGIST

Hobart,
December, 2nd 1926.

le
er,