

UNPUBLISHED REPORT 1968/22

Samples of concentrates from Chilver's bore hole

by G. B. Everard

Two small samples of concentrates from cored material from the Chilver's bore at Cleveland have been examined as follows:

<i>From</i>	<i>To</i>	
75'	95'	About 90% quartz in angular grains with small quantities of zircon, topaz, tourmaline, ilmenite, rutile and garnet.
100'	125'	Quartz 70%, zircon 25%, rutile 5%, with traces of topaz and tourmaline.

[26 July 1968]