

1979/19. Department of Mines diamond drill hole assay logs,
Great Pyramid tin prospect

D.J. Jennings

Abstract

The Department of Mines drilled four diamond drill holes in the Great Pyramid tin prospect between September, 1976 and May, 1978.

INTRODUCTION

The diamond drill holes were located at low and moderate heights on the south-west aspect of Pyramid Hill [FQ000135]. These locations were surveyed and their positions plotted on plan 4309 (Varley, 1970), as precisely as the original grid would permit. The holes were angled at 60° to the horizontal at a bearing of 060°M. Depths reached were 215.7, 170.0, 170.0 and 154.3 metres. Samples were assayed for tin, arsenic, zinc, copper, WO₃ (tungsten), antimony and bismuth.

REFERENCE

VARLEY, R.J. 1970. Progress report No. 1 on exploration at the Great Pyramid, N.E. Tasmania. *Unpubl.Rep.Aberfoyle Management.*

[5 July, 1979]

Table 1. ASSAY RESULTS, HOLE MD1

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
1	0.00- 2.02	64	0.22	-	0.01	-	
2	2.02- 3.05	-	0.09	-	0.02	0.02	
3	3.05- 5.46	87	0.06	-	0.02	-	
4	5.46- 6.99	92	0.04	-	0.05	0.01	
5	6.99- 8.70	88	0.03	-	0.08	-	
6	8.70- 10.24	96	-	-	0.02	-	
7	10.24- 11.75	93	0.03	-	0.04	-	
8	11.75- 13.30	95	0.02	-	0.06	-	
9	13.30- 14.85	-	0.01	-	0.05	-	
10	14.85- 16.40	-	0.01	-	0.05	-	
11	16.40- 17.92	-	0.01	-	0.05	-	
12	17.92- 19.35	94	0.02	-	0.05	-	
13	19.35- 20.89	94	0.02	-	0.06	-	
14	20.89- 23.39	82	-	-	0.10	-	
15	23.39- 25.56	94	0.01	-	0.07	-	
16	25.56- 27.58	-	0.02	-	0.08	-	
17	27.58- 29.22	-	0.02	-	0.08	-	
18	29.22- 31.70	-	-	-	0.04	-	
19	31.70- 33.77	-	0.02	-	0.09	-	
20	33.77- 35.67	-	0.01	-	0.11	-	
21	35.67- 37.96	-	0.02	-	0.10	-	
22	37.96- 39.75	-	-	-	0.06	-	
23	39.75- 41.35	-	0.02	-	0.11	-	
24	41.35- 42.75	-	0.02	-	0.08	-	
25	42.75- 44.62	-	-	-	0.05	-	
26	44.62- 46.38	97	0.06	-	0.04	-	
27	46.38- 48.58	95	0.01	-	0.06	-	
28	48.58- 50.52	98	0.02	-	0.08	-	
29	50.52- 52.24	100	-	-	0.06	-	
30	52.24- 54.52	100	0.01	-	0.06	-	
31	54.52- 56.48	100	-	-	0.05	-	
32	56.48- 58.34	100	-	-	0.04	-	

19-2

Table 1. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
33	58.34- 60.38	100	-	-	0.05	-	
34	60.38- 63.00	100	-	-	0.06	-	
35	63.00- 65.50	100	-	-	0.05	-	
36	65.50- 67.36	100	-	-	0.04	-	
37	67.36- 69.46	86	-	0.01	0.04	-	
38	69.46- 71.52	100	-	0.04	0.06	-	WO ₃ 1.8
39	71.52- 73.02	97	-	-	0.05	-	
40	73.02- 74.90	100	-	-	0.05	-	
41	74.90- 76.76	93	0.02	-	0.05	-	0.23
42	76.76- 79.18	88	-	-	0.03	-	
43	79.18- 80.78	99	0.01	-	0.04	-	
44	80.78- 81.63	95	-	-	0.03	0.01	
45	81.63- 83.71	100	-	-	0.05	-	0.13
46	83.71- 85.29	100	-	-	0.05	-	
47	85.29- 86.81	90	0.01	0.14	0.08	0.02	0.07
48	86.81- 88.30	97	-	0.12	0.05	0.02	0.07
49	88.30- 90.04	96	-	-	0.04	-	
50	90.04- 92.34	100	-	0.01	0.03	-	0.03
51	92.34- 94.40	94	-	0.01	0.07	-	0.09
52	94.40- 95.84	100	-	-	0.04	-	0.04
53	95.84- 97.53	96	-	-	0.03	-	
54	97.53-100.34	96	0.02	-	0.04	0.03	
55	100.34-102.90	99	0.02	-	0.04	-	0.05
56	102.90-105.38	100	0.06	-	0.08	0.03	0.04
57	105.38-106.52	83	0.01	-	0.04	-	
58	106.52-108.54	97	-	-	0.02	-	
59	108.54-109.72	95	-	-	0.02	-	
60	109.72-111.55	90	-	-	0.03	-	0.03
61	111.55-113.30	97	0.01	-	0.03	-	
62	113.30-115.06	85	-	-	0.05	-	
63	115.06-116.82	97	-	-	0.10	0.02	0.03
64	116.82-117.69	98	0.01	-	0.03	-	

19-3

Table 1. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
65	117.69-119.39	100	0.10	-	0.14	0.08	WO ₃ 0.03
66	119.39-121.13	97	0.02	-	0.06	0.02	
67	121.13-122.85	98	0.06	-	0.13	0.04	
68	122.85-125.37	91	0.02	-	0.05	-	0.03
69	125.37-127.72	96	0.15	-	0.03	0.02	
70	127.72-129.22	99	0.04	0.82	0.08	0.05	
71	129.22-131.38	98	0.10	0.02	0.02	0.01	0.03
72	131.38-133.12	98	0.06	0.02	0.03	0.02	
73	133.12-134.40	95	0.03	-	0.01	-	
74	134.40-136.05	98	0.04	-	0.02	0.03	
75	136.05-137.70	97	0.09	0.05	0.04	0.01	
76	137.70-139.84	100	0.23	-	0.01	0.02	
77	139.84-141.51	98	0.08	-	0.01	0.05	
78	141.51-143.14	94	0.17	0.05	0.03	0.04	
79	143.14-144.12	100	0.09	2.1	0.19	0.05	0.05
80	144.12-145.34	94	0.05	0.05	0.06	0.04	
81	145.34-146.69	100	0.60	2.0	0.03	0.04	0.04
82	146.69-147.50	100	0.09	0.15	0.07	0.06	
83	147.50-148.36	100	0.18	0.15	0.09	0.05	
84	148.36-149.86	100	0.08	0.11	0.02	0.06	
85	149.86-151.36	100	0.03	-	0.01	0.02	
86	151.36-152.80	94	0.04	-	0.01	-	0.04
87	152.80-154.20	96	0.01	-	0.02	-	
88	154.20-155.60	100	0.20	-	0.02	0.02	
89	155.60-157.10	100	0.09	0.03	-	0.02	
90	157.10-158.68	100	0.02	-	0.02	0.02	
91	158.68-160.20	100	0.07	-	0.01	0.03	
92	160.20-161.72	100	0.02	-	0.01	0.02	
93	161.72-163.12	100	-	-	0.01	-	
94	163.12-164.77	100	-	-	0.01	-	
95	164.77-166.25	100	-	-	0.01	-	
96	166.25-167.30	100	-	-	0.01	-	

19-4

Table 1. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
97	167.30-169.00	100	0.04	0.04	0.03	0.02	
98	169.00-170.70	100	0.02	-	0.02	0.02	
99	170.70-172.40	100	0.04	-	0.06	0.02	
100	172.40-174.00	100	0.06	-	0.19	0.03	
101	174.00-176.00	100	0.02	-	0.02	0.01	
102	176.00-178.09	100	0.01	-	0.01	-	
103	178.09-180.12	100	0.01	-	-	-	
104	180.12-181.62	100	0.01	-	0.01	-	
105	181.62-183.05	100	0.01	-	0.01	-	
106	183.05-184.25	100	0.01	-	0.01	-	
107	184.25-185.59	100	0.02	-	0.02	-	
108	185.59-187.40	100	0.03	-	0.05	0.04	
109	187.40-189.28	100	0.03	-	0.04	0.02	
110	189.28-190.94	100	0.01	-	0.02	-	
111	190.94-193.00	100	-	-	0.01	-	
112	193.00-195.50	100	0.01	-	-	-	
113	195.50-197.00	100	0.02	-	-	-	
114	197.00-198.60	100	-	-	-	-	
115	198.60-200.05	100	0.11	-	0.04	0.04	
116	200.05-201.45	100	0.26	0.01	0.11	0.16	
117	201.45-203.35	100	0.48	0.04	0.04	0.02	
118	203.35-205.25	100	0.03	-	0.02	0.01	
119	205.25-206.50	100	0.03	-	0.01	0.02	
120	206.50-208.06	100	0.03	-	0.02	0.02	
121	208.06-209.58	100	0.05	-	0.04	0.09	
122	209.58-211.10	100	0.02	-	0.02	-	
123	211.10-212.60	100	0.33	-	0.10	-	
124	212.60-214.00	100	0.09	0.06	0.03	0.06	Sb 0.03
125	214.00-215.70	100	0.03	-	0.01	-	0.02

19-5

Table 2. ASSAY RESULTS, HOLE MD2

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
1	3.00- 4.97	58	0.01	-	0.06	-	
2	4.97- 6.54	94	-	-	0.06	-	
3	6.54- 8.83	89	0.11	-	0.06	0.01	
4	8.83- 11.16	93	0.01	-	0.07	0.01	
5	11.16- 12.72	64	0.02	-	0.09	0.01	
6	12.72- 14.28	95	-	-	0.15	-	
7	14.28- 15.81	89	0.01	-	0.07	0.02	
8	15.81- 17.37	90	0.02	-	0.03	0.02	
9	17.37- 18.93	97	0.03	-	0.04	0.04	
10	18.93- 20.23	98	0.03	-	0.03	0.04	
11	20.23- 21.79	96	0.12	0.01	0.02	0.03	
12	21.79- 23.35	92	0.02	-	0.01	0.02	
13	23.35- 24.74	54	-	-	0.02	0.01	
14	24.74- 26.27	90	-	-	-	-	
15	26.27- 27.83	74	0.01	0.01	0.01	0.02	
16	27.83- 29.26	91	-	-	0.02	0.02	
17	29.26- 30.16	91	-	-	0.03	0.03	
18	30.16- 32.38	86	-	0.01	0.02	0.04	
19	32.38- 33.87	68	-	0.04	0.01	0.06	WO ₃ 0.02
20	33.87- 35.56	92	-	0.01	0.01	0.06	
21	35.56- 36.99	87	0.02	-	0.01	0.04	
22	36.99- 38.55	97	-	0.01	0.02	0.03	0.03
23	38.55- 39.72	92	0.02	0.02	0.03	0.04	
24	39.72- 41.42	94	0.11	0.05	0.02	0.05	
25	41.42- 43.86	70	-	0.01	0.04	0.03	
26	43.86- 45.00	98	-	0.01	0.04	0.02	
27	45.00- 47.23	100	-	0.03	0.04	0.03	
28	47.23- 49.00	98	0.04	0.07	0.04	0.05	
29	49.00- 52.12	99	0.03	0.24	0.03	0.05	
30	52.12- 55.12	100	0.02	0.02	0.03	0.05	
31	55.12- 58.14	98	0.06	-	0.05	0.09	
32	58.14- 60.24	76	0.04	0.02	0.05	0.18	

19-6

Table 2. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
33	60.24-63.86	28	0.05	-	0.10	0.18	
34	63.86-67.63	99	0.02	-	0.05	0.03	
35	67.63-73.61	45	0.07	0.02	0.05	0.03	
36	73.61-76.65	94	0.02	0.21	0.06	0.03	
37	76.65-79.70	99	0.03	0.01	0.03	0.03	
38	79.70-81.70	100	0.02	0.11	0.03	0.17	
39	81.70-82.71	100	0.02	-	0.02	0.08	
40	82.71-85.76	100	0.03	0.12	0.02	0.13	
41	85.76-88.81	100	0.01	0.86	0.01	0.05	
42	88.81-91.86	100	0.02	0.35	0.03	0.27	
43	91.86-94.88	100	0.02	0.06	0.03	0.19	
44	94.88-97.93	100	0.02	0.11	0.03	0.15	
45	97.93-100.93	100	0.06	0.46	0.02	0.11	
46	100.93-103.89	100	0.03	0.02	0.03	0.17	
47	103.89-105.40	100	0.02	-	0.02	0.02	
48	105.40-107.12	97	-	-	0.02	0.03	
49	107.12-110.17	100	0.01	0.05	0.02	0.12	
50	110.17-113.22	98	0.01	0.01	0.03	0.04	
51	113.22-117.00	100	0.02	0.04	0.02	0.14	
52	117.00-121.02	98	0.04	0.16	0.04	0.23	
53	121.02-125.04	100	0.02	0.08	0.01	0.10	WO ₃ 0.04
54	125.04-126.97	100	0.02	0.19	0.06	0.13	0.04
55	126.97-130.02	100	0.02	0.02	-	0.03	
56	130.02-132.96	100	-	-	-	0.01	0.03
57	132.96-135.94	100	0.01	0.02	-	-	0.03
58	135.94-138.89	100	-	0.02	-	-	0.05
59	138.89-140.91	100	0.02	0.15	-	0.02	0.07
60	140.91-142.25	100	0.01	0.15	-	0.02	0.05
61	142.25-144.60	100	0.02	0.07	-	0.03	0.03
62	144.60-147.22	100	0.02	0.04	-	0.01	0.03
63	147.22-148.93	100	0.02	-	-	0.03	
64	148.93-150.66	100	0.02	0.04	-	0.06	

19-7

Table 2. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
65	150.66-153.66	100	-	-	-	0.01	
66	153.66-156.65	100	0.06	-	-	0.03	
67	156.65-159.64	100	0.07	0.02	0.01	0.15	
68	159.64-162.64	100	0.19	0.02	-	0.11	WO ₃ 0.04
69	162.64-165.22	100	0.05	-	-	0.03	
70	165.22-167.59	100	0.06	-	-	0.02	
71	167.69-170.00	100	0.04	-	0.02	0.02	
	Debris: Sweepings						
	General:		0.03	0.11	0.05	0.10	
	Box 1 : 2		0.02	-	0.08	0.01	
	Box 3 : 4		0.02	-	0.03	0.03	
	Box 5 : 6 : 7		0.01	0.01	0.02	0.04	
	Box 8 : 9 : 10		0.02	0.11	0.03	0.06	
	Box 11 : 12 : 13		0.04	0.18	0.03	0.05	
	Box 14 - 24		0.02	0.05	0.02	0.11	

19-8

8/13

Table 3. ASSAY RESULTS, HOLE MD3

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zb (%)	Cu (%)	WO ₃ , Sb, Bi (%)
1	3.11- 4.74	55	0.05	0.02	0.02	0.01	
2	4.74- 6.24	100	0.48	0.01	-	0.01	
3	6.24- 7.84	100	0.40	-	-	-	
4	7.84- 9.44	100	0.09	-	-	-	
5	9.44- 11.10	88	0.05	-	-	-	
6	11.10- 12.72	93	0.08	0.04	-	-	
7	12.72- 14.32	79	0.18	0.06	-	-	
8	14.32- 15.75	100	0.35	0.04	-	-	
9	15.75- 17.23	56	0.10	0.01	-	-	
10	17.23- 18.71	98	0.22	0.02	-	-	
11	18.71- 21.89	60	0.03	0.05	-	-	
12	21.89- 23.31	99	0.02	0.13	0.01	-	
13	23.31- 26.22	57	0.05	0.15	-	-	
14	26.22- 27.88	78	0.05	0.16	-	-	
15	27.88- 29.20	88	0.15	0.47	-	-	
16	29.20- 30.81	93	0.30	0.54	-	-	
17	30.81- 32.45	91	0.15	0.28	-	-	
18	32.45- 33.80	81	0.17	0.50	-	-	
19	33.80- 35.20	88	0.13	0.15	-	-	
20	35.20- 38.28	62	0.30	0.14	-	-	
21	38.28- 39.88	85	0.29	0.24	-	0.01	Bi 0.03
22	39.88- 42.86	54	0.05	0.06	-	-	
23	42.86- 45.83	76	0.04	0.03	-	-	
24	45.83- 47.37	74	0.03	0.01	-	0.02	
25	47.37- 48.97	99	-	-	0.05	0.03	
26	48.97- 50.57	100	-	-	0.04	0.02	
27	50.57- 52.09	100	-	-	0.04	-	
28	52.09- 53.69	88	0.07	-	0.04	0.01	
29	53.69- 54.86	100	-	-	0.07	-	
30	54.86- 56.38	100	-	-	0.10	-	
31	56.38- 57.85	100	0.02	0.01	0.06	0.02	
32	57.85- 59.15	100	0.07	-	0.06	0.02	

19-9

9/13

Table 3. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
33	59.15- 60.85	100	0.07	-	0.05	0.01	
34	60.85- 62.36	97	0.05	0.01	0.08	0.02	
35	62.36- 63.00	94	0.01	-	0.04	-	
36	63.00- 66.05	92	0.33	0.20	0.05	0.13	
37	66.05- 70.14	63	0.02	0.02	0.04	0.02	
38	70.14- 72.39	100	0.01	-	0.08	-	
39	72.39- 75.44	37	0.13	0.06	0.09	0.05	
40	75.44- 77.67	99	0.20	0.06	0.07	0.05	WO ₃ 0.03
41 & 42	77.67- 81.66	90	-	0.01	0.07	-	
43	81.66- 84.64	81	0.02	-	0.05	0.01	
44	84.64- 87.69	93	-	-	0.05	-	
45	87.69- 90.74	-	-	-	0.05	-	
46	90.74- 93.74	100	-	-	0.07	-	
47	93.74- 96.84	53	0.05	-	0.07	-	
48	96.84- 99.89	75	0.01	-	0.06	-	
49	99.89-101.64	80	0.02	-	0.07	0.02	
50	101.64-104.82	69	0.02	-	0.05	-	
51	104.82-109.04	63	0.01	-	0.04	-	
52	109.04-112.09	63	0.06	-	0.26	0.02	
53	112.09-116.04	51	0.07	-	0.30	0.05	
54	116.04-118.19	79	2.8	-	2.3	0.26	
55	118.19-119.19	79	0.08	0.01	0.18	0.03	
56	119.19-121.66	91	0.01	-	0.04	-	
57	121.66-124.29	89	0.01	-	0.06	-	
58	A 124.29-127.34	100	0.02	-	0.08	0.03	
59	B 124.29-127.34	100	0.07	0.06	0.16	0.19	
60	127.34-130.39	94	0.02	-	0.18	-	
61	130.39-133.44	90	0.07	0.02	0.34	0.02	
62	133.44-136.49	100	0.51	0.02	0.49	0.02	
63	136.49-139.54	100	0.05	0.14	0.19	0.01	
64	139.54-142.59	97	0.06	0.02	0.17	0.03	
65	142.59-145.64	100	0.09	-	0.23	-	

19-10

10/13

Table 3. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
66	145.64-148.69	100	0.20	-	0.39	0.01	
67	148.69-151.74	100	0.21	0.01	0.16	0.03	
68	151.74-154.74	97	0.12	0.21	0.20	0.05	
69	154.74-157.74	100	0.20	-	0.07	0.05	
70	157.74-160.74	100	0.08	0.01	0.15	0.04	
71	160.74-163.74	100	0.06	0.12	0.07	0.02	
72	163.74-166.74	100	0.03	0.06	0.04	0.02	
73	166.74-170.00	86	-	0.02	0.05	0.01	
Debris: Sweepings							
	Box 1 : 2 : 3		0.39	0.04	0.01	0.01	
	Box 4 : 5		0.11	0.28	-	-	
	Box 6 : 7		0.33	0.63	-	0.02	
	Box 8		0.13	0.08	-	0.01	
	Box 9		0.03	0.01	0.04	0.02	
	Box 10		0.13	-	0.07	-	
	Box 11 : 12		0.34	0.09	0.07	0.01	WO ₃ 0.03: Bi 0

19-11

Table 4. ASSAY RESULTS, HOLE MD4

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bu (%)
1	7.17- 13.12	30	0.07	0.06	0.03	0.02	
2	13.12- 15.68	55	0.09	0.04	0.02	0.01	
3	15.68- 17.66	60	0.44	-	0.02	-	
4	17.66- 18.76	73	0.49	-	0.03	0.02	
5	18.76- 21.76	50	0.05	0.03	-	-	
6	21.76- 24.65	48	0.10	0.01	0.01	-	
7	24.65- 26.50	43	0.15	-	-	-	
8	26.50- 27.76	78	0.04	-	0.01	-	
9	27.76- 30.76	63	0.03	-	-	-	
10	30.76- 32.92	-	0.04	-	-	-	
11	32.92- 36.00	-	0.03	-	-	-	
12	36.00- 39.76	51	0.06	-	-	-	
13	39.76- 42.76	53	0.01	0.02	-	-	
14	42.76- 45.76	35	0.10	0.10	-	0.05	
15	45.76- 48.76	35	0.09	0.01	-	-	
16	48.76- 50.76	-	0.04	0.01	-	-	
17	50.76- 53.27	29	0.04	0.47	-	-	
18	53.27- 56.27	75	0.03	0.03	0.01	0.02	
19	56.27- 59.28	91	0.01	0.01	-	0.02	
20	59.28- 63.00	73	0.04	0.01	-	0.03	
21	63.00- 66.25	100	0.02	-	0.02	0.05	
22	66.25- 69.27	93	0.03	-	0.02	0.04	
23	69.27- 72.25	-	0.01	-	0.02	0.06	
24	72.25- 75.20	-	0.04	-	0.07	0.02	
25	75.20- 78.15	-	0.19	-	0.04	0.03	
26	78.15- 81.47	-	0.04	-	0.05	-	
27	81.47- 84.52	-	0.17	0.05	0.07	0.26	
28	84.52- 86.27	-	0.43	0.01	0.08	0.02	
29	86.27- 90.62	100	0.06	-	0.12	0.02	WO ₃ 0.04
30	90.62- 94.86	39	0.04	-	0.11	0.04	
31	94.86- 96.72	59	0.02	-	0.07	0.02	
32	96.72- 99.77	79	0.04	0.04	0.02	0.06	Sb 0.03

19-12

10/13

Table 4. (continued)

Sample	Depth (m)	Recovery (%)	Sn (%)	As (%)	Zn (%)	Cu (%)	WO ₃ , Sb, Bi (%)
33	99.77-102.00	76	0.01	-	0.02	0.05	
34	102.00-105.87	89	0.01	-	0.01	0.04	
35	105.87-110.47	75	0.04	-	0.05	0.03	
36	110.47-115.02	70	0.03	-	0.13	-	
37	115.02-118.17	84	0.06	-	0.29	-	
38	118.17-124.17	92	0.02	-	0.12	-	WO ₃ 0.02
39	124.17-126.37	88	-	-	0.10	-	
40	126.37-130.27	74	0.03	-	0.09	-	
41	130.27-134.60	79	0.03	-	0.11	-	
42	134.60-136.37	-	0.10	-	0.23	0.02	
43	136.37-139.42	85	0.04	-	0.22	0.02	
44	139.42-142.47	97	0.02	-	0.15	-	
45	142.47-145.52	89	0.01	0.14	0.07	-	
46	145.52-148.20	-	-	-	0.09	-	
47	148.20-151.57	80	0.02	0.03	0.31	0.07	
48	151.57-152.27	100	0.04	0.10	5.1	0.80	
49	152.27-154.30	84	0.03	-	0.72	0.14	
Debris: Sweepings							
	7.17- 18.76		0.43	0.04	0.03	0.02	
	26.50- 32.92		0.09	0.01	0.01	-	
	33.00- 56.00		0.11	0.10	0.01	0.02	
	56.00- 63.00		0.03	0.02	0.01	0.04	
	86.27- 94.86		0.08	-	0.22	0.03	
	94.86-110.47		0.03	-	0.05	0.04	
	110.47-126.37		0.02	-	0.14	-	
	126.37-142.47		0.07	-	0.47	0.02	
	142.47-154.30		0.02	0.04	0.57	0.05	

19-13