

DEPARTMENT OF MINES LABORATORY

C O P Y

LAUNCESTON,.....

ORE DRESSING INVESTIGATION

316/38

No. R13FLOTATION TEST.Material Renison Ass. Tin Mines N.L. "General Sample" from 7 faces

<u>Product</u>	<u>Weight Gms.</u>	<u>Weight %</u>	<u>Assay Sn. %</u>	<u>Contents Sn gms.</u>	<u>Recovery %</u>
Feed	1050	100	2.5	26.25	
Sulphide Cons.	568	54.09	0.36	2.04	7.39
Silicious residue	476	45.3	5.07	24.13	91.89
	<u>1044</u>	<u>99.39</u>		<u>26.17</u>	<u>99.28</u>

