

DEPARTMENT OF MINES LABORATORY

21st March, 1944

C O P Y

LAUNCESTON,.....

ORE DRESSING INVESTIGATION

SCANNED

No.R114.Reg. No. 131.

Mr. J.A. G. O'Dea,
 General Manager,
 Renison Associated Tin Mines,
 Renison Bell, Tas.

Dear Sir,

Herewith sizing analysis of cassiterite concentrate stated to be "fine concentrate from Kieve."

<u>Fraction</u>	<u>Weight Percent.</u>	<u>Weight Percent Cumulative.</u>
+ 200	4.8	4.8
IS/1	37.9	42.7
2	26.4	69.1
3	18.3	87.4
4	8.9	96.3
5	2.2	98.5
6	0.7	99.2
7	0.8	100.0

W. H. Hanson
CHIEF CHEMIST & METALLURGIST.