

MRC9304011-ACM

1968 - 1971	20	Sandstone: As above, no show.
	40	Claystone: As above, very carbonaceous in part.
	40	Siltstone: As above, very carbonaceous in part, brown and firm in part.
1971 - 1974	10	Sandstone: As above, no show.
	90	Claystone: Brown to grey brown, light to medium, occasionally white, micromicaceous, common carbonaceous detritus, silty in part, sandy microlaminae, laminated, subfissile, very soft to firm, occasional dolomitic concretions, dispersive.
1974 - 1977	30	Coal: Black, dull, hard, brittle, hackly fracture, slightly argillaceous in part, platy to blocky.
	70	Claystone: As above.
1977 - 1980	20	Coal: As above.
	80	Claystone: As above.
1980 - 1983	90	Claystone: Off white, occasionally light grey brown, silty, micromicaceous, soft, dispersive, grading to siltstone.
	10	Sandstone: White, very fine grained, subangular to subround, well sorted, strong calcareous cement, very hard, no porosity, no show.
1983 - 1986	90	Claystone: As above.
	10	Sandstone: As above, no show.
1986 - 1989	20	Sandstone: As above, grading to siltstone, slightly calcareous in part.
	70	Claystone: As above.
	10	Siltstone: White, very sandy, firm, blocky, argillaceous and soft in part.
1989 - 1992	10	Sandstone: As above, no show.
	90	Claystone: As above, becoming commonly light grey brown, laminated, subfissile to fissile.
1992 - 1995	100	Claystone: Light grey brown to pale brown, soft to firm, subfissile, with occasional micromicaceous and silty laminae, carbonaceous specks in part, trace pyrite.
1995 - 1998	100	Claystone: As above.
1998 - 2001	100	Claystone: As above, with dolomitic concretions.
	Tr	Coal: As above.
2001 - 2004	80	Claystone: As above, with dolomitic concretions.
	10	Siltstone: Off white, firm, argillaceous, generally sandy, moderate siliceous cement, blocky, grades to silty sandstone.
	10	Coal: Black, subvitreous to dull, hard, brittle, splintery to blocky.
2004 - 2007	80	Claystone: As above, with dolomitic concretions.
	10	Siltstone: Off white to light brown, argillaceous, occasionally carbonaceous, moderate calcareous cement, firm to hard, <b>FLUORESCENCE</b> 50% patchy dull yellow, no cut, weak crush cut, trace residue ring.