

Casing/Cementing

Table #3

| Hole | | Casing | | | | Cement | | | Slurry density | Remarks |
|--|-------------|---------|------------------|-------|------------|-------------|--|--------------|---|---------|
| Depth M | Size inches | Depth M | OD/ID inches | # jts | Weight ppf | # sx | Type | | | |
| 209 | 36 | 203 | 30/28 | 8 | 310 | 2000 | Class G w/ 1% CaCl ₂ | 15.8 | Returns to seabed | |
| 416 | 26 | 413 | 20/ 18.73 | 26 | 133 | 1500 500 | Class G w/ P.H.Gel + NF-1 Class G neat | 12.8 15.8 | Returns to seabed Returns to seabed | |
| 1662 | 17.5 | 1651 | 13.375 12.415 | 130 | 68 | 1607 500 | Class G w/ P.H.Gel + CFR-2 Class G w/ HR6L | 12.8 15.8 | Plug bumped early. Drill out 1036m cement in casing | |
| Repeat cementation of 13.375" casing via EZSV plug and Ø.E.Drillpipe | | | | | | 1589 513 | Class G w/ P.H.Gel + CFR-2 Class G w/ HR6L | 12.8 15.8 | | |
| 3901 | 12.25 | Plug#1 | | | | 560 | Class G w/- 2.5% gel, Ø.4% CFR2 and Ø.12% HR-12 | 12.8 | Plug back prior to testing | |
| 3554 | 12.25 | Plug#2 | | | | 630 | Class G w/- 2.5% gel, Ø.75% CFR2 Ø.8% Halad 22 | 12.8 | | |
| 3314 | 12.25 | 3311.6 | 9.62 | 268 | 47 | 630 | Class G w/- 2.5% gel, Ø.75% CFR2 Ø.8% Halad 22 | 12.8 | Cement 9.625" casing. Lead slurry | |
| | | | | | | 1500 | Class G w/- 35% silica flour Ø.75% CFR2, Ø.8% Halad 22, Ø.4% HR-12 | 15.8 | Tail slurry | |