

329628

Casing/Cementing

Table #1

| Hole | | Casing | | | | Cement | | | | Remarks |
|-----------|----------------|------------|-----------------|----------|---------------|--------|--|-------------------|----------------------------|---------|
| epth M | Size inches | Depth M | OD/ID inches | # jts | Weight ppf | # sx | Type | Slurry density | | |
| 3901 | 12.25 | Plug#1 | | | | 560 | Class G w/- 2.5% gel, 0.4% CFR2 and 0.12% HR-12 | 12.8 | Plug back prior to testing | |
| 3554 | 12.25 | Plug#2 | | | | 630 | Class G w/- 2.5% gel, 0.75% CFR2 0.8% Halad 22 | 12.8 | | |
| 3314 | 12.25 | 3311.6 | 9.62/ 8.68 | 268 | 47 | 630 | Class G w/- 2.5% gel, 0.75% CFR2 0.8% Halad 22 | 12.8 | Cement 9.625" casing. | |
| | | | | | | 1500 | Class G w/- 35% silica flour 0.75% CFR2, 0.8% Halad 22, 0.4% HR-12 | 15.8 | Lead slurry Tail slurry | |