

IV CASING - LINER - TUBING RECORD							
Type	Size	Weight	Grade	Thread	No. Joints	Amount	Depth
Conductor	30"x16-3/4" Pile Joint						
	20"	104	X55LP	Vetco	11	478.16	865
Surface	13-3/8"	54.5	J-55	Butt.	56	2162.00	2512
Inter- mediate	9-5/8"	43.5	N-80	Butt.	82	3346.32	
	9-5/8"	40.0	N-80	Butt.	121	4854.40	8548
NOTE:	Pile Joint was salvaged prior to rig down.						

V CEMENT RECORD			
String	20"	13-3/8"	9-5/8"
Type of Cement	940 sx w/2% Gel & 500 sx w/2% CaCl ₂	375 sx w/2% Gel & 300 sx w/2% CaCl ₂	640 sx w/.8% HR-7
Number of FT ³	2100	958	755
Average weight of slurry	13.7 / 15.5	13.7 / 15.3	15.2
Cement Top	Sea Floor	1450' Temp. Survey	6400' (Calc)
Casing Tested with	500 psi	1500 psi	3000 psi
Number of Centralizers	0	5	12
Number of Scratchers	0	0	0
Stage Collar etc.	0	0	0
Remarks	Gel Prehydrated	Gel Prehydrated Seal Leaked on Test	

 Engineer