

COMPANY: Golden Triangle NL
 PROJECT: Main Creek
 HOLE NUMBER: MC 50

Description		Core Recovery			RQD			Assays							
From	To				From	To	%	From	To	MgO	CaO	SiO ₂	Fe ₂ O ₃		
142.1 continued.....	144.0	pyrite in wispy structures; SCA 70; abundant breaks along schistosity and low angle joint set;													
144.0	155.0	MAGNESITE, water worn: as for 132.0 m. above..... trace disseminated pyrite throughout <0.5% but locally 0.5-1.0% core generally competent but crumbly and soft where water action advanced;													
		143.6	146.0	100	145.0	149.6	70	144.0	145.0	38.03	9.13	2.46	1.33		
		146.0	148.4	85	149.6	154.1	85	145.0	146.0	37.14	10.81	0.88	1.52		
		148.4	155.0	100				146.0	147.0	34.26	13.48	1.95	1.71		
								147.0	148.0	37.06	10.69	1.61	1.52		
								148.0	149.0	39.53	8.21	0.41	1.47		
								149.0	150.0	38.20	10.03	<0.05	1.54		
								150.0	151.0	38.83	9.22	<0.05	1.61		
155.0	162.6	FOOTWALL SCHIST: dark gray speckled schistose (?) volcanics; calcareous in upper section; water worn (vuggy) variably magnetic; ocassional thin cream colored (dolomitic) magnesite bands; speckled texture possibly carbonate alteration; 1-2% pervasive fine-medium grained pyrite; well developed schistosity 60-70 CA;													
		155.0	157.5	85	154.1	158.7	35	151.0	152.0	41.68	5.63	0.89	1.73		
		157.5	161.0	100	158.7	162.6	30	152.0	153.0	33.06	14.60	2.40	2.00		
		161.0	162.6	90				153.0	154.0	38.71	9.03	1.10	1.42		
								154.0	155.0	35.96	12.04	1.51	1.48		
		END OF HOLE													