



Our reference : BU015765
 Your reference : Batch 290199
 Project code : Magnesite Project
 Report date : 22/02/99
 Report status : Final
 Page : 7 of 8

Analabs Pty. Ltd.
 ACN 004 591 664
 14 Thirkell St, Burnie
 Tasmania 7320
 Telephone : (03) 6431 6837
 Facsimile : (03) 6431 8890

ANALYTICAL DATA

Sample	MgO	CaO	SiO2	Fe2O3		
MC41 209.0-210.0	30.45	19.39	0.69	1.14		
MC41 210.0-211.0	36.07	13.45	0.46	0.83		
MC41 211.0-212.0	29.96	20.04	0.36	1.28		
MC41 212.0-213.0	36.27	12.17	<0.05	1.74		
MC41 213.0-214.0	42.12	4.72	<0.05	2.18		
MC41 214.0-215.0	42.59	5.56	0.27	0.70		
MC41 215.0-216.0	39.00	9.96	0.33	0.73		
MC41 216.0-217.0	41.84	6.13	<0.05	0.63		
MC41 217.0-218.0	43.62	4.40	<0.05	0.63		
MC41 218.0-219.0	36.99	11.61	0.43	1.14		
MC41 219.0-220.0	41.79	6.76	<0.05	0.90		
MC41 220.0-221.0	42.21	6.22	<0.05	0.87		
MC41 221.0-222.0	40.07	8.63	<0.05	0.82		
MC41 222.0-223.0	37.65	11.09	0.45	1.25		
MC43 29.2-30.0	36.07	11.25	2.02	1.76		
MC43 30.0-310	41.34	6.96	<0.05	1.22		
MC43 31.0-320	42.42	5.52	0.16	1.11		
MC43 32.0-330	43.07	4.47	0.37	1.08		
MC43 33.0-340	42.66	5.38	0.31	1.12		
MC43 34.0-350	41.45	6.64	0.12	1.05		
MC43 35.0-360	44.05	3.78	<0.05	1.04		
MC43 36.0-370	43.44	4.28	<0.05	0.98		
MC43 37.0-380	43.98	3.95	<0.05	1.03		
MC43 38.0-390	42.44	5.44	<0.05	0.95		
MC43 39.0-400	42.49	5.42	<0.05	0.97		
MC43 40.0-410	39.57	8.72	<0.05	1.05		
MC43 41.0-420	22.81	28.18	0.24	1.25		
MC43 42.0-430	41.42	6.61	<0.05	1.13		
MC43 43.0-440	41.72	6.57	<0.05	0.82		
MC43 44.0-450	39.24	9.39	<0.05	0.76		
MC43 45.0-460	42.71	5.16	<0.05	0.85		
MC43 46.0-470	41.44	6.79	<0.05	1.00		
MC43 47.0-480	37.34	11.12	0.17	1.31		
MC43 48.0-490	39.22	8.78	1.03	0.89		
MC43 49.0-500	40.26	8.22	<0.05	0.83		
MC43 50.0-510	41.26	7.32	<0.05	0.82		
MC43 51.0-520	42.28	6.16	<0.05	0.82		
MC43 52.0-530	40.60	8.12	<0.05	0.80		
MC43 53.0-540	39.78	8.96	<0.05	0.71		
MC43 54.0-550	39.35	8.67	<0.05	0.92		
MC43 55.0-560	35.76	13.27	<0.05	1.30		
MC43 56.0-570	27.20	22.22	1.26	1.62		
MC43 57.0-580	35.12	13.06	0.53	1.78		
MC43 58.0-590	33.85	14.98	0.52	1.48		
MC43 59.0-600	39.66	7.92	0.28	1.74		
MC43 60.0-610	32.17	16.66	0.77	1.85		
MC43 61.0-620	33.70	14.94	0.42	2.01		
MC43 62.0-630	38.33	9.51	0.38	1.98		
MC43 63.0-640	36.27	11.92	0.14	2.03		
MC43 64.0-650	39.49	7.78	0.31	2.23		
Method	X408	X408	X408	X408		
Units	%	%	%	%		
Detection Limit	0.01	0.01	0.05	0.01		

37.3 38.90 MgO
 9.37 CaO

Notes: N.A. = not analysed, -- = element not determined, I.S. = insufficient sample, L.N.R. = listed not received