

A N A L A B S



Our reference : BU015913
 Your reference : Batch 230299
 Project code : Magnesite Project
 Report date : 12/03/99
 Report status : Final
 Page : 1 of 3

Analabs Pty. Ltd.
 ACN 004 591 664
 14 Thirkell St, Burnie
 Tasmania 7320
 Telephone : (03) 6431 6837
 Facsimile : (03) 6431 8890

ANALYTICAL DATA

Sample	MgO	CaO	SiO ₂	Fe ₂ O ₃		
MC46 123.0-124.0	43.34	2.83	0.15	2.75		
MC46 124.0-125.0	42.93	3.39	0.19	2.75		
MC46 125.0-126.0	43.12	2.77	0.16	2.89		
MC46 126.0-127.0	40.79	4.69	0.27	4.10		
MC46 127.0-128.0	31.09	17.26	1.25	2.20		
MC46 129.0-130.0	36.89	10.25	1.27	2.39		
MC46 130.0-131.0	40.57	5.17	1.28	2.84		
MC46 131.0-132.0	42.16	3.89	0.19	2.70		
MC46 132.0-133.0	41.20	5.27	0.20	2.65		
MC46 133.0-134.0	42.58	3.13	0.59	2.75		
MC46 134.0-135.0	41.50	4.34	1.08	2.60		
MC46 135.0-136.0	42.25	4.03	0.31	2.55		
MC46 136.0-137.0	42.31	4.08	0.20	2.54		
MC46 137.0-138.0	42.34	3.83	0.57	2.72		
MC46 138.0-139.0	42.25	4.11	0.24	2.58		
MC46 139.0-140.0	40.65	6.06	0.23	2.50		
MC46 140.0-141.0	39.89	6.58	0.78	2.45		
MC46 141.0-142.0	37.54	9.82	0.27	2.46		
MC46 142.0-143.9	33.96	8.72	6.10	4.56		
MC46 160.5-162.0	25.04	23.10	4.48	2.75		
MC46 162.0-163.0	26.38	21.22	6.47	2.21		
MC46 163.0-164.0	36.06	9.52	5.21	2.86		
MC46 164.0-165.0	37.41	9.56	1.40	2.48		
MC46 165.0-166.0	38.45	6.97	4.10	2.87		
MC46 166.0-167.0	38.18	6.59	9.80	1.92		
MC46 167.0-168.0	38.59	5.51	11.67	2.11		
MC46 168.0-169.0	41.55	4.02	5.24	2.11		
MC46 169.0-170.0	42.52	3.36	2.65	2.13		
MC46 170.0-171.0	43.33	3.25	1.34	2.21		
MC46 171.0-172.0	43.52	2.80	2.32	2.18		
MC46 172.0-173.0	43.59	2.64	1.43	1.92		
MC46 173.0-174.0	41.35	4.92	3.17	1.94		
MC46 174.0-175.0	41.97	3.35	5.05	2.00		
MC46 175.0-176.0	40.71	4.20	5.72	2.04		
MC46 176.0-177.0	42.77	1.91	7.24	1.94		
MC46 177.0-178.0	42.46	1.86	9.81	1.70		
MC46 178.0-179.0	43.68	1.74	3.42	1.81		
MC46 179.0-180.0	42.06	2.81	7.18	1.78		
MC46 180.0-181.5	32.57	15.58	3.81	1.30		
MC46 204.5-206.0	24.03	25.39	1.99	1.82		
MC46 206.0-207.0	32.03	16.45	2.32	1.30		
MC46 207.0-208.0	29.65	19.34	1.61	1.23		
MC46 208.0-209.0	27.72	19.89	4.22	2.06		
MC46 209.0-210.0	32.83	15.10	2.40	1.34		
MC46 210.0-211.0	37.47	9.84	2.91	1.00		
MC46 211.0-212.0	36.18	12.08	1.11	1.00		
MC46 212.0-213.0	35.60	12.70	0.71	1.18		
MC46 213.0-214.0	31.87	17.22	0.96	1.16		
MC46 214.0-215.0	39.40	8.29	0.43	1.06		
MC46 215.0-216.0	32.23	14.33	3.85	1.95		
Method	X408	X408	X408	X408		
Units	%	%	%	%		

170-180

10m. 42.54 MgO.

2.95 CaO

4.66 SiO₂

2.16.