



Our reference : BU015981  
 Your reference : Batch 110399  
 Project code : Magnesite Project  
 Report date : 30/03/99  
 Report status : Final  
 Page : 1 of 2

Analabs Pty. Ltd.  
 ACN 004 591 664  
 14 Thirkell St, Burnie  
 Tasmania 7320  
 Telephone : (03) 6431 6837  
 Facsimile : (03) 6431 8890

**FAXED**

**ANALYTICAL DATA**

Sample	MgO	CaO	SiO2	Fe2O3		
MC 48A 108.0 109.0	25.11	12.11	23.56	1.43		
MC 48A 109.0 110.0	41.65	2.82	4.34	2.09		
MC 48A 110.0 111.0	43.81	2.16	0.52	2.60		
MC 48A 111.0 112.0	41.04	4.42	1.14	2.86		
MC 48A 112.0 113.0	41.82	2.02	3.69	3.22		
MC 48A 113.0 114.0	40.98	3.63	3.80	2.74	<i>9m almost.</i>	
MC 48A 114.0 115.0	41.28	3.09	3.27	3.19		
MC 48A 115.0 116.0	41.00	4.92	1.63	2.92		
MC 48A 116.0 117.0	40.45	5.38	1.79	2.45		
MC 48A 117.0 118.0	40.53	2.37	5.27	3.67		
MC 48A 127.0 128.0	39.60	1.81	10.80	1.63		
MC 48A 128.0 129.0	37.90	2.42	13.29	1.83		
MC 48A 129.0 130.0	38.57	1.82	13.99	1.74		
MC 48A 130.0 131.0	35.64	2.99	17.14	1.72		
MC 48A 131.0 132.0	38.24	4.04	11.11	1.64		
MC 48A 132.0 132.6	--	--	--	--	?	
MC 48A 133.0 134.0	39.71	3.56	14.78	1.49		
MC 48A 134.0 135.0	43.56	3.38	2.35	1.29		
MC 48A 135.0 136.0	43.20	3.26	2.71	1.62		
MC 48A 136.0 137.0	42.32	4.34	1.07	1.99		
MC 48A 137.0 138.0	34.26	12.60	4.93	1.53		
MC 48A 138.0 139.0	20.95	26.07	8.85	1.02		
MC 48A 139.0 140.0	20.72	26.76	7.73	0.97		
MC 48A 140.0 141.0	24.96	22.61	10.79	0.62		
MC 48A 141.0 142.0	37.84	8.68	8.00	0.88		
MC 48A 142.0 143.0	35.36	11.10	7.70	0.80		
MC 48A 143.0 144.0	38.82	8.99	2.50	0.96		
MC 48A 144.0 145.0	40.71	5.37	6.58	1.04		
MC 48A 145.0 146.0	42.23	3.46	5.48	1.18		
MC 48A 146.0 147.0	39.74	4.46	11.22	1.55		
MC 48A 147.0 148.0	38.60	3.49	15.45	1.60		
MC 48A 148.0 149.0	42.82	2.66	4.53	1.89		
MC 48A 149.0 150.0	39.06	2.83	10.67	2.03		
MC 48A 150.0 151.0	38.34	1.52	14.85	1.78		
MC 48A 151.0 152.0	43.38	1.86	4.05	1.56		
MC 48A 152.0 153.0	41.53	1.33	8.26	1.65		
MC 48A 153.0 154.0	24.31	7.53	33.40	1.75		
MC 48A 154.0 155.0	32.16	1.63	26.36	1.76		
MC 48A 155.0 156.0	40.19	4.87	4.23	2.19		
MC 48A 156.0 157.0	26.42	13.28	17.85	2.17		
MC 48A 157.0 158.0	38.98	6.58	4.79	1.75		
MC 48A 158.0 159.0	41.57	2.28	6.74	2.09		
MC 48A 159.0 160.0	22.86	22.90	10.50	0.99		
MC 48A 160.0 161.0	28.59	11.66	15.14	2.04		
MC 48A 161.0 162.0	34.98	11.41	0.53	3.37		
MC 48A 200.0 201.0	39.09	7.43	3.89	0.64		
MC 48A 201.0 202.0	35.86	10.74	4.71	0.52		
MC 48A 202.0 203.0	31.24	17.33	2.56	0.47		
MC 48A 203.0 204.0	34.39	13.20	3.34	0.62		
MC 48A 204.0 205.0	34.76	14.30	0.86	0.73		
Method	X408	X408	X408	X408		
Units	%	%	%	%		
Detection Limit	0.01	0.01	0.05	0.01		

Notes: N.A. = not analysed, -- = element not determined, I.S. = insufficient sample, L.N.R. = listed not received