



Our reference : BU016039
 Your reference : Batch 190399
 Project code : Magnesite
 Report date : 15/04/99
 Report status : Final
 Page : 4 of 5

Analabs Pty. Ltd.
 ACN 004 591 664
 14 Thirkell St, Burnie
 Tasmania 7320
 Telephone : (03) 6431 6837
 Facsimile : (03) 6431 8890

ANALYTICAL DATA

Sample	MgO	CaO	SiO ₂	Fe ₂ O ₃		
MC52 165.0 166.0	37.96	1.48	13.57	2.65		
MC52 166.0 167.0	36.61	0.78	17.94	2.32		
MC52 167.0 168.0	39.02	0.65	12.87	2.18		
MC52 168.0 169.0	38.16	1.27	13.67	2.18		
MC52 169.0 170.0	39.32	2.79	9.48	2.01		
MC52 170.0 171.0	35.92	2.78	16.50	1.84		
MC52 171.0 172.0	38.33	2.86	11.40	1.91		
MC52 172.0 173.0	37.98	2.49	12.36	1.95		
MC52 173.0 174.0	36.48	2.40	15.39	2.04		
MC52 174.0 175.0	38.87	3.89	7.90	2.04		
MC52 175.0 176.0	38.06	6.05	6.29	1.88		
MC52 176.0 177.0	39.17	4.56	6.38	1.99		
MC52 177.0 178.0	40.33	2.99	7.00	2.01		
MC52 178.0 179.0	38.59	3.37	9.04	2.18		
MC52 179.0 180.0	38.90	3.01	9.37	2.01		
MC52 180.0 181.0	42.04	2.97	3.52	1.92		
MC52 181.0 182.0	42.30	2.33	3.62	1.94		
MC52 182.0 183.0	42.16	2.46	3.68	2.19		
MC52 183.0 184.0	40.56	3.75	4.86	2.13		
MC52 184.0 185.0	41.21	3.16	4.71	2.15		180-193m
MC52 185.0 186.0	40.94	3.87	3.49	2.22		
MC52 186.0 187.0	40.68	4.44	3.35	2.11		
MC52 187.0 188.0	41.70	3.08	3.93	2.03		
MC52 188.0 189.0	43.04	2.14	2.91	1.87		
MC52 189.0 190.0	42.42	2.69	3.32	1.88		13m. 41.78 MgO. 2.93 CaO 3.88 SiO ₂
MC52 190.0 191.0	42.23	2.67	3.55	1.84		
MC52 191.0 192.0	42.93	2.32	2.40	1.77		
MC52 192.0 193.0	40.98	2.22	7.10	1.63		
MC52 193.0 194.0	38.43	3.06	10.53	1.85		
MC52 194.0 195.0	42.06	3.25	2.81	1.67		1.97 Fe ₂ O ₃ .
MC52 195.0 196.0	40.31	4.08	5.41	1.56		
MC52 196.0 197.0	39.44	4.18	6.98	1.84		
MC52 197.0 198.0	41.81	3.70	3.31	1.58		
MC52 198.0 199.0	41.35	3.36	4.23	1.53		
MC52 199.0 200.0	41.84	3.30	3.78	1.74		
MC52 200.0 201.0	42.19	2.97	4.55	1.67		
MC52 201.0 202.0	42.70	2.34	4.14	1.64		
MC52 202.0 203.0	42.99	2.59	3.35	1.62		
MC52 203.0 204.0	42.95	3.03	2.58	1.68		
MC52 204.0 205.0	43.81	2.76	1.27	1.60		200-210m:
MC52 205.0 206.0	43.36	3.09	1.03	1.87		
MC52 206.0 207.0	41.02	3.68	4.40	2.15		
MC52 207.0 208.0	42.13	2.76	3.81	2.16		
MC52 208.0 209.0	42.84	3.75	1.20	1.73		
MC52 209.0 210.0	43.25	2.68	2.12	1.82		120m: 42.72 MgO. 2.96 CaO 2.84 SiO ₂
MC52 210.0 211.0	42.19	4.03	2.27	1.62		
MC52 211.0 212.0	43.16	2.75	2.44	1.71		
MC52 212.0 213.0	41.55	4.17	3.33	1.79		
MC52 213.0 214.0	40.22	5.55	3.24	1.99		
MC52 214.0 215.0	39.57	4.88	6.06	1.66		1.79 Fe ₂ O ₃ .
Method	X408	X408	X408	X408		
Units	%	%	%	%		
Detection Limit	0.01	0.01	0.05	0.01		

Notes: N.A. = not analysed, -- = element not determined, I.S. = insufficient sample, L.N.R. = listed not received