

Robza

828375

A N A L A B S



Our reference : BU016172
Your reference : Batch 150499
Project code : Magnesite
Report date : 06/05/99
Report status : Final
Page : 1 of 5

Analabs Pty. Ltd.
ACN 004 591 664
14 Thirkell St, Burnie
Tasmania 7320
Telephone : (03) 6431 6837
Facsimile : (03) 6431 8890

ANALYTICAL DATA

Sample	MgO	CaO	SiO2	Fe2O3		
MC53 244 245	44.18	2.94	0.97	1.02		
MC53 245 246	43.64	3.25	1.84	1.02		
MC53 246 247	44.71	2.11	0.61	0.97		
MC53 247 248	44.84	2.41	0.20	0.94		
MC53 248 249	42.60	4.01	0.97	1.02		
MC53 249 250	42.52	3.97	2.29	1.04		
MC53 250 251	41.05	5.58	2.18	1.06		
MC53 251 252	43.40	4.26	<0.05	0.95		
MC53 252 253	40.36	7.61	<0.05	1.06		
MC53 253 254	43.77	3.71	0.18	1.09		
MC53 254 255	42.68	4.26	1.39	1.16		
MC53 255 256	43.25	3.84	0.39	1.28		
MC53 256 257	36.01	13.32	0.16	1.07		
MC53 257 258	43.90	3.49	0.35	1.00		
MC53 258 259	44.46	2.98	0.42	1.02		
MC53 259 260	42.69	4.88	0.54	1.04		
MC53 260 261	41.95	4.79	1.70	0.95		
MC53 261 262	43.15	3.59	1.05	0.95		
MC53 262 263	43.33	3.05	1.46	0.95		
MC53 263 264	44.27	2.43	1.48	0.97		
MC53 264 265	44.36	2.12	0.67	0.89		
MC53 265 266	44.67	2.53	0.82	0.91		
MC53 266 267	44.33	2.34	1.10	0.87		
MC53 267 268	43.32	3.64	1.18	0.87		
MC53 268 269	44.59	1.55	1.99	0.80		
MC53 269 270	44.85	1.80	1.31	0.83		
MC53 270 271	45.57	1.35	0.58	0.80		263-369.
MC53 271 272	44.92	2.13	0.54	0.78		105mm
MC53 272 273	43.36	3.18	2.11	0.83		
MC53 273 274	43.80	1.93	2.85	0.80		
MC53 274 275	43.74	2.41	2.23	0.81		
MC53 275 276	44.57	1.98	1.48	0.78		
MC53 276 277	44.25	2.52	1.33	0.88		
MC53 277 278	43.03	4.24	0.50	1.16		
MC53 278 279	44.57	2.10	0.44	1.27		
MC53 279 280	45.32	1.52	1.25	0.99		
MC53 284.4 286	43.18	2.70	2.70	1.43		<gap
MC53 286 287	44.25	3.14	<0.05	1.05		
MC53 287 288	44.47	3.16	<0.05	0.95		
MC53 288 289	45.43	1.99	<0.05	0.92		
MC53 289 290	45.28	1.97	<0.05	0.88		
MC53 290 291	45.35	1.65	<0.05	0.94		
MC53 291 292	43.47	2.47	2.75	0.86		
MC53 292 293	43.79	3.24	0.80	0.95		
MC53 293 294	43.79	2.99	1.33	1.12		
MC53 294 295	44.45	2.54	0.33	1.10		
MC53 295 296	44.47	2.81	0.11	0.96		
MC53 296 297	44.96	2.74	<0.05	0.93		
MC53 297 298	44.14	3.46	<0.05	0.94		
MC53 298 299	44.56	2.59	<0.05	0.88		
Method	X408	X408	X408	X408		
Units	%	%	%	%		
Detection Limit	0.01	0.01	0.05	0.01		

Notes: N.A. = not analysed, -- = element not determined, I.S. = insufficient sample, L.N.R. = listed not received