

MARIPOSA

D.D. N.B.H. No.8

Bearing 245°

Depression -45°

From	To	Run	Description	Assays		
				Pb	ag	Zn
0	11	11	No recovery			
11	76	65	Grey and light grey lst.			
76	105	29	Grey and dark grey lst.			
105	108	3	Light and grey lst.			
108	194	86	Grey and dark grey lst.			
194	227	33	Dark grey lst. Scattered white calcite with pyrtie			
227	241	14	Cavity			
241	242	1	Medium grade ore	7.5	9.2	0.9
242	245	3	Cavity			
245	247	2	Low grade ore	3.2	1.1	0.8
247	249	2	Cavity			
249	250	1	Low grade ore	3.0	1.2	0.8
250	252	2	Cavity			
252	254	2	High grade ore	21.0	6.8	3.8
254	255	1	Low grade ore	5.5	1.0	0.4
255	256	1	Cavity			
256	257	1	Low grade ore	6.2	2.0	0.8
257	264	7	Cavity			
Core recovery: 84%						
Recovery in Ore (241'-257'):						
						37%