

## MARIPOSA

D.D. N.B.H. No. 9

Bearing 245°

Depression - 45°

From	To	Run	Description	Assays		
				Pb	Ag	Zn
0	8	8	No recovery			
8	148	140	Grey lst. mottled and banded			
148	164'6"	16'6"	Grey lst. Specks and veinlets galena and pyrite in white calcite			
164'6"	166'3"	1'9"	Grey mottled lst.			
166'3"	167'9"	1'6"	Low grade ore	5.5	1.5	8.7
167'9"	170'8"	2'11"	Grey lst. replaced by white and cream carbonate			
170'8"	173'2"	2'6"	Low grade ore	0.4	0.1	3.2
173'2"	211'	38'	Grey mottled lst.	0.4	0.1	3.2
211'	214'6"	3'6"	Low grade ore	3.6	1.0	1.2
214'6"	215'11"	1'5"	High grade ore	21.0	5.2	1.1
215'11"	221'9"	5'10"	Low grade ore	0.7	0.3	0.6
221'9"	226'	4' 3"	" " "	0.8	0.4	1.1
226'	233'	7'	Grey brecciated lst.			
233'	263'	30'	Cavity			
263'	266'	3'	Grey lst.			
Core Recovery: 84%						
Recovery in Ore (211'- 226')						
					87%	