

Drill Hole Intersections (Allison's Lode, West Lode, Trial Road, Oceana)

Location	Hole ID	From (m)	To (m)	Intersection (m)	Zn%	Pb%	Ag (ppm)
West Lode	SY023	0	17	17	7.81	1.97	47
	incl.	0	12	12	10.37	2.71	64
West Lode	SY024	0	3	3	5.77	2.85	97
	incl.	0	2	2	8.28	3.76	132
		6	7	1	2.19	4.86	57
West Lode	SY025	1	3	3	1.42	0.26	0
West Lode	SY026	0	7	7	1.69	1.34	1
West Lode	SY027	0	12	12	2.21	0.63	5
	incl.	0	4	4	3.53	1.21	11
West Lode	SY028	3	21	18	5.82	1.55	23
	incl.	5	12	7	11.95	2.92	46
West Lode	SY029	11	16	5	1.19	0.20	5
West Lode	SY030	x	x	x	x	x	x
West Lode	SY031	12	13	1	1.89	0.69	8
Allison's	SY032	3	25	22	6.07	1.52	43
	incl.	3	18	15	8.59	2.04	59
	incl.	3	12	9	12.12	2.90	91
Allison's	SY033	13	28	15	2.32	0.77	20
	incl.	26	27	1	5.11	0.80	25
		43	50	7	2.17	0.33	15
Allison's	SY034	15	26	11	5.05	0.76	15
	incl.	15	19	4	7.77	1.40	30
	incl.	24	26	2	9.73	0.90	23
Allison's	SY035	0	19	19	2.13	1.17	22
	incl.	0	3	3	5.10	3.50	68
Allison's	SY036	7	14	7	13.91	3.43	48
	incl.	8	12	4	22.95	5.64	81
	incl.	9	11	2	39.00	8.63	129
Allison's	SY037	1	3	2	1.87	0.26	11
Allison's	SY038	2	8	6	1.51	0.21	7
Allison's	SY039	0	5	5	8.08	0.63	17
Allison's	SY040	0	4	4	22.37	5.19	127
Allison's	SY041	0	24	24	8.18	1.25	24
	incl.	5	21	16	11.92	1.76	33
Allison's	SY042	8	22	14	5.39	1.31	17
	incl.	13	22	9	7.44	1.32	17
Trial Road	SY043	10	11	1	0.02	1.42	x
Trial Road	SY044	x	x	x	x	x	x
Oceana	ZZE1	0	12	12	1.63	2.26	9
	incl.	0	6	6	2.45	3.24	18
Oceana	ZZE2	9	40	31	1.28	7.13	17
Oceana	ZZE3	0	1	1	0.19	3.03	9

Allison's RL	SY038	SY039	SY040	SY037	SY036	SY035	SY041	SY042	SY032	SY034	SY033
RL											
303											
302											
301											
300									No.3 shaft		Road North
299											
298										East	
297									East		
296							West	West			0-1
295											1-2
294										0-1	2-3
293								0-1	0-1	1-2	4-5
292							1-2	1-2	2-3	3-4	5-6
290						West	2-3	2-3	3-4	4-5	6-7
289							3-4	3-4	4-5	5-6	7-8
288					North		4-5	4-5	5-6	6-7	8-9
287							5-6	5-6	6-7	7-8	9-10
286							6-7	6-7	7-8	8-9	10-11
285				0-1		2-3	7-8	7-8	8-9	9-10	11-12
284				1-2		3-4	8-9	8-9	9-10	10-11	12-13
283				2-3		4-5	9-10	9-10	10-11	11-12	13-14
282				West		3-4	10-11	10-11	11-12	12-13	14-15
281						4-5	11-12	11-12	12-13	13-14	15-16
280	North	West	West			5-6	12-13	12-13	13-14	14-15	16-17
279				0-1		6-7	13-14	13-14	14-15	15-16	17-18
278				1-2		7-8	9-10	14-15	14-15	15-16	18-19
277	0-1	0-1	0-1	2-3		8-9	10-11	15-16	15-16	16-17	19-20
276	1-2	1-2	1-2	3-4		9-10	11-12	16-17	16-17	17-18	20-21
275	2-3	2-3	2-3	4-5		10-11	12-13	17-18	17-18	18-19	21-22
274	3-4	3-4	3-4	5-6		11-12	13-14	18-19	18-19	19-20	22-23
273	4-5	4-5	4-5	6-7		12-13	14-15	19-20	19-20	20-21	23-24
272	5-6	5-6	5-6	7-8		13-14	15-16	20-21	20-21	21-22	24-25
271	6-7	6-7	6-7	8-9		14-15	16-17	21-22	21-22	22-23	25-26
270	7-8	7-8	7-8	9-10		15-16	17-18	22-23	22-23	23-24	26-27
269	8-9	8-9	8-9	10-11		16-17	18-19	23-24	23-24	24-25	27-28
268	9-10	9-10	9-10	11-12		17-18	19-20	24-25	24-25	25-26	28-29
267	10-11			12-13		18-19			26-27	27-28	29-30
266	11-12			13-14		19-20			27-28	28-29	30-31
265	12-13			14-15					28-29	29-30	31-32
264	13-14								29-30	30-31	32-33
	14-15								30-31	31-32	33-34
									31-32	32-33	34-35
									32-33	33-34	35-36
									33-34	34-35	36-37
									34-35	35-36	37-38
									35-36	36-37	38-39
									36-37	37-38	39-40
									37-38	38-39	40-41
									38-39	39-40	41-42
									39-40		42-43
									40-41		43-44
									41-42		44-45
									42-43		45-46
									43-44		46-47
									44-45		47-48
									45-46		48-49
									46-47		49-50
									47-48		
									48-49		
									49-50		
									50-51		
									51-52		
									52-53		
									53-54		
									54-55		
									55-56		
									56-57		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY023		NORTHING: 5360282.208										RIG: 4WD truck, mounted rig						
AZIMUTH: Vertical		EASTING: 357350.515										DRILL TYPE: Diamond						
DIP: 90		R.L.: 290.292										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 35m		DRILL HOLE COMPLETION DATE: 19-Feb-2005										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 23-Jun-2005										PROSPECT LOCATION: West Lode, Comstock Mine						
PURPOSE: To test the depth and mineral extent of West Lode (Preliminary description log ONLY)																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY023 00-01	100%	solid, Zn-Pb, patches of FeS	0	1	9.61	3.79	56	202	32.80%	340	6	1320	X	310	39	100	0.2	
SY023 01-02	100%	solid Zn/Pb/Fe lode	1	2	19.8	17.5	370	299	16.50%	1.70%	14	240	X	150	29	280	0.3	
SY023 02-03	63%	solid Zn/Pb/Fe lode	2	3	3.78	4.7	161	496	30.30%	3.96%	50	270	X	140	36.3	110	0.1	
SY023 03-04	18%	talc, diss <5% Zn	3	4	2.45	0.85	7	30	16.30%	9.76%	396	1170	X	80	18.1	20	X	
SY023 04-05	58%	talc, diss <5% Zn	4	5	2.3	0.84	15	55	7.93%	13.50%	105	570	X	80	8.44	30	0.3	
SY023 05-06	23%	talc, broken, <5% diss Zn	5	6	3.2	1.15	21	42	5.29%	14.40%	45	210	X	90	5.47	30	0.3	
SY023 06-07	63%	talc, diss <5% sulphides	6	7	2.49	0.78	14	93	7.73%	14.60%	70	460	X	180	7.26	30	0.3	
SY023 07-08	100%	talc, diss <5% sulphides	7	8	2.11	0.96	18	168	9.50%	13.60%	90	510	X	160	12.2	30	0.3	
SY023 08-09	100%	talc, diss <5% sulphides	8	9	2.38	0.38	5	506	9.45%	9.25%	202	540	X	230	9.5	40	0.2	
SY023 09-10	82%	talc, diss <5% sulphides	9	10	1.46	0.67	5	80	22.80%	5.57%	175	790	X	220	22.9	80	0.5	
SY023 10-11	30%	talc, ZnS lode	10	11	36.8	0.51	46	272	16.10%	3460	36	720	X	180	33.3	40	0.5	
SY023 11-12	43%	talc, ZnS lode	11	12	38.1	0.43	55	665	14.00%	4010	59	370	X	190	31.9	30	0.4	
SY023 12-13	10%	talc, diss <5% sulphides	12	13	0.76	0.32	8	113	27.20%	2980	30	2350	X	390	27.4	40	X	
SY023 13-14	35%	talc, diss <5% sulphides	13	14	0.43	0.17	X	22	2.58%	2.58%	15	100	X	450	2.31	X	X	
SY023 14-15	35%	talc, diss <5% sulphides	14	15	0.09	0.06	X	X	6400	2.08%	5	X	X	520	0.16	X	X	
SY023 15-16	65%	talc, diss <5% sulphides	15	16	1.05	0.09	X	26	1.32%	1.77%	23	30	X	430	1.10	X	X	
SY023 16-17	75%	talc, diss <5% sulphides	16	17	5.91	0.24	11	77	4.12%	3.21%	102	100	X	1180	5.25	20	0.1	
SY023 17-18	35%	talc, diss <5% sulphides	17	18	0.14	0.2	5	47	3.54%	3.52%	64	80	X	6810	1.40	20	X	
SY023 18-19	73%	talc, diss <5% sulphides	18	19	0.24	0.41	9	139	4.37%	1.07%	36	150	X	610	4.46	20	X	
SY023 19-20	58%	Interbedded siltstone, sandstone	19	20	0.08	0.1	4	91	2.58%	1.50%	41	30	X	570	1.69	10	X	
SY023 20-21	45%	Interbedded siltstone, sandstone	20	21	0.09	0.08	3	90	2.42%	1.55%	33	50	X	690	1.42	X	X	
SY023 21-22	50%	Interbedded siltstone, sandstone	21	22	0.07	0.07	3	47	4.04%	3.93%	34	70	X	1010	2.12	10	X	
SY023 22-23	90%	Interbedded siltstone, sandstone	22	23	0.02	X	X	39	2.85%	2.00%	20	10	X	710	0.56	X	X	
SY023 23-24	100%	Interbedded siltstone, sandstone	23	24	X	X	X	38	2.87%	1.60%	20	X	X	650	0.53	X	X	
SY023 24-25	100%	Interbedded siltstone, sandstone	24	25	0.01	X	X	35	2.34%	1.39%	14	X	X	530	0.09	X	X	
SY023 25-26	100%	Interbedded siltstone, sandstone	25	26	0.02	0.01	X	37	3.49%	2.03%	15	20	X	850	0.37	X	X	
SY023 26-27	100%	Interbedded siltstone, sandstone	26	27	0.07	0.01	X	24	2.89%	1.82%	15	20	X	690	0.50	X	X	
SY023 27-28	100%	Interbedded siltstone, sandstone	27	28	0.09	0.06	X	35	2.64%	1.23%	16	50	X	800	0.68	X	X	
SY023 28-29	100%	Interbedded siltstone, sandstone	28	29	0.02	X	X	38	2.95%	1.40%	22	40	X	600	1.19	X	X	
SY023 29-30	100%	Interbedded siltstone, sandstone	29	30	0.01	0.01	X	42	3.01%	1.45%	22	240	X	700	1.12	X	X	
SY023 30-31	100%	Interbedded siltstone, sandstone	30	31	0.02	X	X	33	3.20%	1.61%	26	30	X	880	0.79	X	X	
SY023 31-32	100%	Interbedded siltstone, sandstone	31	32	0.02	0.01	X	15	2.29%	9710	14	10	X	750	0.28	X	X	
SY023 32-33	100%	Interbedded siltstone, sandstone	32	33	0.04	0.02	X	17	1.95%	8480	11	X	X	350	0.21	X	X	
SY023 33-34	100%	Interbedded siltstone, sandstone	33	34	X	X	X	27	2.03%	8460	13	20	X	520	0.14	X	X	
SY023 34-35	100%	Interbedded siltstone, sandstone	34	35	X	0.01	X	42	2.40%	1.01%	18	30	X	480	0.32	X	X	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY024		NORTHING: 5360309.219										RIG: 4WD truck, mounted rig						
AZIMUTH: Vertical		EASTING: 357358.455										DRILL TYPE: Air Core						
DIP: 90		R.L: 284.304										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 35m		DRILL HOLE COMPLETION DATE: 07-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 08-Jun-05										PROSPECT LOCATION: West Lode, Comstock Mine						
PURPOSE: To test the depth and mineral extent of West Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY024 0-1	N/A	high-grade lode, ZnS, PbS	0	1	10.6	5.17	157	456	21.90%	2.90%	16	1050	X	430	29.2	120	0.5	
SY024 1-2	N/A	high-grade lode, ZnS, PbS	1	2	5.95	2.35	107	464	26.20%	2.22%	19	1880	X	380	31.6	120	0.6	
SY024 2-3	N/A	talca, lode, ZnS, PbS	2	3	0.77	1.03	27	266	18.50%	6.94%	36	780	X	300	19.1	60	0.2	
SY024 3-4	N/A	talca with minor visible sulphides	3	4	0.39	0.46	4	14	3.28%	15.60%	35	150	X	260	1.58	10	0.1	
SY024 4-5	N/A	talca with minor visible sulphides	4	5	0.31	0.29	X	77	4.99%	15.40%	27	230	X	140	2.17	10	0.1	
SY024 5-6	N/A	talca with minor visible sulphides	5	6	0.45	0.43	4	49	5.96%	14.20%	42	250	X	1070	3.48	10	0.1	
SY024 6-7	N/A	talca with coarse grained >3mm (Pb/Zn) upto 5%	6	7	2.19	4.86	57	272	13.00%	9.55%	38	830	X	2960	12.5	40	0.2	
SY024 7-8	N/A	talca with >10%ZnS, PbS	7	8	0.71	1.73	25	149	10.90%	10.00%	40	1240	X	1.88%	10	30	0.2	
SY024 8-9	N/A	shale	8	9	0.17	0.22	X	70	5.74%	2.84%	89	280	X	1830	5.02	20	0.1	
SY024 9-10	N/A	shale	9	10	0.14	0.22	X	81	4.68%	1.68%	94	200	X	820	4.21	30	0.1	
SY024 10-11	N/A	shale	10	11	0.11	0.09	X	73	4.80%	2.02%	78	150	X	850	4.14	20	0.2	
SY024 11-12	N/A	shale	11	12	0.08	0.08	79	103	4.58%	1.89%	68	130	X	740	4.17	20	0.2	
SY024 12-13	N/A	shale	12	13	0.07	0.08	X	59	3.70%	1.59%	59	100	X	760	3.34	10	0.2	
SY024 13-14	N/A	shale	13	14	0.04	0.05	X	41	2.63%	1.14%	52	100	X	490	2.29	X	0.1	
SY024 14-15	N/A	shale	14	15	0.03	0.04	X	51	3.97%	1.38%	45	80	X	750	3.6	X	0.1	
SY024 15-16	N/A	shale	15	16	0.04	0.03	X	38	2.41%	1.19%	52	50	X	690	1.93	X	X	
SY024 16-17	N/A	shale, light-gray mudstone/siltstone	16	17	0.03	0.02	X	29	3.05%	1.84%	32	60	X	700	1.94	X	0.1	
SY024 17-18	N/A	shale, siltstone	17	18	0.11	0.03	X	52	3.36%	1.71%	58	260	X	640	2.39	X	0.1	
SY024 18-19	N/A	cavity, shale, light-brown talca?, mudstone?	18	19	0.55	0.05	X	24	8.38%	8.25%	62	180	X	640	5.48	X	X	
SY024 19-20	N/A	cavity	19	20	0.07	X	X	22	11.50%	12.80%	24	200	X	110	4.88	X	0.2	
SY024 20-21	N/A	cavity	20	21	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 21-22	N/A	cavity	21	22	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 22-23	N/A	cavity	22	23	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 23-24	N/A	cavity	23	24	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 24-25	N/A	cavity	24	25	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 25-26	N/A	qtz, sandstone?, snow-white in colour	25	26	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 26-27	N/A	sandstone?, qtz fragments snow white, ultramafics?	26	27	0.07	X	X	7	3.47%	11.40%	X	40	X	15.20%	0.61	20	X	
SY024 27-28	N/A	white powder - sandstone?	27	28	0.08	X	X	13	4.27%	11.10%	6	50	X	16.30%	0.66	X	0.1	
SY024 28-29	N/A	brown - phyllite?	28	29	0.12	0.05	X	59	5.01%	9.54%	30	180	X	5.23%	2.96	X	0.1	
SY024 29-30	N/A	brown - phyllite?	29	30	0.05	X	X	21	4.36%	10.90%	X	100	X	16.80%	0.60	X	0.1	
SY024 30-31	N/A	qtz, phyllite?	30	31	0.03	X	91	20	4.04%	11.10%	X	210	X	18.40%	0.76	X	X	
SY024 31-32	N/A	coarse qtz, ultramafics (green), mudstone	31	32	0.09	0.02	X	17	6.44%	11.90%	21	200	X	12.00%	1.38	X	X	
SY024 32-33	N/A	medium light-tanned -brown sand	32	33	0.3	0.02	X	8	3.54%	11.60%	10	50	X	15.70%	0.72	X	X	
SY024 33-34	N/A	light gray fine- to medium sand, siltstone?	33	34	0.3	0.04	X	X	6.08%	12.50%	23	40	X	7.67%	0.47	X	X	
SY024 34-35	N/A	brown clay	34	35	0.16	0.02	X	23	3.94%	6.06%	30	50	X	5.49%	1.2	X	0.1	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY025		NORTHING: 5360322.099										RIG: 4WD truck, mounted rig								
AZIMUTH: Vertical		EASTING: 357362.419										DRILL TYPE: Air Core								
DIP: 90		R.L: 281.983										DRILLER: Tasmanian Drilling Services Pty Ltd								
TOTAL DEPTH: 35m		DRILL HOLE COMPLETION DATE: 08-Apr-05										SAMPLED BY: Paul Heath								
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 27-Jul-05										PROSPECT LOCATION: West Lode, Comstock Mine								
PURPOSE: To test the depth and mineral extent of West Lode.																				
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM		
SY025 00-01	N/A	talc	0	1	0.8	0.22	X	29	4.61%	13.50%	32	380	X	5.45%	3.51	10				
SY025 01-02	N/A	talc	1	2	1.48	0.22	X	82	7.62%	13.30%	45	590	X	1.30%	>5.00	20				
SY025 02-03	N/A	talc	2	3	1.36	0.3	X	57	5.44%	14.40%	33	460	X	3.47%	>5.00	20				
SY025 03-04	N/A	talc	3	4	0.67	0.19	X	33	4.01%	16.00%	34	280	X	8010	3.78	X				
SY025 04-05	N/A	talc	4	5	0.51	0.27	X	15	3.07%	15.70%	32	160	X	5320	2.29	X				
SY025 05-06	N/A	talc	5	6	0.37	0.23	X	7	2.75%	16.60%	25	100	X	5520	1.75	X				
SY025 06-07	N/A	talc	6	7	0.25	0.1	X	X	2.38%	17.70%	22	50	X	2250	1.19	X				
SY025 07-08	N/A	talc	7	8	0.3	0.14	X	11	3.00%	16.50%	25	110	X	5290	1.99	X				
SY025 08-09	N/A	talc	8	9	0.19	0.34	X	86	2.49%	14.30%	26	100	X	2.39%	1.6	X				
SY025 09-10	N/A	talc	9	10	0.42	0.36	X	30	3.81%	13.20%	41	180	X	1.49%	3.15	10				
SY025 10-11	N/A	talc	10	11	0.25	0.21	X	45	4.56%	10.20%	51	130	X	1.05%	3.68	10				
SY025 11-12	N/A	talc	11	12	0.3	0.2	X	45	4.70%	8.73%	58	120	X	1.51%	4.12	20				
SY025 12-13	N/A	talc	12	13	0.24	0.03	X	32	4.05%	5.48%	50	80	X	1.14%	2.75	10				
SY025 13-14	N/A	talc	13	14	0.15	0.04	X	39	4.65%	6.35%	57	80	X	5800	3.64	10				
SY025 14-15	N/A	shale	14	15	0.05	X	X	33	3.25%	2.00%	39	50	X	1190	2.39	X				
SY025 15-16	N/A	shale	15	16	0.02	X	X	31	3.16%	1.71%	36	50	X	980	2.37	X				
SY025 16-17	N/A	shale	16	17	0.04	0.02	X	70	2.97%	1.46%	59	70	X	1020	2.3	20				
SY025 17-18	N/A	shale	17	18	0.04	X	X	41	3.21%	2.17%	40	50	X	1110	1.85	X				
SY025 18-19	N/A	shale	18	19	0.03	0.01	3	35	2.79%	2.12%	32	40	X	890	0.83	X				
SY025 19-20	N/A	shale	19	20	0.07	0.04	3	33	3.25%	3.36%	36	60	X	2670	1.62	X				
SY025 20-21	N/A	shale	20	21	0.08	0.03	X	28	3.03%	2.90%	35	40	X	1920	1.27	X				
SY025 21-22	N/A	shale	21	22	0.04	0.03	X	26	3.24%	2.67%	28	30	X	1620	0.86	X				
SY025 22-23	N/A	shale	22	23	0.06	0.03	X	23	2.96%	3.13%	31	40	X	4760	0.93	X				
SY025 23-24	N/A	shale	23	24	0.07	0.02	X	39	3.31%	3.04%	36	50	X	1980	0.65	X				
SY025 24-25	N/A	shale	24	25	0.07	0.12	X	24	3.68%	2.98%	33	50	X	1840	0.53	X				
SY025 25-26	N/A	light-brown pug clay	25	26	0.04	0.02	X	41	3.04%	2.66%	30	40	X	1820	0.42	X				
SY025 26-27	N/A	cavity from 27.5m to 29m	26	27	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR				
SY025 27-28	N/A	cavity from 27.5m to 29m	27	28	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR				
SY025 28-29	N/A	medium sand	28	29	0.09	0.02	X	23	7.79%	15.80%	20	100	X	3.62%	0.706	X				
SY025 29-30	N/A	sandstone?	29	30	0.34	0.02	X	22	4.81%	16.60%	38	30	X	4.28%	1.7	X				
SY025 30-31	N/A	light-gray phyllite? Clay	30	31	0.1	0.02	X	14	3.94%	16.80%	36	20	X	4.50%	1.02	X				
SY025 31-32	N/A	sandstone?	31	32	0.18	X	X	18	7.02%	14.40%	26	30	X	6.82%	2.6	X				
SY025 32-33	N/A	white sandy powder	32	33	0.07	X	5	18	7.01%	11.50%	16	30	X	13.40%	2.38	X				
SY025 33-34	N/A	light-gray sand	33	34	0.06	X	6	19	7.75%	10.50%	14	40	X	14.00%	2.72	X				
SY025 34-35	N/A	light-gray sand	34	35	0.07	X	X	19	5.55%	12.60%	14	30	X	12.00%	1.52	X				

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY026		NORTHING: 5360276.379										RIG: 4WD truck, mounted rig							
AZIMUTH: Vertical		EASTING: 357345.928										DRILL TYPE: Air Core							
DIP: 90		R.L: 289.241										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 16m		DRILL HOLE COMPLETION DATE: 08-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 19-Jul-05										PROSPECT LOCATION: West Lode, Comstock Mine							
PURPOSE: To test the depth and mineral extent of West Lode.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY026 00-01	N/A	taic	0	1	1.91	1.12	X	43	6.92%	10.70%	91	650	X	8850	>5.00	40			
SY026 01-02	N/A	taic	1	2	1.79	1.14	X	45	6.31%	12.20%	76	460	X	6170	>5.00	50			
SY026 02-03	N/A	taic	2	3	1.94	1.29	X	33	6.88%	12.30%	139	450	X	9980	>5.00	70			
SY026 03-04	N/A	taic	3	4	1.75	1.79	X	34	6.05%	12.90%	122	380	X	1.24%	>5.00	100			
SY026 04-05	N/A	taic	4	5	1.71	1.64	5	25	5.79%	9.99%	137	280	X	2940	>5.00	90			
SY026 05-06	N/A	taic	5	6	1.18	0.89	X	23	6.73%	8.89%	145	270	X	1970	>5.00	60			
SY026 06-07	N/A	taic	6	7	1.57	1.52	X	61	5.79%	8.40%	189	270	X	4000	>5.00	90			
SY026 07-08	N/A	sand, shale?, mudstone?	7	8	0.39	0.37	X	40	2.40%	2.36%	44	80	X	1990	1.33	30			
SY026 08-09	N/A	sand, shale?, mudstone?	8	9	0.3	0.31	X	60	3.26%	2.27%	47	110	X	1090	1.9	30			
SY026 09-10	N/A	sand, shale?, mudstone?	9	10	0.16	0.22	3	78	3.63%	2.40%	44	100	X	3100	2.19	20			
SY026 10-11	N/A	sand, shale?, mudstone?	10	11	0.17	0.18	X	117	3.42%	1.58%	42	130	X	720	2.14	20			
SY026 11-12	N/A	sand, shale?, mudstone?	11	12	0.11	0.13	3	95	3.53%	1.81%	49	90	X	460	1.96	20			
SY026 12-13	N/A	sand, shale?, mudstone?	12	13	0.09	0.06	X	89	3.63%	2.50%	29	340	X	3440	1.53	20			
SY026 13-14	N/A	sand, shale?, mudstone?	13	14	0.43	0.15	5	43	2.59%	1.21%	36	250	X	680	1.73	20			
SY026 14-15	N/A	sand, shale?, mudstone?	14	15	0.16	0.12	4	66	2.74%	1.47%	31	50	X	620	0.77	10			
SY026 15-16	N/A	silty clay	15	16	0.4	0.43	4	33	3.08%	2.30%	49	80	X	440	1.27	30			

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY027		NORTHING: 5360279.808										RIG: 4WD truck, mounted rig							
AZIMUTH: Vertical		EASTING: 357351.542										DRILL TYPE: Air Core							
DIP: 90		R.L.: 290.182										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 35m		DRILL HOLE COMPLETION DATE: 09-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 27-Jul-05										PROSPECT LOCATION: West Lode, Comstock Mine							
PURPOSE: To test the depth and mineral extent of West Lode (Preliminary description log ONLY)																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY027 00-01	N/A	solid, Zn-Pb, patches of FeS	0	1	2.59	1.47	12	250	25.20%	2.80%	87	2410 X	410	>5.00	60				
SY027 01-02	N/A	solid Zn/Pb/Fe lode	1	2	4.97	1.51	12	168	17.00%	5.15%	129	1430 X	260	>5.00	60				
SY027 02-03	N/A	solid Zn/Pb/Fe lode	2	3	4.47	1.00	7	105	15.00%	6.47%	184	2830 X	180	>5.00	70				
SY027 03-04	N/A	taic, diss <5% Zn	3	4	2.08	0.87	13	142	14.00%	9.47%	104	940 X	240	>5.00	50				
SY027 04-05	N/A	taic, diss <5% Zn	4	5	1.85	0.45	4	55	7.42%	11.90%	84	410 X	260	>5.00	30				
SY027 05-06	N/A	taic, broken, <5% diss Zn	5	6	0.88	0.19 X		41	5.95%	9.71%	71	180 X	610	4.27	20				
SY027 06-07	N/A	taic, diss <5% sulphides	6	7	2.4	0.51 X	4	281	6.85%	12.20%	120	480 X	200	>5.00	30				
SY027 07-08	N/A	taic, diss <5% sulphides	7	8	2.08	0.25 X		118	5.31%	13.30%	135	320 X	190	4.77	20				
SY027 08-09	N/A	taic, diss <5% sulphides	8	9	1.65	0.24 X		91	4.35%	9.07%	139	360 X	280	4.45	20				
SY027 09-10	N/A	taic, diss <5% sulphides	9	10	1.75	0.27 X		28	5.25%	13.90%	92	330 X	110	3.79	20				
SY027 10-11	N/A	taic, ZnS lode	10	11	0.58	0.23 X		32	2.61%	4.91%	53	150 X	280	2.22	10				
SY027 11-12	N/A	taic, ZnS lode	11	12	1.24	0.53	4	60	7.06%	9.17%	130	440 X	350	>5.00	30				
SY027 12-13	N/A	taic, diss <5% sulphides	12	13	0.99	0.53	4	63	7.27%	8.44%	168	550 X	430	>5.00	40				
SY027 13-14	N/A	taic, diss <5% sulphides	13	14	0.44	0.38	6	83	4.55%	3.57%	126	300 X	590	4.97	30				
SY027 14-15	N/A	taic, diss <5% sulphides	14	15	0.13	0.14	5	83	3.00%	2.02%	63	110 X	670	2.43	20				
SY027 15-16	N/A	taic, diss <5% sulphides	15	16	0.12	0.17 X		85	3.42%	2.29%	70	120 X	1710	3.05	20				
SY027 16-17	N/A	taic, diss <5% sulphides	16	17	0.14	0.12 X		104	2.85%	2.42%	50	120 X	740	1.65	20				
SY027 17-18	N/A	taic, diss <5% sulphides	17	18	0.12	0.08	4	144	2.49%	1.68%	51	90 X	380	1.85	10				
SY027 18-19	N/A	taic, diss <5% sulphides	18	19	0.05	0.03 X		47	2.76%	1.92%	46	70 X	590	1.66 X					
SY027 19-20	N/A	Interbedded siltstone, sandstone	19	20	0.04	0.02 X		35	4.53%	6.18%	46	70 X	1780	1.54 X					
SY027 20-21	N/A	Interbedded siltstone, sandstone	20	21	0.41	0.31 X		57	5.34%	7.29%	81	190 X	2070	2.96	20				
SY027 21-22	N/A	Interbedded siltstone, sandstone	21	22	0.11	0.08 X		71	4.88%	5.84%	53	100 X	1540	2.12 X					
SY027 22-23	N/A	Interbedded siltstone, sandstone	22	23	0.04	0.03 X		36	3.57%	2.70%	27	40 X	840	1.22 X					
SY027 23-24	N/A	Interbedded siltstone, sandstone	23	24	0.03	0.02 X		60	3.80%	2.36%	40	140 X	730	1.92 X					
SY027 24-25	N/A	Interbedded siltstone, sandstone	24	25	0.07	0.05 X		61	3.69%	2.39%	29	100 X	770	1.75 X					
SY027 25-26	N/A	Interbedded siltstone, sandstone	25	26	0.05	0.04 X		58	3.52%	2.26%	34	120 X	780	1.49 X					
SY027 26-27	N/A	Interbedded siltstone, sandstone	26	27	0.07	0.05 X		46	3.73%	2.10%	33	100 X	730	1.36 X					
SY027 27-28	N/A	Interbedded siltstone, sandstone	27	28	0.26	0.13 X		32	3.89%	2.67%	53	110 X	1340	2.01 X					
SY027 28-29	N/A	Interbedded siltstone, sandstone	28	29	0.12	0.02 X		84	3.53%	1.88%	35	30 X	670	0.68 X					
SY027 29-30	N/A	Interbedded siltstone, sandstone	29	30	0.02 X		X	58	3.70%	1.45%	31	30 X	650	0.97 X					
SY027 30-31	N/A	Interbedded siltstone, sandstone	30	31	0.02 X		X	35	3.19%	1.15%	32	30 X	510	1.05 X					
SY027 31-32	N/A	Interbedded siltstone, sandstone	31	32	0.02 X		X	23	2.66%	1.11%	22	20 X	610	0.48 X					
SY027 32-33	N/A	Interbedded siltstone, sandstone	32	33	0.03 X			24	3.26%	1.29%	23	30 X	750	0.88 X					
SY027 33-34	N/A	Interbedded siltstone, sandstone	33	34	0.16	0.02 X		73	2.93%	1.48%	24	30 X	930	0.45 X					
SY027 34-35	N/A	Interbedded siltstone, sandstone	34	35	0.03	0.01 X		27	3.24%	1.48%	26	30 X	880	0.50 X					

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY028		NORTHING: 5360291.043										RIG: 4WD truck, mounted rig								
AZIMUTH: 125		EASTING: 357346.593										DRILL TYPE: Air Core								
DIP: 60		R.L: 288.677										DRILLER: Tasmanian Drilling Services Pty Ltd								
TOTAL DEPTH: 30m		DRILL HOLE COMPLETION DATE: 09-Apr-05										SAMPLED BY: Paul Heath								
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 24-Jun-05										PROSPECT LOCATION: West Lode, Comstock Mine								
PURPOSE: To test the depth and mineral extent of West Lode.																				
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM		
SY028 00-01	N/A	talc, no visible sulphides	0	1	0.29	0.3	X	20	3.52%	14.10%	34	330	X	210	3.3	30	0.1			
SY028 01-02	N/A	talc, <2% sulphides	1	2	0.64	0.64	X	16	2.91%	17.00%	31	140	X	60	2.57	40	X			
SY028 02-03	N/A	talc, visible ZnS	2	3	0.63	0.65	X	11	2.17%	12.90%	23	90	X	320	1.54	20	0.1			
SY028 03-04	N/A	talc, visible sulphides present	3	4	1.22	0.48		163	16.20%	6.72%	27	1860	X	260	18.8	40	0.2			
SY028 04-05	N/A	talc, visible sulphides present	4	5	4.21	1.05	19	114	7.94%	6.86%	62	790	X	170	9.65	50	0.2			
SY028 05-06	N/A	talc, ZnS/Pbs visible 5-10%, 1-3cm Zn pieces - lode	5	6	12.9	1.83	43	251	7.60%	10.70%	110	420	X	170	12.7	90	0.3			
SY028 06-07	N/A	talc, ZnS/Pbs visible 5-10%, 1-3cm Zn pieces - lode	6	7	12.4	2.58	45	110	8.76%	10.40%	41	220	X	190	13.3	100	0.3			
SY028 07-08	N/A	talc, visible chips of ZnS	7	8	1.08	0.74	9	31	4.75%	15.80%	41	190	X	100	4.22	30	X			
SY028 08-09	N/A	talc, visible sulphides	8	9	1.05	0.5	5	42	4.82%	14.90%	51	360	X	180	4.52	30	0.1			
SY028 09-10	N/A	talc, massive sulphide ZnS/Pb 20-30% lode	9	10	23.3	8.36	120	187	9.46%	5.24%	43	340	40	230	22.3	190	0.3			
SY028 10-11	N/A	talc, massive sulphide ZnS/Pb 20-30% lode	10	11	25.3	4.27	65	536	16.70%	2.77%	33	1010	40	330	31.9	160	0.3			
SY028 11-12	N/A	talc, visible FeS2, ZnS, PbS - 5-10%	11	12	7.6	2.13	35	277	13.80%	8.45%	68	1420	X	230	18.1	100	0.2			
SY028 12-13	N/A	talc, minor sulphides	12	13	3.11	0.59	13	192	15.70%	9.62%	77	930	X	180	17.20	50	0.1			
SY028 13-14	N/A	talc, minor sulphides	13	14	2.72	0.72	13	119	9.53%	13.10%	55	730	X	110	9.24	50	0.1			
SY028 14-15	N/A	talc, minor sulphides	14	15	1.55	0.32	5	47	5.72%	11.70%	55	290	X	120	4.74	20	X			
SY028 15-16	N/A	talc & wet sand, FeS2 visible	15	16	1.04	0.31	5	50	5.18%	7.92%	66	210	X	480	3.52	20	0.2			
SY028 16-17	N/A	talc, minor sulphides	16	17	1.04	0.47	4	34	8.18%	13.30%	110	220	X	130	5.38	30	X			
SY028 17-18	N/A	talc, minor sulphides	17	18	1.76	1.15	16	83	13.20%	10.90%	97	900	X	190	12.30	60	X			
SY028 18-19	N/A	talc, minor sulphides	18	19	1.76	0.74	7	57	6.34%	9.58%	59	430	X	150	5.32	40	0.1			
SY028 19-20	N/A	talc, minor sulphides	19	20	1.46	0.79	5	32	4.53%	13.40%	54	320	X	190	3.45	60	0.2			
SY028 20-21	N/A	talc, cap rock?, qtz?	20	21	1.23	0.94	6	22	4.47%	9.02%	82	410	X	2220	2.13	50	0.1			
SY028 21-22	N/A	shale?	21	22	0.25	0.15	X	64	2.64%	2.53%	61	130	X	560	1.73	20	0.1			
SY028 22-23	N/A	shale?	22	23	0.2	0.11	X	103	7.48%	7.52%	49	200	X	1440	4.04	20	0.2			
SY028 23-24	N/A	shale?	23	24	0.23	0.14	X	85	4.93%	5.26%	40	80	X	750	2.17	10	0.2			
SY028 24-25	N/A	Not logged	24	25	0.71	0.45	7	60	4.00%	4.01%	38	220	X	500	3.06	20	0.2			
SY028 25-26	N/A	Not logged	25	26	0.05	0.05	X	63	2.59%	2.06%	24	40	X	490	0.86	X	0.1			
SY028 26-27	N/A	Not logged	26	27	0.04	0.04	X	83	2.74%	2.06%	29	50	X	710	1.17	X	0.1			
SY028 27-28	N/A	Not logged	27	28	0.06	0.03	X	41	2.62%	1.41%	26	40	X	530	1.42	X	0.1			
SY028 28-29	N/A	Not logged	28	29	0.06	0.03	X	19	2.47%	1.56%	14	20	X	470	0.54	X	X			
SY028 29-30	N/A	Not logged	29	30	0.14	0.14	X	21	3.06%	2.23%	23	60	X	540	1.35	X	X			

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY029		NORTHING: 5360292.485										RIG: 4WD truck, mounted rig						
AZIMUTH: 263		EASTING: 357366.041										DRILL TYPE: Air Core						
DIP: 70		R.L: 282.365										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 35m		DRILL HOLE COMPLETION DATE: 10-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 02-Aug-05										PROSPECT LOCATION: West Lode, Comstock Mine						
PURPOSE: To test the depth and mineral extent of West Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY029 00-01	N/A	taic	0	1	0.41	0.02 X		7	1.42%	18.80%	41	70 X		50	0.72 X			
SY029 01-02	N/A	taic	1	2	0.38 X		X	5	2.08%	19.40%	78	120 X		60	1.49 X			
SY029 02-03	N/A	taic	2	3	0.44	0.03 X		X	1.81%	12.80%	77	120 X		150	1.72 X			
SY029 03-04	N/A	taic	3	4	0.93	0.12 X		15	3.59%	15.90%	122	240 X		150	3.99	10		
SY029 04-05	N/A	taic	4	5	0.81	0.1 X		18	4.49%	16.30%	120	240 X		80	>5.00 X			
SY029 05-06	N/A	taic	5	6	0.75	0.1 X		22	4.57%	15.10%	140	280 X		110	>5.00	10		
SY029 06-07	N/A	taic	6	7	0.77	0.12 X		11	6.57%	13.90%	229	380 X		90	>5.00	10		
SY029 07-08	N/A	taic	7	8	0.67	0.13 X		11	4.06%	10.90%	111	250 X		350	4.18	10		
SY029 08-09	N/A	taic	8	9	0.55	0.1 X		8	2.72%	10.60%	69	120 X		160	2.29	10		
SY029 09-10	N/A	taic	9	10	0.49	0.14 X		81	2.88%	8.77%	72	130 X		140	2.18	10		
SY029 10-11	N/A	taic	10	11	0.55	0.07	3	87	4.46%	3.37%	141	180 X		140	4.84	20		
SY029 11-12	N/A	taic	11	12	1.68	0.3	8	221	16.10%	7.37%	138	1280 X		160	>5.00	40		
SY029 12-13	N/A	taic	12	13	1.17	0.18	6	201	24.10%	4.84%	111	2280 X		280	>5.00	50		
SY029 13-14	N/A	taic	13	14	0.33	0.07 X		98	30.90%	2.82%	98	2270 X		440	>5.00	40		
SY029 14-15	N/A	taic	14	15	1.48	0.3	8	153	14.10%	7.04%	140	1750 X		340	>5.00	40		
SY029 15-16	N/A	taic	15	16	1.29	0.15	5	52	9.99%	11.70%	125	710 X		370	>5.00	30		
SY029 16-17	N/A	Not logged	16	17	0.72	0.1 X		7	6.51%	15.00%	107	280 X		250	>5.00	20		
SY029 17-18	N/A	Not logged	17	18	0.85	0.14	3	40	6.15%	12.00%	109	370 X		1560	4.84	20		
SY029 18-19	N/A	Not logged	18	19	0.45	0.08 X		82	3.99%	6.24%	79	230 X		1.69%	2.59	20		
SY029 19-20	N/A	Not logged	19	20	0.26	0.03 X		33	4.75%	7.38%	68	180 X		3.38%	1.52	20		
SY029 20-21	N/A	Not logged	20	21	0.09	0.1 X		38	2.87%	2.79%	58	110 X		3.47%	0.54	20		
SY029 21-22	N/A	cavity 0.5m	21	22	0.19	0.06 X		57	4.61%	4.90%	55	200 X		1.65%	2.12	20		
SY029 22-23	N/A	sand	22	23	0.12	0.03 X		42	5.13%	6.69%	33	140 X		2090	1.82 X			
SY029 23-24	N/A	sand	23	24	0.09	0.03 X		59	4.01%	4.93%	33	80 X		3210	1.40 X			
SY029 24-25	N/A	sand	24	25	0.05	0.03 X		94	4.85%	4.58%	30	150 X		2340	2.08 X			
SY029 25-26	N/A	sand	25	26	0.09	0.04 X		99	3.62%	2.66%	31	150 X		1170	2.04 X			
SY029 26-27	N/A	sand	26	27	0.04	0.02 X		52	3.03%	1.70%	30	100 X		1050	1.99 X			
SY029 27-28	N/A	sand	27	28	0.13	0.03 X		41	3.11%	2.70%	33	120 X		790	1.69 X			
SY029 28-29	N/A	sand	28	29	0.12	0.04 X		65	3.34%	2.73%	38	100 X		1500	1.68 X			
SY029 29-30	N/A	sand	29	30	0.08	1.29 X		41	2.87%	2.47%	26	90 X		1150	1.22 X			
SY029 30-31	N/A	sand	30	31	0.11	0.03 X		36	2.66%	2.15%	26	90 X		1350	1.28 X			
SY029 31-32	N/A	sand	31	32	0.15	0.05 X		40	3.09%	2.29%	35	150 X		2430	1.81 X			
SY029 32-33	N/A	sand	32	33	0.1	0.04 X		21	2.83%	1.79%	36	110 X		730	2.19 X			
SY029 33-34	N/A	sand	33	34	0.09	0.04 X		40	3.15%	1.69%	25	60 X		870	1.56 X			
SY029 34-35	N/A	sand	34	35	0.25	0.1 X		42	3.13%	2.31%	33	120 X		910	1.81 X			

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY030		NORTHING: 5360314.110										RIG: 4WD truck, mounted rig						
AZIMUTH: 306		EASTING: 357366.695										DRILL TYPE: Air Core						
DIP: 65		R.L.: 279.996										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 20m		DRILL HOLE COMPLETION DATE: 10-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 19-Jul-05										PROSPECT LOCATION: West Lode, Comstock Mine						
PURPOSE: To test the depth and mineral extent of West Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY030 00-01	N/A	taic	0	1	0.44	0.04 X	X		4.55%	14.80%	73	200 X		70	>5.00 X			
SY030 01-02	N/A	taic	1	2	0.33	0.01 X			6	2.30%	9.70%	41	80 X	260	2.18 X			
SY030 02-03	N/A	taic	2	3	0.48	0.03 X			12	3.47%	12.00%	76	190 X	410	3.52	10		
SY030 03-04	N/A	taic	3	4	0.23 X		X		9	2.96%	11.80%	36	210 X	170	2.52	10		
SY030 04-05	N/A	taic	4	5	0.23 X		X		7	4.07%	16.50%	37	220 X	80	3.54	10		
SY030 05-06	N/A	taic	5	6	0.47	0.04 X			16	6.68%	12.30%	56	310 X	190	>5.00	10		
SY030 06-07	N/A	taic, shale	6	7	0.16	0.05	4		36	4.56%	2.41%	55	170 X	570	4.82	20		
SY030 07-08	N/A	taic, shale	7	8	0.13	0.03 X			32	3.87%	2.37%	49	150 X	310	3.77	10		
SY030 08-09	N/A	shale	8	9	0.21	0.03 X			38	3.89%	2.52%	56	140 X	430	4.06	20		
SY030 09-10	N/A	shale	9	10	0.11	0.02 X			46	3.61%	1.49%	66	110 X	760	3.79	20		
SY030 10-11	N/A	shale	10	11	0.08	0.02 X			62	4.05%	1.74%	57	90 X	1130	3.92	10		
SY030 11-12	N/A	shale	11	12	0.08 X		X		32	3.61%	2.55%	30	50 X	940	2.80 X			
SY030 12-13	N/A	shale	12	13	0.04	0.01 X			40	3.27%	1.72%	46	60 X	790	2.69	10		
SY030 13-14	N/A	Interbedded shale/mudstone	13	14	0.05 X		X		47	3.97%	2.50%	34	60 X	970	2.85	10		
SY030 14-15	N/A	Interbedded shale/mudstone	14	15	0.03 X		X		42	3.26%	2.13%	29	60 X	910	2.33	10		
SY030 15-16	N/A	Interbedded shale/mudstone	15	16	0.03 X		X		53	3.70%	1.83%	43	100 X	980	2.93	20		
SY030 16-17	N/A	Interbedded shale/mudstone	16	17	0.03 X		X		60	3.79%	1.69%	44	80 X	990	3.07	20		
SY030 17-18	N/A	Interbedded shale/mudstone	17	18	0.03 X		X		53	3.61%	1.70%	43	80 X	1010	2.87	20		
SY030 18-19	N/A	Interbedded shale/mudstone	18	19	0.03 X		X		42	3.28%	1.82%	30	70 X	870	1.77	10		
SY030 19-20	N/A	Interbedded shale/mudstone	19	20	0.02 X		X		37	2.95%	2.02%	22	50 X	830	1.46 X			

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY031		NORTHING: 5360329.695										RIG: 4WD truck, mounted rig						
AZIMUTH: 327		EASTING: 357370.546										DRILL TYPE: Air Core						
DIP: 65		R.L.: 280.258										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 20m		DRILL HOLE COMPLETION DATE: 11-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 02-Aug-05										PROSPECT LOCATION: West Lode, Comstock Mine						
PURPOSE: To test the depth and mineral extent of West Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY031 00-01	N/A	taic, mudstone	0	1	0.19	0.19	5	117	6.44%	4.71%	78	370	X	710	>5.00	20		
SY031 01-02	N/A	taic, mudstone	1	2	0.33	0.18	3	34	7.79%	7.70%	56	410	X	1210	>5.00	20		
SY031 02-03	N/A	sandy soil/shale	2	3	0.26	0.14	X	55	5.73%	5.02%	76	360	X	2090	>5.00	20		
SY031 03-04	N/A	sandy soil/shale	3	4	0.26	0.11	3	59	5.75%	4.57%	72	500	X	1290	>5.00	20		
SY031 04-05	N/A	silicified shale	4	5	0.09	0.03	X	58	7.90%	5.45%	68	200	X	690	>5.00	20		
SY031 05-06	N/A	sandy soil/shale	5	6	0.12	0.04	X	54	7.02%	5.21%	57	150	X	720	>5.00	20		
SY031 06-07	N/A	sandy soil/shale	6	7	0.11	0.03	X	44	3.91%	2.88%	62	110	X	760	3.71	20		
SY031 07-08	N/A	shale	7	8	0.07	0.01	X	37	3.41%	2.76%	45	80	X	710	3.33	X		
SY031 08-09	N/A	shale	8	9	0.08	0.01	X	44	3.76%	3.69%	49	90	X	640	3.78	X		
SY031 09-10	N/A	shale	9	10	0.06	0.02	X	45	3.77%	1.56%	50	100	X	850	3.84	10		
SY031 10-11	N/A	shale	10	11	0.03	0.05	X	45	3.18%	1.18%	44	60	X	740	3.40	10		
SY031 11-12	N/A	shale	11	12	0.02	0.02	X	48	3.48%	7.720	51	50	X	580	3.52	10		
SY031 12-13	N/A	taic	12	13	1.89	0.69	8	85	6.38%	5.94%	62	360	X	660	>5.00	30		
SY031 13-14	N/A	taic with mixed shale	13	14	0.32	0.12	X	50	3.58%	1.49%	48	100	X	730	3.17	10		
SY031 14-15	N/A	taic with mixed shale	14	15	0.39	0.15	3	52	4.16%	1.76%	48	150	X	700	3.71	20		
SY031 15-16	N/A	taic with minor shale	15	16	0.95	0.34	6	69	5.41%	4.70%	53	240	X	720	4.69	30		
SY031 16-17	N/A	light-brown clay, whoite clay, qtz sandy soil	16	17	0.17	0.06	X	80	3.54%	1.66%	49	80	X	2380	2.52	10		
SY031 17-18	N/A	shale	17	18	0.04	0.02	X	72	3.23%	1.17%	60	90	X	810	2.48	20		
SY031 18-19	N/A	taic, sand, qtz, shlae	18	19	0.4	0.17	X	50	3.59%	3.55%	52	150	X	2810	2.14	20		
SY031 19-20	N/A	shale	19	20	0.07	0.03	X	36	2.87%	1.70%	25	40	X	1510	0.87	X		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY032		NORTHING: 5360647.286										RIG: 4WD truck, mounted rig							
AZIMUTH: 104		EASTING: 357570.907										DRILL TYPE: Air Core							
DIP: 65		R.L.: 294.227										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 57m		DRILL HOLE COMPLETION DATE: 11-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 23-Jun-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine							
PURPOSE: To delineate the north extension and depth of Allison's Lode zinc-lead-silver sulphides.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY032 00-01	N/A	talc/pink clay no visible sulphides	0	1	0.02	0.03	5	9	1.23%	18.40%	X	50	X	370	0.18	X	X		
SY032 01-02	N/A	talc/pink clay no visible sulphides	1	2	0.02	0.02	9	8	2.04%	16.20%	X	50	X	6570	0.09	10	X		
SY032 02-03	N/A	talc/pink clay no visible sulphides	2	3	0.04	0.16	103	47	4.35%	13.80%	X	40	X	3.90%	0.09	240	0.4		
SY032 03-04	N/A	talc, visible PbS, FeS2	3	4	2.87	6.61	171	1620	26.10%	3.53%	X	150	X	6060	28.40	200	0.4		
SY032 04-05	N/A	talc, visible ZnS, PbS, FeS2	4	5	2.09	4.13	167	1030	11.70%	9.39%	X	90	X	1.48%	12.80	210	0.6		
SY032 05-06	N/A	talc, visible PbS, FeS2	5	6	6.55	3.15	118	1120	9.94%	9.71%	5	140	X	2.47%	13.10	180	0.3		
SY032 06-07	N/A	talc, visible ZnS, PbS, FeS2	6	7	36.3	5.05	130	292	8.92%	3.60%	12	180	X	1.01%	25.10	240	0.4		
SY032 07-08	N/A	talc, visible ZnS, PbS, FeS2	7	8	4.94	1.74	52	292	6.24%	11.80%	7	120	X	4.44%	7.02	80	0.1		
SY032 08-09	N/A	talc, visible ZnS, PbS, FeS2	8	9	4.45	0.76	28	137	4.81%	12.00%	5	60	X	5.29%	3.97	50	0.1		
SY032 09-10	N/A	talc, visible ZnS, PbS, FeS2	9	10	8.59	0.85	29	106	5.62%	10.70%	10	70	X	4.25%	6.43	50	0.1		
SY032 10-11	N/A	talc, visible ZnS, PbS, FeS2	10	11	34.3	1.98	91	188	9.25%	4.04%	14	110	X	1.54%	23.20	180	0.3		
SY032 11-12	N/A	talc, visible ZnS, PbS, FeS2	11	12	8.99	1.87	31	130	7.16%	8.54%	9	110	X	2.51%	9.14	100	0.1		
SY032 12-13	N/A	Cavity	12	13	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 13-14	N/A	Cavity	13	14	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 14-15	N/A	Cavity	14	15	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 15-16	N/A	Cavity, ZnS, PbS	15	16	12	2.18	33	89	6.63%	9.48%	8	90	X	7510	10.30	70	X		
SY032 16-17	N/A	Cavity	16	17	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 17-18	N/A	Cavity, talc ZnS, PbS	17	18	7.7	2.24	40	161	7.00%	9.22%	8	100	X	1.21%	9.98	60	0.1		
SY032 18-19	N/A	Cavity	18	19	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 19-20	N/A	Cavity	19	20	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 20-21	N/A	Cavity	20	21	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 21-22	N/A	Cavity	21	22	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 22-23	N/A	Cavity	22	23	-	-	-	-	-	-	-	-	-	-	-	-	-	-	
SY032 23-24	N/A	Cavity, minor talc, ZnS	23	24	3.63	0.88	21	173	6.31%	3.88%	27	120	X	9260	5.54	60	0.1		
SY032 24-25	N/A	talc, visible ZnS, PbS, FeS2	24	25	1.23	1.98	27	59	6.79%	10.30%	8	180	X	6.31%	2.77	40	0.1		
SY032 25-26	N/A	talc, visible ZnS, PbS, FeS2	25	26	0.97	2.03	22	48	7.83%	9.93%	8	160	X	5.51%	4.22	30	X		
SY032 26-27	N/A	specs-ZnS, PbS, FeS2?, green mineral	26	27	0.72	0.55	9	200	22.40%	3.64%	10	530	X	1.99%	16.5	40	0.2		
SY032 27-28	N/A	specs PbS, >80%FeS2?	27	28	0.61	0.39	9	120	36.30%	1.01%	6	2620	X	6880	34.3	60	0.2		
SY032 28-29	N/A	~85%FeS2?, specs of ZnS/PbS, shale chips	28	29	0.56	0.67	11	74	31.70%	2.06%	20	2090	X	7770	28.7	60	0.1		
SY032 29-30	N/A	~65%FeS2?, specs of ZnS/PbS, talc, chlorite?	29	30	0.71	1.43	16	74	18.80%	3.81%	39	740	X	1.51%	14.3	60	0.1		
SY032 30-31	N/A	FeS2, shale, qtz	30	31	0.46	0.95	12	49	7.90%	3.21%	51	350	X	1.81%	4.10	40	0.1		
SY032 31-32	N/A	FeS2, shale, qtz	31	32	0.44	0.79	12	52	7.87%	2.46%	51	320	X	1.13%	5.03	40	X		
SY032 32-33	N/A	FeS2, shale, specs of PbS, orange clay	32	33	0.83	1.84	19	56	9.78%	3.48%	45	430	X	9440	7.25	50	X		
SY032 33-34	N/A	FeS, shale, specs of PbS ~1% (chert) hard	33	34	0.55	1.27	21	98	9.44%	2.96%	47	330	X	5410	7.19	60	0.1		
SY032 34-35	N/A	FeS 5%, shale 90%, carb gm blebs 2%, orange clay 3%	34	35	0.5	1.64	20	59	8.77%	2.17%	49	290	X	5250	7.81	50	0.1		
SY032 35-36	N/A	FeS, specs of PbS, qtz, carbonate specs, shale (Chert) 85%	35	36	0.28	0.63	11	91	9.58%	3.25%	49	210	X	6380	4.62	30	X		
SY032 36-37	N/A	FeS, specs of PbS, qtz, carbonate specs, shale (Chert) 85%	36	37	0.36	1.24	15	92	10.00%	2.89%	46	260	X	9120	6.69	50	X		
SY032 37-38	N/A	specs-ZnS, PbS, FeS2, shale 90%, orange & green clay blebs	37	38	0.49	1.16	12	54	7.74%	3.73%	37	240	X	1.14%	4.07	30	X		
SY032 38-39	N/A	specs-ZnS, PbS, FeS2, shale 90%, orange & green clay blebs	38	39	0.41	0.91	10	47	7.24%	3.86%	46	280	X	1.01%	3.87	30	X		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY032 39-40	N/A	specs-ZnS, PbS, FeS2, shale 90%, orange & green clay blebs	39	40	0.32	0.56	9	109	6.21%	3.24%	46	460	X	6250	3.64	40	X	
SY032 40-41	N/A	shale with qtz, green blebs <1% PbS	40	41	0.43	1.03	11	46	5.84%	3.23%	40	220	X	6720	3.61	40	X	
SY032 41-42	N/A	shale with qtz, green blebs <1% PbS	41	42	0.31	0.43	6	51	4.75%	2.54%	48	200	X	3820	3.27	30	X	
SY032 42-43	N/A	shale 85% with blebs of FeS2, green carbonate? 15% white clay	42	43	0.19	0.24	4	51	4.66%	1.96%	49	130	X	7430	3.34	30	X	
SY032 43-44	N/A	shale 75%, qtz 10%, FeS 5-10%, green & orange blebs, sandy	43	44	0.37	0.54	6	55	6.42%	3.22%	48	220	X	5970	4.06	20	X	
SY032 44-45	N/A	shale(chert), orange blebs, qtz 15%, FeS2 5%, PbS <1%	44	45	0.2	0.27	6	72	6.17%	2.38%	66	140	X	3470	4.83	30	X	
SY032 45-46	N/A	FeS2 within shale 30%, orange blebs 15% , shale 55%	45	46	0.33	0.34	4	29	3.86%	1.96%	21	160	X	3670	2.77	20	X	
SY032 46-47	N/A	shale 70%, qtz 15%, brown blebs 5%, FeS2 10%	46	47	0.2	0.47	6	24	4.45%	2.77%	14	190	X	5480	3.13	20	X	
SY032 47-48	N/A	shale, qtz, FeS2	47	48	0.13	0.12	4	78	5.79%	1.17%	50	220	X	3470	5.52	20	X	
SY032 48-49	N/A	shale, qtz, FeS2	48	49	0.13	0.11	3	56	5.49%	1.16%	69	150	X	2510	5.48	20	X	
SY032 49-50	N/A	shale, qtz, FeS2	49	50	0.22	0.5	6	33	5.58%	2.74%	40	180	X	6370	4.02	30	X	
SY032 50-51	N/A	shale, qtz, FeS2	50	51	0.08	0.12	X	45	3.74%	1.38%	64	110	X	4200	3.10	30	X	
SY032 51-52	N/A	shale, qtz, FeS2	51	52	0.07	0.08	X	45	4.24%	1.33%	60	140	X	3760	3.71	30	X	
SY032 52-53	N/A	shale, qtz, FeS2	52	53	0.14	0.33	4	48	4.67%	2.04%	57	160	X	8950	3.71	30	X	
SY032 53-54	N/A	shale, qtz, FeS2	53	54	0.08	0.11	X	57	3.51%	1.17%	47	100	X	5520	3.01	30	X	
SY032 54-55	N/A	shale, qtz, FeS2	54	55	0.1	0.06	X	54	3.72%	1.37%	61	100	X	9190	3.12	30	X	
SY032 55-56	N/A	shale, qtz, FeS2	55	56	0.18	0.52	8	57	5.43%	2.97%	54	170	X	1,52%	3.99	40	X	
SY032 56-57	N/A	shale 80%, qtz 20%, PbS <2%	56	57	0.04	0.07	X	56	3.80%	1.44%	66	110	X	6220	3.06	30	X	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY033		NORTHING: 5360672.234										RIG: 4WD truck, mounted rig						
AZIMUTH: 15		EASTING: 357564.800										DRILL TYPE: Air Core						
DIP: 60		R.L: 296.431										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 50m		DRILL HOLE COMPLETION DATE: 12-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED:										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To delineate the north extention and depth of Allison's Lode zinc-lead-silver sulphides. Drillhole parallel to strike of Allison's Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY033 00-01	N/A	qtz, surface rubble from workings, talc	0	1	0.05	0.06	X	15	7000	2.17%	X	40	X	220	0.13	X	X	
SY033 01-02	N/A	pink clay, no visible sulphides	1	2	0.04	0.02	X	9	1.00%	17.30%	X	20	X	220	0.11	X	X	
SY033 02-03	N/A	qtz, talc, clay, frag. of shale (old road works?)	2	3	0.07	0.11	X	17	1.01%	8.19%	5	40	X	940	0.29	20	X	
SY033 03-04	N/A	qtz, talc, clay, frag. of shale (old road works?)	3	4	0.06	0.1	4	16	1.02%	8.27%	6	40	X	260	0.29	10	X	
SY033 04-05	N/A	talc, ZnS, PbS <10%, orange fragments	4	5	1.7	0.63	16	46	2.43%	17.60%	7	50	X	570	2.10	40	0.1	
SY033 05-06	N/A	talc, qtz specs, dark brown fragments	5	6	0.78	0.27	7	34	1.87%	18.40%	11	50	X	490	1.46	30	X	
SY033 06-07	N/A	talc - no visible sulphides	6	7	0.41	0.19	X	13	1.69%	18.20%	15	40	X	380	1.19	30	X	
SY033 07-08	N/A	talc - no visible sulphides	7	8	0.37	0.34	X	11	2.15%	17.80%	11	40	X	1190	1.15	40	X	
SY033 08-09	N/A	talc - no visible sulphides	8	9	0.21	0.18	X	X	2.03%	18.20%	5	20	X	1470	0.36	30	X	
SY033 09-10	N/A	talc - no visible sulphides	9	10	0.19	0.17	X	5	1.54%	18.80%	11	20	X	4910	0.31	30	X	
SY033 10-11	N/A	talc - no visible sulphides	10	11	0.21	0.16	X	X	2.04%	18.20%	X	50	X	1.13%	0.29	40	X	
SY033 11-12	N/A	talc, silica cap rock - no visible sulphides	11	12	0.28	0.31	X	10	2.11%	16.20%	5	50	X	4.02%	0.51	50	X	
SY033 12-13	N/A	talc, silica cap rock - no visible sulphides	12	13	0.14	0.08	X	9	2.25%	12.60%	X	60	X	10.40%	0.28	40	X	
SY033 13-14	N/A	talc, <5% sulphides ZnS,FeS2	13	14	1.71	0.66	16	127	9.44%	12.10%	X	220	X	3.52%	9.67	90	X	
SY033 14-15	N/A	talc, <5% sulphides ZnS,FeS3	14	15	2.44	0.7	18	143	9.98%	12.70%	X	520	X	2.73%	10.7	60	X	
SY033 15-16	N/A	talc, FeS 30%, ZnS <5%	15	16	3.54	1.12	34	106	11.50%	12.40%	X	4050	X	1.28%	14.1	100	X	
SY033 16-17	N/A	talc, FeS 30%, ZnS <5%	16	17	4.9	2.63	63	149	12.10%	10.80%	6	1.40%	X	1.16%	14.9	220	X	
SY033 17-18	N/A	talc, FeS 20%, ZnS <5%	17	18	1.77	1.01	28	57	7.85%	14.70%	14	1.79%	X	4100	7.99	200	X	
SY033 18-19	N/A	talc, FeS 20%, ZnS <5%	18	19	0.57	0.28	5	14	3.26%	17.50%	10	1260	X	1300	2.05	40	X	
SY033 19-20	N/A	talc	19	20	1.9	1	23	67	7.30%	14.70%	12	7140	X	1.09%	8.02	120	X	
SY033 20-21	N/A	talc	20	21	1.01	0.69	14	29	5.73%	16.40%	10	3620	X	3990	5.49	70	X	
SY033 21-22	N/A	talc	21	22	0.97	0.48	13	22	4.65%	17.00%	10	1660	X	3180	4.22	50	X	
SY033 22-23	N/A	talc	22	23	3.1	0.39	15	28	5.10%	15.40%	11	860	X	5700	6.06	70	X	
SY033 23-24	N/A	talc	23	24	2.46	0.49	11	21	5.72%	15.40%	12	820	X	820	6.79	70	X	
SY033 24-25	N/A	talc	24	25	1.37	0.44	9	20	8.18%	14.30%	10	610	X	2190	8.85	50	X	
SY033 25-26	N/A	talc	25	26	0.84	0.3	6	18	4.40%	16.50%	10	640	X	4180	3.93	40	X	
SY033 26-27	N/A	talc, ZnS 40%, FeS2 40%, cap rock/limestone	26	27	5.11	0.8	25	74	24.60%	6.56%	X	1570	X	1070	29.9	90	X	
SY033 27-28	N/A	cap rock/limestone	27	28	2.17	0.62	16	44	17.50%	7.11%	X	1050	X	5.89%	21.8	80	X	
SY033 28-29	N/A	light gray rock, no sulphides, calcite crystals	28	29	0.35	0.19	X	15	4.64%	15.30%	15	300	X	3.26%	2.84	30	X	
SY033 29-30	N/A	light gray rock, no sulphides	29	30	0.12	0.03	X	10	3.33%	13.50%	10	100	X	12.10%	1.54	10	X	
SY033 30-31	N/A	light gray rock, no sulphides	30	31	0.06	0.02	X	9	2.74%	12.00%	10	110	X	14.90%	1.19	10	X	
SY033 31-32	N/A	light gray rock, no sulphides	31	32	0.3	0.15	X	26	5.73%	12.50%	12	570	X	7.60%	4.76	30	X	
SY033 32-33	N/A	shale	32	33	0.19	0.09	4	48	8.38%	4.91%	51	830	X	5.63%	8.80	30	0.3	
SY033 33-34	N/A	shale	33	34	0.08	0.04	4	69	5.02%	2.37%	76	220	X	1.43%	4.74	40	X	
SY033 34-35	N/A	shale	34	35	0.03	0.03	X	69	4.03%	1.63%	77	110	X	1930	3.65	20	X	
SY033 35-36	N/A	shale	35	36	0.07	0.04	3	92	4.94%	2.43%	79	150	X	5090	4.71	40	X	
SY033 36-37	N/A	shale	36	37	0.03	0.03	X	67	4.38%	1.98%	66	110	X	1640	3.86	20	X	
SY033 37-38	N/A	shale, FeS2	37	38	0.37	0.11	5	158	6.83%	2.49%	67	240	X	1520	6.49	40	X	
SY033 38-39	N/A	shale, FeS2	38	39	0.13	0.04	3	63	4.54%	1.06%	77	130	X	1520	4.73	40	X	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

<i>Drill hole ID</i>	<i>Recovery</i>	<i>Description</i>	<i>from (m)</i>	<i>to (m)</i>	<i>Zn %</i>	<i>Pb %</i>	<i>Ag PPM</i>	<i>Cu PPM</i>	<i>Fe PPM</i>	<i>Mg PPM</i>	<i>Ni PPM</i>	<i>As PPM</i>	<i>Bi PPM</i>	<i>Ca PPM</i>	<i>S %</i>	<i>Sb PPM</i>	<i>Hg PPM</i>	<i>Au PPM</i>
SY033 39-40	N/A	shale, FeS2	39	40	0.38	0.13	5	57	6.09%	1.56%	66	300 X		2880	6.21	40 X		
SY033 40-41	N/A	shale, FeS2	40	41	0.84	0.21	9	56	9.03%	2.12%	54	430 X		4340	10.10	60 X		
SY033 41-42	N/A	shale, FeS2	41	42	0.75	0.16	8	51	7.67%	2.88%	47	340 X		6560	8.31	60 X		
SY033 42-43	N/A	shale, FeS2	42	43	0.43	0.13	7	50	5.84%	1.86%	58	370 X		4260	6.57	50 X		
SY033 43-44	N/A	shale	43	44	2.66	0.34	14	64	11.40%	2.52%	39	600 X		6930	14.40	70 X		
SY033 44-45	N/A	shale	44	45	4.27	0.47	22	85	14.10%	1.46%	45	520 X		3440	18.40	90	0.1	
SY033 45-46	N/A	shale	45	46	2.07	0.33	16	110	11.00%	9990	56	390 X		2250	13.30	60 X		
SY033 46-47	N/A	shale	46	47	2.1	0.33	16	67	12.90%	1.77%	48	440 X		6670	15.80	60 X		
SY033 47-48	N/A	shale	47	48	1.62	0.23	11	52	9.07%	1.85%	32	370 X		5160	11.10	50 X		
SY033 48-49	N/A	shale	48	49	1.33	0.31	14	58	10.90%	1.60%	39	430 X		3990	13.20	60 X		
SY033 49-50	N/A	shale	49	50	1.17	0.31	13	113	9.36%	1.68%	56	430 X		4180	11.40	50 X		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY034		NORTHING: 5360654.948										RIG: 4WD truck, mounted rig						
AZIMUTH: 90		EASTING: 357563.392										DRILL TYPE: Air Core						
DIP: 65		R.L.: 295.522										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 40m		DRILL HOLE COMPLETION DATE: 13-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 05-Jul-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To delineate the north extention and depth of Allison's Lode zinc-lead-silver sulphides.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY034 00-01	N/A	talc, qtz, no visible sulphides	0	1	0.02	0.02	X	50	6900	4430	6	10	X	550	0.37	X	X	
SY034 01-02	N/A	talc, qtz, no visible sulphides	1	2	0.02	X	X	8	6000	1.62%	6	10	X	500	0.18	X	X	
SY034 02-03	N/A	pink clay, no visible sulphides	2	3	0.02	X	X	8	1.86%	18.20%	6	20	X	840	0.15		20	X
SY034 03-04	N/A	pink clay, no visible sulphides	3	4	0.02	X	X	8	1.19%	9.69%	6	X	X	350	0.18	X	X	
SY034 04-05	N/A	talc, pink clay, no visible sulphides	4	5	0.04	0.05	X	18	1.74%	18.40%	5	20	X	4750	0.12		30	X
SY034 05-06	N/A	talc, pink clay, no visible sulphides	5	6	0.03	X	X	X	1.84%	18.30%	X	30	X	4010	0.17		30	LNR
SY034 06-07	N/A	talc, pink clay, no visible sulphides	6	7	0.03	0.12	X	18	1.76%	18.20%	5	30	X	1.52%	0.10		40	X
SY034 07-08	N/A	talc, no visible sulphides	7	8	0.06	0.24	X	19	2.00%	17.10%	7	50	X	3.03%	0.33		30	X
SY034 08-09	N/A	talc, no visible sulphides	8	9	0.2	0.27	X	9	2.30%	16.30%	13	80	X	3.88%	0.48		30	X
SY034 09-10	N/A	talc, no visible sulphides	9	10	0.17	0.16	X	5	1.34%	16.70%	6	30	X	4.28%	0.19		20	X
SY034 10-11	N/A	talc, no visible sulphides	10	11	0.16	0.15	X	5	1.40%	17.50%	6	20	X	2.28%	0.17		20	X
SY034 11-12	N/A	talc, sandstone? no visible sulphides	11	12	0.33	0.13	X	X	2.40%	14.90%	X	20	X	6.35%	0.13		20	X
SY034 12-13	N/A	talc, no visible sulphides	12	13	0.41	0.1	X	X	2.04%	14.80%	X	20	X	6.44%	0.35		20	X
SY034 13-14	N/A	talc, no visible sulphides	13	14	0.3	0.08	X	X	1.72%	12.30%	X	20	X	9.84%	0.31	X	X	
SY034 14-15	N/A	talc, no visible sulphides	14	15	1.99	0.64	8	10	3.72%	11.90%	X	100	X	6.58%	2.41		30	X
SY034 15-16	N/A	talc ZnS 10-20%, Pb <2% - High grade	15	16	9.47	1.48	35	42	5.80%	12.40%	10	240	X	1.85%	>5.00		70	0.1
SY034 16-17	N/A	talc, <5-10% sulphides	16	17	1.24	0.38	5	13	3.47%	15.40%	8	110	X	2.83%	2.15		30	X
SY034 17-18	N/A	talc, ZnS 10-20%, Pb <2% - High grade	17	18	15.5	2.52	58	80	8.67%	10.10%	6	240	X	2.06%	>5.00		100	0.1
SY034 18-19	N/A	talc, ZnS 5-10%, FeS2	18	19	4.86	1.2	20	26	4.76%	10.80%	5	190	X	6.29%	>5.00		50	X
SY034 19-20	N/A	talc, silica cap	19	20	1.07	0.44	4	11	3.57%	14.50%	8	90	X	4.37%	1.88		30	X
SY034 20-21	N/A	cap rock, no visible sulphides	20	21	0.5	0.19	X	X	3.09%	12.70%	6	60	X	9.01%	0.90		20	X
SY034 21-22	N/A	cap rock, <5% ZnS, carbonates?	21	22	2.46	0.09	X	10	3.64%	11.70%	X	80	X	13.40%	1.99		20	X
SY034 22-23	N/A	cap rock, carbonates? No visible sulphides	22	23	0.6	0.09	X	5	2.76%	13.50%	X	60	X	14.10%	1.06	X	X	
SY034 23-24	N/A	cap rock, carbonates? No visible sulphides	23	24	0.36	0.18	X	7	3.86%	13.70%	8	120	X	10.40%	2.22		10	X
SY034 24-25	N/A	cap rock, carbonates?	24	25	14.1	1.24	32	49	16.00%	7.79%	15	1110	X	1.63%	>5.00		80	X
SY034 25-26	N/A	caprock, ZnS/PbS <5%	25	26	5.35	0.56	13	21	8.55%	11.20%	8	520	X	7.68%	>5.00		40	X
SY034 26-27	N/A	caprock, ZnS/PbS <5%	26	27	0.56	0.1	X	X	3.95%	16.00%	X	70	X	3.86%	1.25		10	X
SY034 27-28	N/A	cap rock, carbonates? blue-lightgray rock	27	28	0.38	0.06	X	X	2.06%	13.90%	6	20	X	10.20%	0.62		10	X
SY034 28-29	N/A	cap rock, carbonates? blue-lightgray rock	28	29	0.52	0.1	X	X	1.84%	11.50%	9	40	X	13.80%	0.98		10	X
SY034 29-30	N/A	cap rock, carbonates? blue-lightgray rock	29	30	0.67	0.08	X	X	2.79%	15.20%	X	40	X	6.07%	1.04		10	X
SY034 30-31	N/A	<2% ZnS within talc, carbonate?	30	31	0.4	0.1	X	X	5.01%	12.50%	6	50	X	5.08%	0.99		10	X
SY034 31-32	N/A	20% ZnS, 30%FeS2, blue-lightgray rock	31	32	2.57	1.43	23	183	19.30%	5.61%	9	130	X	3.47%	>5.00		40	X
SY034 32-33	N/A	shale	32	33	0.51	0.6	14	283	28.80%	1.92%	19	510	X	7500	>5.00		40	0.1
SY034 33-34	N/A	shale	33	34	0.91	0.31	8	105	10.90%	3.87%	49	350	X	2.86%	>5.00		40	0.1
SY034 34-35	N/A	shale	34	35	0.5	0.17	5	54	4.23%	1.67%	53	210	X	6520	3.64		20	X
SY034 35-36	N/A	shale	35	36	0.22	0.07	4	45	3.93%	1.02%	56	190	X	2480	3.71		20	X
SY034 36-37	N/A	shale	36	37	0.6	0.13	5	57	4.37%	1.20%	54	160	X	3830	4.55		30	X
SY034 37-38	N/A	shale	37	38	0.18	0.05	X	46	3.81%	1.04%	67	100	X	1950	3.78		30	X
SY034 38-39	N/A	shale	38	39	0.21	0.05	X	62	3.63%	1.18%	68	100	X	1890	3.27		20	X
SY034 39-40	N/A	shale	39	40	0.38	0.07	3	46	3.81%	1.30%	61	110	X	3180	3.98		20	X

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY035		NORTHING: 5360606.306										RIG: 4WD truck, mounted rig							
AZIMUTH: 305		EASTING: 357589.109										DRILL TYPE: Air Core							
DIP: 60		R.L: 287.303										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 20m		DRILL HOLE COMPLETION DATE: 13-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine							
PURPOSE: To define width and depth along Allison's Lode.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY035 00-01	N/A	talca, pyrite	0	1	6.15	2.43	61	246	21.80%	5.12%	5	2190 X	1870	28.5	70	0.1			
SY035 01-02	N/A	pyrite, 5% PbS, talc	1	2	5.52	6.62	120	151	26.30%	3.14%	8	2470 X	1480	33	100 X				
SY035 02-03	N/A	talca, 5% sulphides	2	3	3.63	1.45	24	165	13.30%	10.80%	10	1360 X	1270	16.1	40	0.1			
SY035 03-04	N/A	talca, 5% sulphides	3	4	0.9	0.56	8	42	7.46%	15.10%	7	680 X	2460	7.68	30 X				
SY035 04-05	N/A	talca, 5% sulphides	4	5	1.06	0.59	9	43	8.95%	13.20%	15	840 X	1440	9.34	30 X				
SY035 05-06	N/A	talca, 5% sulphides	5	6	2.38	1.38	21	125	14.30%	9.94%	19	1510 X	2200	15.8	50	0.2			
SY035 06-07	N/A	talca, 5% sulphides	6	7	1.57	1.35	20	38	7.42%	15.00%	22	730 X	610	8.13	50	0.2			
SY035 07-08	N/A	talca, 5% sulphides	7	8	1.74	0.54	8	27	6.16%	15.90%	25	630 X	640	6.53	40	0.2			
SY035 08-09	N/A	talca, 5% sulphides	8	9	1.67	0.87	8	44	7.80%	12.80%	37	730 X	2730	8.72	40	0.1			
SY035 09-10	N/A	talca, >5% sulphides	9	10	2.55	1.95	26	61	10.90%	12.30%	53	1100 X	2250	12.9	60 X				
SY035 10-11	N/A	talca, >5% sulphides	10	11	0.92	1.47	18	51	9.94%	14.40%	22	880 X	1600	10.3	30	0.1			
SY035 11-12	N/A	talca	11	12	0.57	0.19 X		41	5.20%	16.10%	8	150 X	1.07%	2.55	30 X				
SY035 12-13	N/A	talca	12	13	6.07	1.19	28	259	18.80%	5.93%	22	570 X	6500	21.2	40	0.3			
SY035 13-14	N/A	talca	13	14	1.13	0.35	10	143	15.20%	2.88%	18	600 X	6110	14.9	50	0.5			
SY035 14-15	N/A	talca, silica caprock	14	15	0.2	0.1	8	68	16.20%	1.43%	74	420 X	7060	16.6	60	0.3			
SY035 15-16	N/A	shale	15	16	0.97	0.38	12	55	4.74%	1.37%	63	100 X	5280	4.5	40	0.1			
SY035 16-17	N/A	shale	16	17	1.71	0.43	19	64	4.54%	1.17%	65	150 X	3610	5.01	40	0.1			
SY035 17-18	N/A	shale	17	18	0.76	0.27	13	60	4.20%	9030	62	110 X	2220	4.51	30	0.1			
SY035 18-19	N/A	shale	18	19	1.03	0.15	10	55	4.73%	1.12%	50	120 X	2900	5.02	30	0.1			
SY035 19-20	N/A	shale	19	20	0.25	0.09	8	48	4.57%	1.07%	61	210 X	1860	4.34	40 X				

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY036		NORTHING: 5360595.492										RIG: 4WD truck, mounted rig						
AZIMUTH: 21		EASTING: 357576.305										DRILL TYPE: Air Core						
DIP: 60		R.L.: 285.308										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 20m		DRILL HOLE COMPLETION DATE: 13-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To define width and depth along Allison's Lode.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY036 00-01	N/A	rubble	0	1	0.41	0.41	5	53	3.89%	15.50%	7	240 X		1090	2.84	30 X		
SY036 01-02	N/A	talc, sulphides	1	2	0.62	0.64	7	66	3.96%	13.70%	10	270 X		880	3.18	40 X		
SY036 02-03	N/A	talc, sulphides	2	3	0.56	0.65	7	56	3.64%	13.60%	13	240 X		340	2.91	50 X		
SY036 03-04	N/A	talc, no visible sulphides	3	4	0.1	0.31 X		48	1.84%	18.30% X		70 X		80	0.48	40 X		
SY036 04-05	N/A	talc, no visible sulphides	4	5	0.15	0.42 X		70	2.15%	18.70% X		120 X		70	0.81	40 X		
SY036 05-06	N/A	talc, no visible sulphides	5	6	0.18	0.58 X		166	2.66%	18.20%	7	130 X		350	1.32	40 X		
SY036 06-07	N/A	talc, no visible sulphides	6	7	0.26	0.56 X		164	3.19%	17.00%	6	140 X		7930	1.35	40 X		
SY036 07-08	N/A	hard talc, 5-10% ZnS,	7	8	1.38	0.32 X		68	6.18%	13.50% X		100 X		3.45%	1.97	30 X		
SY036 08-09	N/A	talc, 20-30-% ZnS	8	9	6.36	3.52	42	101	9.30%	9.98% X		140 X		3.80%	7.49	60 X		
SY036 09-10	N/A	ZnS/PbS- high-grade lode	9	10	40.5	7.05	123	253	13.20%	1.16% X		350 X		4750	29	100		0.3
SY036 10-11	N/A	ZnS/PbS- high-grade lode	10	11	37.5	10.2	134	223	11.20%	1.52%	7	320 X		6240	28.5	90		0.2
SY036 11-12	N/A	85% hard talc, 10% ZnS/PbS	11	12	7.42	1.79	26	173	5.35%	11.60% X		420 X		7.59%	8.17	40 X		
SY036 12-13	N/A	talc, <5% sulphides	12	13	2.9	0.77	10	136	3.79%	13.30%	9	720 X		9.68%	3.78	20 X		
SY036 13-14	N/A	silica cap rock, qtz, green fragments, <2% ZnS	13	14	1.29	0.37	3	93	3.24%	13.00% X		120 X		7.37%	1.92	10 X		
SY036 14-15	N/A	cap rock, 90% qtz with visible ZnS/PbS <5%, 3% FeS	14	15	0.93	0.26	3	21	3.17%	2.89%	11	60 X		1.57%	1.56 X			0.2
SY036 15-16	N/A	dark cap rock, no visible sulphides, hard, gray, qtz	15	16	0.59	0.26	4	61	4.72%	2.33%	56	100 X		1.56%	3.16	20		0.2
SY036 16-17	N/A	shale	16	17	0.62	0.17	4	55	5.22%	2.05%	67	140 X		1.20%	4.25	20		0.1
SY036 17-18	N/A	shale	17	18	0.31	0.1	4	51	5.15%	1.96%	57	340 X		7880	3.76	20 X		
SY036 18-19	N/A	shale	18	19	0.57	0.14	7	49	4.51%	1.79%	57	200 X		6700	4.25	20 X		
SY036 19-20	N/A	shale	19	20	0.51	0.18	9	58	4.93%	1.19%	56	130 X		4120	5.02	20 X		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY037		NORTHING: 5360587.947										RIG: 4WD truck, mounted rig						
AZIMUTH: 274		EASTING: 357594.526										DRILL TYPE: Air Core						
DIP: 60		R.L.: 279.199										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 15m		DRILL HOLE COMPLETION DATE: 14-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To define width and depth along Allison's Lode (base of current pit).																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY037 00-01	N/A	taic,	0	1	0.3	0.12	X	27	4.97%	7.30%	13	100	X	8580	1.87	20	X	
SY037 01-02	N/A	taic, sulphides	1	2	1.7	0.34	13	128	18.30%	1.53%	25	760	X	1.80%	20	80	0.2	
SY037 02-03	N/A	taic, sulphides	2	3	2.03	0.17	9	186	32.70%	1.63%	14	2580	X	5040	38.8	20	0.2	
SY037 03-04	N/A	taic, sulphides	3	4	0.66	0.27	6	103	26.20%	3.69%	16	2280	X	1.07%	28.9	X	0.1	
SY037 04-05	N/A	light gray cap rock, no visible ZnS	4	5	0.45	0.11	3	67	11.40%	5.20%	37	620	X	2.21%	10.2	10	0.3	
SY037 05-06	N/A	white rock containing FeS2 & other minor sulphides	5	6	0.62	0.07	X	31	11.70%	10.60%	15	660	X	5.69%	9.5	20	0.2	
SY037 06-07	N/A	cap rock,	6	7	0.19	0.06	5	41	23.10%	4.31%	23	1060	X	1.48%	25	40	0.5	
SY037 07-08	N/A	cap rock, FeS	7	8	0.42	0.09	4	68	14.80%	3.89%	36	830	X	2.81%	13.9	20	0.4	
SY037 08-09	N/A	cap rock, sulphides >20%	8	9	0.64	0.13	5	197	17.20%	5.45%	52	1020	X	4.23%	16.6	40	0.2	
SY037 09-10	N/A	cap rock, FeS	9	10	0.49	0.06	X	68	8.45%	11.00%	10	530	X	12.40%	7.96	20	0.1	
SY037 10-11	N/A	ligh gray rock - caprock,carbonate? Sulphides 20%, ZnS 5%	10	11	0.56	0.11	X	58	8.55%	10.50%	6	590	X	13.30%	9.49	10	0.1	
SY037 11-12	N/A	light gray rock 95%	11	12	0.4	0.15	X	46	7.37%	11.10%	6	510	X	15.90%	7.96	10	0.1	
SY037 12-13	N/A	shale	12	13	0.38	0.06	X	86	7.32%	2.28%	61	340	X	2.06%	8.11	30	0.1	
SY037 13-14	N/A	shale	13	14	0.22	0.04	X	86	6.32%	1.40%	76	260	X	7250	6.75	40	0.1	
SY037 14-15	N/A	shale	14	15	0.2	0.04	X	107	6.30%	1.07%	85	230	X	3310	6.43	40	X	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID:	SY039	NORTHING: 5360549.722										RIG: 4WD truck, mounted rig						
AZIMUTH:	264	EASTING: 357601.669										DRILL TYPE: Air Core						
DIP:	55	R.L.: 277.223										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH:	10m	DRILL HOLE COMPLETION DATE: 14-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY:	SGS Welshpool Minerals	ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Cornstock Mine						
PURPOSE: To define width and depth along Allison's Lode (base of current pit).																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY039 00-01	100%	high-grade lode, ZnS, PbS	0	1	18.7	1.98	48	270	12.30%	7.17%	11	1090	X	500	21.8	250	0.4	
SY039 01-02	100%	high-grade lode, ZnS, PbS	1	2	12.5	0.63	17	319	13.00%	4.65%	7	1480	X	2430	19.9	110	0.4	
SY039 02-03	100%	high-grade lode, ZnS, PbS, cap rock	2	3	5.12	0.21	7	184	12.90%	8290	5	1710	X	740	17.9	60	0.8	
SY039 03-04	100%	cap rock, <5% sulphides	3	4	1.17	0.12	5	87	6.59%	1.55%	47	540	X	1140	7.38	50	0.3	
SY039 04-05	100%	taic, shale, sulphides	4	5	2.92	0.22	8	169	11.40%	1.32%	46	1160	X	1400	14	70	0.6	
SY039 05-06	100%	shale	5	6	0.48	0.1	5	88	5.39%	9260	80	210	X	1030	5.82	70	0.1	
SY039 06-07	100%	shale	6	7	0.31	0.52	17	96	4.89%	8700	80	110	X	810	5.33	80	0.1	
SY039 07-08	100%	shale	7	8	0.26	0.46	19	148	5.40%	8550	78	160	X	800	5.87	80	X	
SY039 08-09	100%	shale	8	9	0.2	0.25	12	91	5.87%	8120	77	160	X	910	6.25	90	0.1	
SY039 09-10	100%	shale	9	10	0.23	0.35	15	109	5.30%	8540	76	130	X	940	5.67	80	0.1	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY040		NORTHING: 5360556.184										RIG: 4WD truck, mounted rig						
AZIMUTH: 282		EASTING: 357601.757										DRILL TYPE: Air Core						
DIP: 55		R.L: 277.745										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 10m		DRILL HOLE COMPLETION DATE: 14-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To define width and depth along Allison's Lode (base of current pit).																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY040 00-01	100%	high-grade lode, ZnS, PbS	0	1	35.6	8.76	210	1020	6.61%	2380	X	170	X	910	23.4	340	0.8	
SY040 01-02	100%	high-grade lode, ZnS, PbS	1	2	35.8	8.9	200	963	5.44%	1320	X	60	X	1590	21.7	270	0.7	
SY040 02-03	100%	high-grade lode, ZnS, PbS	2	3	15.1	2.35	77	501	11.80%	2940	X	970	X	990	19.3	190	0.6	
SY040 03-04	100%	cap rock, FeS	3	4	2.98	0.73	22	121	9.72%	7390	31	550	X	1330	11.5	100	0.3	
SY040 04-05	100%	cap rock, FeS	4	5	0.63	0.29	9	88	7.65%	1.47%	56	420	X	1230	8.13	80	0.3	
SY040 05-06	100%	shale	5	6	0.48	0.16	6	98	5.88%	1.39%	75	190	X	1270	6.21	70	0.2	
SY040 06-07	100%	shale	6	7	0.17	0.06	3	91	5.61%	1.09%	80	160	X	1140	5.99	70	0.1	
SY040 07-08	100%	shale	7	8	0.11	0.27	8	80	5.32%	8220	92	140	X	990	6.29	90	0.1	
SY040 08-09	100%	shale	8	9	0.4	0.11	7	95	5.28%	8500	74	150	X	1240	6.32	80	0.1	
SY040 09-10	100%	shale	9	10	0.31	0.16	7	127	4.47%	9070	80	100	X	1120	5.03	70	0.1	

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY041		NORTHING: 5360621.469										RIG: 4WD truck, mounted rig							
AZIMUTH: 281		EASTING: 357588.323										DRILL TYPE: Air Core							
DIP: 65		R.L: 293.825										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 24m		DRILL HOLE COMPLETION DATE: 14-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine							
PURPOSE: To delineate the north extension and depth of Allison's Lode zinc-lead-silver sulphides.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY041 00-01	N/A	Pink clay, talc, no visible sulphides	0	1	0.14	0.04	X	12	1.59%	15.60%	X	40	X	240	0.413	20	X		
SY041 01-02	N/A	Pink clay, talc, no visible sulphides	1	2	0.05	0.01	9	X	1.66%	15.00%	X	20	X	120	0.168	20	X		
SY041 02-03	N/A	Pink clay, talc, no visible sulphides	2	3	0.06	0.03	6	11	1.75%	18.00%	X	20	X	90	0.163	20	X		
SY041 03-04	N/A	Pink clay, talc, no visible sulphides	3	4	0.05	0.12	12	31	2.49%	17.70%	X	70	X	100	0.27	60	X		
SY041 04-05	N/A	talc, specs of ZnS	4	5	2.34	1.09	25	175	16.50%	9.89%	6	500	X	230	18.6	130	X		
SY041 05-06	N/A	talc, visible sulphides	5	6	14.8	1.91	53	175	12.60%	7.51%	10	310	X	560	19.5	160	0.3		
SY041 06-07	N/A	talc, visible sulphides	6	7	11.6	2.45	44	206	15.40%	7.65%	21	490	X	1940	22.6	110	0.3		
SY041 07-08	N/A	talc, visible sulphides	7	8	8.77	2.36	44	172	12.10%	8.63%	8	300	X	3790	15.1	110	0.2		
SY041 08-09	N/A	high-grade lode, ZnS, PbS in talc	8	9	12.4	3.77	58	501	24.80%	1.82%	23	300	X	1590	35	70	0.2		
SY041 09-10	N/A	high-grade lode, ZnS, PbS in talc	9	10	15	4.59	59	505	18.90%	3.92%	16	200	X	1920	26.3	80	0.2		
SY041 10-11	N/A	high-grade lode, ZnS, PbS in talc	10	11	28.5	4.25	74	216	10.20%	4.82%	5	110	X	3710	20.9	90	0.4		
SY041 11-12	N/A	high-grade lode, ZnS, PbS in talc	11	12	7.69	1.3	21	81	6.11%	12.00%	X	60	X	3880	7.22	40	X		
SY041 12-13	N/A	high-grade lode, ZnS, PbS in talc	12	13	9.27	1.35	27	108	9.80%	8.35%	9	130	X	3110	12.5	60	0.1		
SY041 13-14	N/A	talc with <5% ZnS	13	14	3.52	0.86	14	95	7.91%	13.50%	7	160	X	2480	7.42	50	0.1		
SY041 14-15	N/A	talc, cap rock, 5-10% sulphides	14	15	3.86	0.46	8	114	8.30%	13.40%	8	130	X	6440	6.53	40	X		
SY041 15-16	N/A	high-grade lode, ZnS, PbS in talc	15	16	8.78	0.73	17	442	27.20%	2.64%	10	90	X	4540	24.6	40	0.1		
SY041 16-17	N/A	high-grade lode, ZnS, PbS in talc	16	17	21.5	0.6	22	363	25.50%	7600	20	240	X	1620	32.1	160	0.3		
SY041 17-18	N/A	high-grade lode, ZnS, PbS in talc	17	18	21.4	1.31	32	481	22.80%	9760	13	120	X	1790	30.3	130	0.2		
SY041 18-19	N/A	talc 90%, ZnS 10%	18	19	10.8	1.09	20	438	14.70%	6.62%	11	150	X	4970	16.7	70	0.1		
SY041 19-20	N/A	talc, ZnS 15%	19	20	6.02	0.45	11	203	10.50%	9.09%	12	140	X	1.08%	10.2	50	0.1		
SY041 20-21	N/A	caprock, FeS2	20	21	6.83	0.7	16	210	11.30%	4.01%	38	200	X	6550	13.2	80	0.2		
SY041 21-22	N/A	shale	21	22	1.35	0.18	5	80	7.25%	5.11%	59	110	X	1.35%	5.15	40	0.1		
SY041 22-23	N/A	shale	22	23	0.58	0.1	X	133	5.62%	2.93%	63	90	X	1.37%	4.05	30	0.1		
SY041 23-24	N/A	shale	23	24	1.03	0.21	5	91	5.87%	2.10%	61	120	X	7650	5.15	40	0.2		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY042		NORTHING: 5360625.724										RIG: 4WD truck, mounted rig							
AZIMUTH: 315		EASTING: 357586.007										DRILL TYPE: Air Core							
DIP: 65		R.L: 293.404										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 25m		DRILL HOLE COMPLETION DATE: 15-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 30-May-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine							
PURPOSE: To delineate the north extention and depth of Allison's Lode zinc-lead-silver sulphides.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
SY042 00-01	N/A	taic	0	1	0.16	0.08	5	25	1.11%	3.92%	X	60	X	290	0.618	20	X		
SY042 01-02	N/A	taic, qtz	1	2	0.26	0.09	27	15	7900	9010	X	20	X	230	0.623	20	X		
SY042 02-03	N/A	taic	2	3	1.47	2.01	44	79	4.76%	9.96%	13	120	X	1340	4.22	190	0.2		
SY042 03-04	N/A	taic, <5% ZnS	3	4	1.08	1.62	25	89	7.68%	8.77%	11	110	X	6840	4.39	100	X		
SY042 04-05	N/A	cap rock, <5% sulphides	4	5	0.87	0.32	6	49	4.30%	15.60%	X	110	X	6130	2.74	30	X		
SY042 05-06	N/A	taic with visible ZnS & PbS 5-10%	5	6	3.56	3.35	42	360	24.20%	5.72%	13	390	X	590	25.8	80	0.1		
SY042 06-07	N/A	taic with visible ZnS & FeS2 5-10%	6	7	0.55	0.45	7	144	9.19%	13.10%	8	150	X	1790	6.24	50	X		
SY042 07-08	N/A	taic	7	8	0.87	0.26	6	239	12.10%	11.50%	14	450	X	2550	12.6	50	X		
SY042 08-09	N/A	taic, 5-10% ZnS/PbS - lode	8	9	2.23	0.9	21	423	21.40%	3.15%	45	290	X	1040	24.5	50	0.2		
SY042 09-10	N/A	taic, 5-10% ZnS/PbS - lode	9	10	2.49	3.67	46	693	32.10%	1.83%	49	400	X	950	36.7	50	0.1		
SY042 10-11	N/A	taic, visible sulphides	10	11	0.52	0.87	11	117	8.52%	9.18%	5	260	X	2860	3.6	60	X		
SY042 11-12	N/A	taic, visible sulphides	11	12	0.14	0.15	X	21	7.34%	9.89%	8	330	X	3980	1.13	40	X		
SY042 12-13	N/A	taic, 10-20% ZnS/PbS - lode	12	13	3.15	0.88	10	73	7.10%	10.90%	6	100	X	3.37%	5.46	40	X		
SY042 13-14	N/A	taic, 10-20% ZnS/PbS - high-grade lode	13	14	18.7	2.34	38	564	15.00%	3.69%	27	150	X	2540	21.8	110	0.2		
SY042 14-15	N/A	taic, visible ZnS, PbS	14	15	1.34	1.51	14	52	7.45%	11.90%	9	210	X	5840	2.62	70	X		
SY042 15-16	N/A	taic with visible ZnS & PbS 5-10%	15	16	6.57	0.86	11	218	4.93%	6.72%	31	190	X	1400	6.71	90	X		
SY042 16-17	N/A	taic with visible ZnS & PbS 5-10%	16	17	9.3	3.8	34	274	16.20%	3.27%	12	160	X	2210	17.7	60	X		
SY042 17-18	N/A	taic, 10-20% ZnS - lode	17	18	8.54	0.74	12	431	22.80%	2460	10	80	X	2470	21.1	30	0.1		
SY042 18-19	N/A	cavity, small sample, ZnS 30%	18	19	5.97	0.43	9	292	12.60%	3510	11	60	X	2000	13	40	X		
SY042 19-20	N/A	cavity, small sample, visible ZnS	19	20	LNR	LNR	LNR	-	-	-	-	-	-	-	LNR	-	LNR		
SY042 20-21	N/A	cavity, small sample, visible ZnS	20	21	4.21	0.75	10	191	13.00%	4.40%	36	150	X	1.97%	11.7	40	0.1		
SY042 21-22	N/A	cap rock, <5% sulphides	21	22	12.3	1.43	21	477	26.20%	3870	10	90	X	2150	26.3	40	0.1		
SY042 22-23	N/A	shale	22	23	0.99	0.64	6	98	6.86%	7.29%	35	120	X	1.21%	5.02	40	X		
SY042 23-24	N/A	shale	23	24	0.64	0.61	6	99	6.76%	2.54%	70	90	X	8520	5.58	60	X		
SY042 24-25	N/A	shale	24	25	0.51	0.17	4	78	5.54%	1.58%	65	90	X	7550	4.81	40	0.1		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY043		NORTHING: 5360735.762										RIG: 4WD truck, mounted rig						
AZIMUTH: 199		EASTING: 357575.350										DRILL TYPE: Air Core						
DIP: 60		R.L.: 302.804										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 25m		DRILL HOLE COMPLETION DATE: 15-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 19-Jul-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To test for the location of Balstrup Fault along Trial Harbour Rd.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY043 00-01	N/A	soil	0	1	0.37	0.2	5	84	3.86%	2.02%	41	100	X	4990	2.65	40		
SY043 01-02	N/A	soil	1	2	0.31	0.2	4	55	3.23%	1.25%	43	90	X	4300	2.52	20		
SY043 02-03	N/A	qtz rich fragments, brown soil	2	3	0.06	0.05	X	56	2.81%	1.17%	93	20	X	780	0.53	X		
SY043 03-04	N/A	qtz rich fragments, brown soil	3	4	X	X	X	75	5800	4400	9	X	X	210	0.16	10		
SY043 04-05	N/A	silty gray clay with minor qtz	4	5	0.05	0.05	X	80	1.81%	4900	39	30	X	170	1.63	30		
SY043 05-06	N/A	light-gray sandstone	5	6	0.03	0.04	X	36	6800	2680	18	X	X	160	0.37	X		
SY043 06-07	N/A	light-gray sandstone	6	7	0.04	0.05	X	51	1.34%	4760	34	50	X	1190	1.03	20		
SY043 07-08	N/A	light-gray sandstone	7	8	X	0.05	X	114	1.60%	4240	16	40	X	220	1.47	10		
SY043 08-09	N/A	light-gray sandstone, minor FeS2	8	9	0.04	0.09	X	81	1.21%	4850	24	30	X	360	0.89	10		
SY043 09-10	N/A	light-gray sandstone, minor FeS2 & qtz	9	10	X	0.04	X	99	1.47%	3350	17	50	X	130	1.48	10		
SY043 10-11	N/A	light-gray sandstone, qtz rich, no visible FeS2	10	11	0.02	1.42	X	61	1.10%	4200	12	20	X	250	0.92	X		
SY043 11-12	N/A	light-gray sandstone, 30% qtz <2% FeS2	11	12	0.02	0.05	X	49	1.53%	7030	24	40	X	180	1.36	X		
SY043 12-13	N/A	light-gray sandstone, <5% FeS2	12	13	0.06	0.02	X	25	5.41%	3.29%	47	60	X	250	>5.00	10		
SY043 13-14	N/A	shale, qtz		14	0.04	0.03	X	33	3.42%	1.60%	42	50	X	300	3.08	X		
SY043 14-15	N/A	shale, qtz	14	15	X	0.03	X	18	2.09%	9260	25	40	X	180	1.87	10		
SY043 15-16	N/A	shale, qtz	15	16	0.02	0.02	X	23	2.23%	1.06%	28	50	X	550	1.95	10		
SY043 16-17	N/A	shale? Qtz, FeS2	16	17	0.02	0.31	X	33	3.63%	1.31%	50	60	X	620	3.57	10		
SY043 17-18	N/A	sandstone, minor FeS2, shale?	17	18	0.03	0.54	3	13	1.69%	1.06%	20	40	X	650	1.39	X		
SY043 18-19	N/A	shale with FeS2	18	19	0.02	0.22	X	22	2.32%	1.21%	23	60	X	670	1.77	20		
SY043 19-20	N/A	hard shale with qtz	19	20	0.02	0.22	X	19	1.90%	1.08%	26	50	X	530	1.39	X		
SY043 20-21	N/A	hard shale with qtz	20	21	0.02	0.36	X	14	2.12%	1.26%	18	30	X	580	1.14	X		
SY043 21-22	N/A	hard shale with qtz	21	22	0.03	0.14	X	16	1.74%	1.33%	17	30	X	1100	0.90	X		
SY043 22-23	N/A	hard shale with qtz	22	23	0.12	0.1	X	16	2.02%	2.04%	24	50	X	3250	1.17	X		
SY043 23-24	N/A	hard shale with qtz	23	24	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR		
SY043 24-25	N/A	hard shale with qtz	24	25	0.1	0.09	X	22	2.31%	3.00%	29	50	X	2850	1.31	10		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: SY044		NORTHING: 5360747.260										RIG: 4WD truck, mounted rig						
AZIMUTH: 228		EASTING: 357586.961										DRILL TYPE: Air Core						
DIP: 60		R.L: 303.149										DRILLER: Tasmanian Drilling Services Pty Ltd						
TOTAL DEPTH: 27m		DRILL HOLE COMPLETION DATE: 15-Apr-05										SAMPLED BY: Paul Heath						
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 27-Jul-05										PROSPECT LOCATION: Allison's Lode, Comstock Mine						
PURPOSE: To test for the location of Balstrup Fault along Trial Harbour Rd.																		
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM
SY044 00-01	N/A	orange clay	0	1	0.09	0.01	4	123	8.98%	2.26%	104	20 X		570	0.18 X			
SY044 01-02	N/A	chlorite clay, Crimson Creek?, green- to gray clay	1	2	0.28 X		4	187	8.01%	2.49%	175	20 X		1630	0.31 X			
SY044 02-03	N/A	chlorite clay, Crimson Creek?, green- to gray clay	2	3	0.27 X		X	149	9.79%	3.88%	180	20 X		2260	0.22 X			
SY044 03-04	N/A	chlorite clay, Crimson Creek?, green- to gray clay	3	4	0.15 X		X	163	10.40%	4.43%	147	10 X		2420	0.17 X			
SY044 04-05	N/A	chlorite clay, Crimson Creek?, green- to gray clay	4	5	0.18 X			3	158	11.50%	5.01%	134	20 X	2040	0.25 X			
SY044 05-06	N/A	chlorite clay, Crimson Creek?, green- to gray clay	5	6	0.22 X			3	155	10.40%	3.54%	157	30 X	2400	0.49 X			
SY044 06-07	N/A	chlorite clay, Crimson Creek?, green- to gray clay	6	7	0.1 X			3	162	11.40%	4.17%	100 X	X	1920	0.13 X			
SY044 07-08	N/A	chlorite clay, Crimson Creek?, green- to gray clay	7	8	0.11 X		X		181	11.00%	3.69%	101	10 X	2200	0.18 X			
SY044 08-09	N/A	chlorite clay, Crimson Creek?, green- to gray clay	8	9	0.11 X		X		163	11.40%	4.23%	98 X	X	1620	0.12 X			
SY044 09-10	N/A	chlorite clay, Crimson Creek?, green- to gray clay	9	10	0.18 X		X		127	9.45%	3.46%	73	10 X	1150	0.38 X			
SY044 10-11	N/A	chlorite clay, Crimson Creek?, green- to gray clay	10	11	0.7	0.04 X			151	11.40%	4.26%	132	70 X	1550	2.84 X			
SY044 11-12	N/A	chlorite clay, Crimson Creek?, green- to gray clay	11	12	0.79 X		X		150	10.30%	4.39%	130	70 X	1720	1.88 X			
SY044 12-13	N/A	chlorite clay with orange fragments, minor FeS in shale frag.	12	13	0.56	0.02	3		143	9.41%	3.47%	158	60 X	1910	3.18	10		
SY044 13-14	N/A	chlorite clay	13	14	0.67	0.01 X			141	10.60%	3.99%	196	60 X	1880	3.37	10		
SY044 14-15	N/A	chlorite clay	14	15	0.56 X		X		135	10.60%	4.31%	221	50 X	1490	1.87 X			
SY044 15-16	N/A	chlorite clay	15	16	0.11 X		X		125	9.23%	5.10%	87	10 X	1990	0.25 X			
SY044 16-17	N/A	chlorite clay	16	17	0.14 X		X		127	10.40%	5.34%	106	40 X	1870	1.32 X			
SY044 17-18	N/A	chlorite clay	17	18	0.22 X		X		161	11.60%	5.44%	166	80 X	2020	2.64	20		
SY044 18-19	N/A	chlorite clay	18	19	0.28 X		X		121	9.36%	5.22%	145	40 X	1690	1.04 X			
SY044 19-20	N/A	chert fragments in chlorite clay	19	20	0.12 X		X		87	8.81%	5.17%	104	40 X	1430	1.36 X			
SY044 20-21	N/A	chlorite clay	20	21	0.31 X		X		131	9.34%	5.01%	142	50 X	1520	1.18	10		
SY044 21-22	N/A	Not logged	21	22	0.17	0.01 X			84	7.43%	4.52%	252	110 X	1260	1.91	20		
SY044 22-23	N/A	Not logged	22	23	0.45	0.03 X			74	5.63%	2.33%	96	70 X	1550	2.70	20		
SY044 23-24	N/A	Not logged	23	24	0.85	0.11	4		106	5.11%	2.00%	66	50 X	1280	2.63	20		
SY044 24-25	N/A	Not logged	24	25	0.2	0.13 X			84	2.70%	1.50%	31	40 X	1550	1.19 X			
SY044 25-26	N/A	Not logged	25	26	0.39	0.21	4		96	3.00%	1.23%	28	30 X	1580	2.09	10		
SY044 26-27	N/A	Not logged	26	27	0.42	0.09 X			113	7.07%	2.75%	101	80 X	1710	3.07 X			

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: ZZE1		NORTHING: 5357413.111										RIG: 4WD truck, mounted rig							
AZIMUTH: 254		EASTING: 362274.443										DRILL TYPE: Air Core							
DIP: 60		R.L: 191.902										DRILLER: Tasmanian Drilling Services Pty Ltd							
TOTAL DEPTH: 44m		DRILL HOLE COMPLETION DATE: 15-Apr-05										SAMPLED BY: Paul Heath							
ASSAYED BY: SGS Welshpool Minerals		ASSAY RESULTS REPORTED: 08-Jun-05										PROSPECT LOCATION: Oceana Deposit							
PURPOSE: To test for zinc, lead and silver minerals from surface to 50m.																			
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM	
ZZE1 0-1	N/A	overburden	0	1	0.9	2.94	77	139	1.00%	4230	120	260	X	280	1.77	100	3.3		
ZZE1 1-2	N/A	overburden	1	2	1.25	2.86	15	54	9300	5340	133	30	X	190	2.34	230	2.6		
ZZE1 2-3	N/A	overburden	2	3	4.09	3.69	6	44	3.84%	5540	719	90	X	320	7.17	150	1.6		
ZZE1 3-4	N/A	brown soil	3	4	3.51	3.31	6	83	2.48%	5470	428	60	X	220	5.41	150	1.3		
ZZE1 4-5	N/A	stope material?, sulphides	4	5	2.54	3.47	3	58	3.09%	7610	458	50	X	560	5.02	170	0.9		
ZZE1 5-6	N/A	brown pug	5	6	2.38	3.16	3	41	2.57%	6300	373	50	X	290	4.93	140	0.9		
ZZE1 6-7	N/A	brown pug	6	7	0.92	1.77	X	65	1.67%	6870	218	30	X	480	2.63	100	0.7		
ZZE1 7-8	N/A	brown pug	7	8	0.71	1.38	3	64	1.45%	6640	212	30	X	440	2.42	100	0.6		
ZZE1 8-9	N/A	brown pug	8	9	1.56	1.61	X	89	5.76%	2.30%	381	70	X	1070	3.66	70	0.8		
ZZE1 9-10	N/A	brown pug	9	10	0.83	1.53	X	53	2.43%	9510	327	40	X	510	2.77	90	0.6		
ZZE1 10-11	N/A	brown pug	10	11	0.86	1.35	X	47	2.31%	9410	305	40	X	840	3.00	80	0.6		
ZZE1 11-12	N/A	brown pug	11	12	0.6	0.86	X	32	2.41%	7620	249	40	X	590	3.04	60	0.5		
ZZE1 12-13	N/A	Not logged - water in sample	12	13	0.39	0.46	X	30	3.29%	9910	195	50	X	1010	3.56	40	0.4		
ZZE1 13-14	N/A	Not logged - water in sample	13	14	0.28	0.31	X	23	2.99%	7890	155	30	X	590	3.35	30	0.4		
ZZE1 14-15	N/A	Not logged - water in sample	14	15	0.24	0.44	4	33	2.51%	8070	120	20	X	1290	2.73	40	0.5		
ZZE1 15-16	N/A	Not logged - water in sample	15	16	0.4	0.56	X	39	2.88%	1.18%	150	40	X	1780	2.33	40	0.5		
ZZE1 16-17	N/A	Not logged - water in sample	16	17	0.03	0.03	X	8	3.33%	2.10%	29	X	X	15.30%	1.10	X	0.2		
ZZE1 17-18	N/A	Not logged - water in sample	17	18	0.03	0.02	X	6	2.59%	2.03%	21	X	X	19.60%	0.81	X	0.2		
ZZE1 18-19	N/A	Not logged - water in sample	18	19	0.22	0.32	X	15	2.50%	2.50%	55	20	X	14.40%	1.45	30	0.2		
ZZE1 19-20	N/A	Not logged - water in sample	19	20	0.02	0.02	X	7	2.31%	2.01%	17	X	X	21.50%	0.83	X	0.2		
ZZE1 20-21	N/A	Not logged - water in sample	20	21	0.04	0.03	X	6	2.70%	3.26%	21	X	X	17.40%	1.14	10	0.2		
ZZE1 21-22	N/A	Not logged - water in sample	21	22	0.03	0.02	X	5	3.21%	2.52%	17	X	X	19.90%	0.86	X	0.2		
ZZE1 22-23	N/A	Not logged - water in sample	22	23	0.02	0.01	X	X	2.61%	2.33%	15	X	X	21.90%	0.81	X	0.2		
ZZE1 23-24	N/A	Not logged - water in sample	23	24	0.02	X	X	5	3.02%	2.44%	19	X	X	20.00%	1.28	X	0.2		
ZZE1 24-25	N/A	Not logged - water in sample	24	25	0.03	0.02	X	6	2.50%	1.73%	23	X	X	20.60%	1.48	X	0.2		
ZZE1 25-26	N/A	Not logged - water in sample	25	26	0.03	0.01	X	7	3.04%	2.32%	21	X	X	20.50%	1.32	X	0.2		
ZZE1 26-27	N/A	Not logged - water in sample	26	27	0.05	0.02	X	13	5.55%	2.37%	29	X	X	11.90%	1.79	10	0.2		
ZZE1 27-28	N/A	Not logged - water in sample	27	28	0.07	0.12	X	14	5.46%	3.96%	41	20	X	9.16%	1.89	20	0.3		
ZZE1 28-29	N/A	Not logged - water in sample	28	29	0.03	0.03	X	13	4.64%	4.55%	28	10	X	8.78%	1.96	20	0.2		
ZZE1 29-30	N/A	Not logged - water in sample	29	30	0.08	0.05	X	23	4.13%	4.03%	30	20	X	8.29%	1.71	20	0.2		
ZZE1 30-31	N/A	Not logged - water in sample	30	31	0.06	0.05	X	21	5.70%	3.22%	32	20	X	5.93%	2.15	20	0.2		
ZZE1 31-32	N/A	Not logged - water in sample	31	32	0.19	0.12	X	25	6.85%	2.44%	56	60	X	3.98%	3.93	60	0.4		
ZZE1 32-33	N/A	Not logged - water in sample	32	33	0.06	0.05	X	15	4.14%	4.25%	33	20	X	7.95%	1.87	30	0.2		
ZZE1 33-34	N/A	Not logged - water in sample	33	34	0.07	0.06	X	14	4.22%	5.22%	33	10	X	10.10%	2.05	20	0.2		
ZZE1 34-35	N/A	Not logged - water in sample	34	35	0.21	0.17	X	14	4.78%	4.80%	34	20	X	9.67%	2.45	20	0.3		
ZZE1 35-36	N/A	Not logged - water in sample	35	36	0.02	0.04	X	7	4.59%	4.17%	18	X	X	15.20%	1.36	20	0.2		
ZZE1 36-37	N/A	Not logged - water in sample	36	37	0.02	0.02	X	8	3.80%	4.56%	21	X	X	13.60%	1.29	20	0.2		
ZZE1 37-38	N/A	Not logged - water in sample	37	38	0.02	0.03	X	7	3.48%	2.67%	19	10	X	18.20%	1.19	20	0.2		
ZZE1 38-39	N/A	Not logged - water in sample	38	39	0.01	0.03	X	X	3.64%	1.33%	13	X	X	24.10%	0.83	X	0.1		
ZZE1 39-40	N/A	Not logged - water in sample	39	40	0.05	0.04	X	10	5.41%	1.48%	28	10	X	18.70%	1.57	20	0.2		
ZZE1 40-41	N/A	Not logged - water in sample	40	41	0.04	0.04	X	9	3.38%	2.60%	31	10	X	15.80%	1.63	20	0.2		
ZZE1 41-42	N/A	Not logged - water in sample	41	42	0.03	0.03	X	8	4.53%	2.72%	19	X	X	18.50%	1.27	10	0.1		
ZZE1 42-43	N/A	Not logged - water in sample	42	43	0.06	0.06	X	10	3.13%	2.37%	23	10	X	20.00%	1.33	20	0.2		
ZZE1 43-44	N/A	Not logged - water in sample	43	44	0.08	0.04	X	8	2.32%	2.70%	22	X	X	20.00%	1.14	10	0.2		

ZZ EXPLORATION PTY LTD

SAMPLING SUMMARY SHEET

Hole ID: ZZE2			NORTHING: 5357521.485										RIG: 4WD truck, mounted rig								
AZIMUTH: 240			EASTING: 362243.872										DRILL TYPE: Air Core								
DIP: 60			R.L: 192.839										DRILLER: Tasmanian Drilling Services Pty Ltd								
TOTAL DEPTH: 40m			DRILL HOLE COMPLETION DATE: 16-Apr-05										SAMPLED BY: Paul Heath								
ASSAYED BY: SGS Welshpool Minerals			ASSAY RESULTS REPORTED: 08-Jun-05										PROSPECT LOCATION: Oceana Deposit								
PURPOSE: To test for zinc, lead and silver minerals from surface to 50m.																					
Drill hole ID	Recovery	Description	from (m)	to (m)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	Au PPM			
ZZE2 0-1	N/A	Not logged	0	1	X	0.02	X	X	4600	1610	12	X	X	670	0.02	10	0.1				
ZZE2 1-2	N/A	Not logged	1	2	X	0.02	X	X	5000	1460	12	X	X	410	0.02	10	0.2				
ZZE2 2-3	N/A	Not logged	2	3		1.33	0.17	X	10	13.40%	1580	45	X	X	4510	0.42	X	0.4			
ZZE2 3-4	N/A	Not logged	3	4		2.7	0.31	X	9	19.20%	1750	78		10	X	7280	1.03	X	0.5		
ZZE2 4-5	N/A	Not logged	4	5		1.86	0.28	X	12	11.90%	1850	63	X	X	4270	0.87	X	0.5			
ZZE2 5-6	N/A	Not logged	5	6		3.05	0.58	X	20	16.30%	2360	96		20	X	6000	1.72		20	0.8	
ZZE2 6-7	N/A	Not logged	6	7		2.31	0.38	X	16	14.70%	2550	78		20	X	5690	1.17	X		0.7	
ZZE2 7-8	N/A	Not logged	7	8		2.97	0.68	X	16	17.80%	2040	81		10	X	7540	1.45	X		1.1	
ZZE2 8-9	N/A	Not logged	8	9		2.5	0.72	X	13	18.00%	1770	61	X	X	6910	0.95	X			1	
ZZE2 9-10	N/A	Not logged	9	10		2.51	1.38	X	11	18.50%	2070	57		10	X	7590	0.95		10	1.3	
ZZE2 10-11	N/A	Not logged	10	11		2.45	1.99	X	16	16.40%	1750	53		10	X	7930	1.01	10	10	1.6	
ZZE2 11-12	N/A	Not logged	11	12		1.96	5.17	X	20	12.90%	2800	51		20	X	5290	1.90	40	40	2.9	
ZZE2 12-13	N/A	Not logged	12	13		2.16	18.5	X	25	8.98%	2910	56		20	X	2510	4.43	90	90	6.6	
ZZE2 13-14	N/A	Not logged	13	14		1.74	11.3		4	29	7.28%	2720	43		20	X	2390	3.13	80	80	4.8
ZZE2 14-15	N/A	Not logged	14	15		1.43	9.43		4	26	6.47%	2360	43		10	X	2270	2.45	60	60	4
ZZE2 15-16	N/A	Not logged	15	16		0.83	7.19		22	37	3.04%	2640	26	X	X	1100	1.72	50	50	3.4	
ZZE2 16-17	N/A	Not logged	16	17		1.38	4.39		10	36	1.50%	1280	19	X	X	490	1.55	60	60	2.9	
ZZE2 17-18	N/A	Not logged	17	18		0.31	4.78		9	37	9100	1100	20	X	X	310	1.13	70	70	1.5	
ZZE2 18-19	N/A	Not logged	18	19		0.21	2.64		5	20	8000	670	16	X	X	370	0.64	40	40	1.1	
ZZE2 19-20	N/A	Not logged	19	20		1.65	2.81		7	34	4900	600	13	X	X	150	1.31	60	60	2.6	
ZZE2 20-21	N/A	Not logged	20	21		1.48	4.12		10	39	6800	880	16	X	X	200	1.42	50	50	2.8	
ZZE2 21-22	N/A	Not logged	21	22		0.4	3.6		6	29	5400	820	15	X	X	150	0.82	50	50	1.1	
ZZE2 22-23	N/A	Not logged	22	23		0.26	5.01		8	30	1.10%	1090	18	X	X	410	0.95	50	50	1.3	
ZZE2 23-24	N/A	Not logged	23	24		0.27	2.01		5	22	1.52%	880	18	X	X	450	0.40	30	30	1	
ZZE2 24-25	N/A	Not logged	24	25		0.74	3.62		16	69	14.60%	740	24	X	X	870	0.52	50	50	2.6	
ZZE2 25-26	N/A	Not logged	25	26		0.99	11.1		27	93	28.70%	740	29		20	X	580	0.43	140	140	3.3
ZZE2 26-27	N/A	Not logged	26	27		1.14	17.5		74	152	34.70%	320	31		20	X	240	0.20	140	140	7.2
ZZE2 27-28	N/A	<2% Pb visible	27	28		1.67	8.05		39	114	23.60%	940	28		20	X	560	0.84	160	160	6.1
ZZE2 28-29	N/A	Not logged	28	29		2.36	7.18		21	74	12.70%	1630	34		10	X	2370	1.71	90	90	4.6
ZZE2 29-30	N/A	Not logged	29	30		1.43	9.24		19	63	7.33%	1680	34		20	X	2150	1.03	60	60	3.3
ZZE2 30-31	N/A	Not logged	30	31		1.9	10.3		21	83	10.10%	1440	36		10	X	2830	1.13	70	70	5.1
ZZE2 31-32	N/A	<2% Pb visible	31	32		1.48	10.1		58	68	19.80%	1380	20	X	X	1510	0.39	X		10.4	
ZZE2 32-33	N/A	Not logged	32	33		1.66	8.97		31	138	35.00%	860	35		30	X	390	0.41	200	200	5.9
ZZE2 33-34	N/A	Not logged	33	34		1.34	3.93		23	115	47.60%	390	30		30	X	80	0.10	170	170	4.2
ZZE2 34-35	N/A	Not logged	34	35		1.08	6.01		22	101	43.30%	510	28		20	X	210	0.18	200	200	3.9
ZZE2 35-36	N/A	<2% Pb visible	35	36		0.89	3.92		14	60	45.00%	420	24		20	X	170	0.15	160	160	2.4
ZZE2 36-37	N/A	No visible Pb in carbonate	36	37		0.9	5.66		21	58	44.90%	470	24		20	X	110	0.14	140	140	3.1
ZZE2 37-38	N/A	<2% Pb visible	37	38		1.21	7.77		19	47	39.60%	630	28		20	X	170	0.17	100	100	2.5
ZZE2 38-39	N/A	No visible Pb in carbonate	38	39		0.91	12.1		15	39	24.30%	1820	31		20	X	370	0.20	80	80	1.9
ZZE2 39-40	N/A	No visible Pb in carbonate	39	40		1.02	11.4		17	37	20.80%	2350	33		20	X	530	0.32	50	50	2.8

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY023 00-01	0	1	9.61	3.79	56	202	32.80%	340	6	1320	X	310	39	100	0.2
SY023 01-02	1	2	19.8	17.5	370	299	16.50%	1.70%	14	240	X	150	29	280	0.3
SY023 02-03	2	3	3.78	4.7	161	496	30.30%	3.96%	50	270	X	140	36.3	110	0.1
SY023 03-04	3	4	2.45	0.85	7	30	16.30%	9.76%	396	1170	X	80	18.1	20	X
SY023 04-05	4	5	2.3	0.84	15	55	7.93%	13.50%	105	570	X	80	8.44	30	0.3
SY023 05-06	5	6	3.2	1.15	21	42	5.29%	14.40%	45	210	X	90	5.47	30	0.3
SY023 06-07	6	7	2.49	0.78	14	93	7.73%	14.60%	70	460	X	180	7.26	30	0.3
SY023 07-08	7	8	2.11	0.96	18	168	9.50%	13.60%	90	510	X	160	12.2	30	0.3
SY023 08-09	8	9	2.38	0.38	5	506	9.45%	9.25%	202	540	X	230	9.5	40	0.2
SY023 09-10	9	10	1.46	0.67	5	80	22.80%	5.57%	175	790	X	220	22.9	80	0.5
SY023 10-11	10	11	36.8	0.51	46	272	16.10%	3460	36	720	X	180	33.3	40	0.5
SY023 11-12	11	12	38.1	0.43	55	665	14.00%	4010	59	370	X	190	31.9	30	0.4
SY023 12-13	12	13	0.76	0.32	8	113	27.20%	2980	30	2350	X	390	27.4	40	X
SY023 13-14	13	14	0.43	0.17	X	22	2.58%	2.58%	15	100	X	450	2.31	X	X
SY023 14-15	14	15	0.09	0.06	X	X	6400	2.08%	5	X	X	520	0.16	X	X
SY023 15-16	15	16	1.05	0.09	X	26	1.32%	1.77%	23	30	X	430	1.10	X	X
SY023 16-17	16	17	5.91	0.24	11	77	4.12%	3.21%	102	100	X	1180	5.25	20	0.1
SY023 17-18	17	18	0.14	0.2	5	47	3.54%	3.52%	64	80	X	6810	1.40	20	X
SY023 18-19	18	19	0.24	0.41	9	139	4.37%	1.07%	36	150	X	610	4.46	20	X
SY023 19-20	19	20	0.08	0.1	4	91	2.58%	1.50%	41	30	X	570	1.69	10	X
SY023 20-21	20	21	0.09	0.08	3	90	2.42%	1.55%	33	50	X	690	1.42	X	X
SY023 21-22	21	22	0.07	0.07	3	47	4.04%	3.93%	34	70	X	1010	2.12	10	X
SY023 22-23	22	23	0.02	X	X	39	2.85%	2.00%	20	10	X	710	0.56	X	X
SY023 23-24	23	24	X	X	X	38	2.87%	1.60%	20	X	X	650	0.53	X	X
SY023 24-25	24	25	0.01	X	X	35	2.34%	1.39%	14	X	X	530	0.09	X	X
SY023 25-26	25	26	0.02	0.01	X	37	3.49%	2.03%	15	20	X	850	0.37	X	X
SY023 26-27	26	27	0.07	0.01	X	24	2.89%	1.82%	15	20	X	690	0.50	X	X
SY023 27-28	27	28	0.09	0.06	X	35	2.64%	1.23%	16	50	X	800	0.68	X	X
SY023 28-29	28	29	0.02	X	X	38	2.95%	1.40%	22	40	X	600	1.19	X	X
SY023 29-30	29	30	0.01	0.01	X	42	3.01%	1.45%	22	240	X	700	1.12	X	X
SY023 30-31	30	31	0.02	X	X	33	3.20%	1.61%	26	30	X	880	0.79	X	X
SY023 31-32	31	32	0.02	0.01	X	15	2.29%	9710	14	10	X	750	0.28	X	X
SY023 32-33	32	33	0.04	0.02	X	17	1.95%	8480	11	X	X	350	0.21	X	X
SY023 33-34	33	34	X	X	X	27	2.03%	8460	13	20	X	520	0.14	X	X
SY023 34-35	34	35	X	0.01	X	42	2.40%	1.01%	18	30	X	480	0.32	X	X

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY024 0-1	0	1	10.6	5.17	157	456	21.90%	2.90%	16	1050	X	430	29.2	120	0.5
SY024 1-2	1	2	5.95	2.35	107	464	26.20%	2.22%	19	1880	X	380	31.6	120	0.6
SY024 2-3	2	3	0.77	1.03	27	266	18.50%	6.94%	36	780	X	300	19.1	60	0.2
SY024 3-4	3	4	0.39	0.46	4	14	3.28%	15.60%	35	150	X	260	1.58	10	0.1
SY024 4-5	4	5	0.31	0.29	X	77	4.99%	15.40%	27	230	X	140	2.17	10	0.1
SY024 5-6	5	6	0.45	0.43	4	49	5.96%	14.20%	42	250	X	1070	3.48	10	0.1
SY024 6-7	6	7	2.19	4.86	57	272	13.00%	9.55%	38	830	X	2960	12.5	40	0.2
SY024 7-8	7	8	0.71	1.73	25	149	10.90%	10.00%	40	1240	X	188%	10	30	0.2
SY024 8-9	8	9	0.17	0.22	X	70	5.74%	2.84%	89	280	X	1830	5.02	20	0.1
SY024 9-10	9	10	0.14	0.22	X	81	4.68%	1.68%	94	200	X	820	4.21	30	0.1
SY024 10-11	10	11	0.11	0.09	X	73	4.80%	2.02%	78	150	X	850	4.14	20	0.2
SY024 11-12	11	12	0.08	0.08	79	103	4.58%	1.89%	68	130	X	740	4.17	20	0.2
SY024 12-13	12	13	0.07	0.08	X	59	3.70%	1.59%	59	100	X	760	3.34	10	0.2
SY024 13-14	13	14	0.04	0.05	X	41	2.63%	1.14%	52	100	X	490	2.29	X	0.1
SY024 14-15	14	15	0.03	0.04	X	51	3.97%	1.38%	45	80	X	750	3.6	X	0.1
SY024 15-16	15	16	0.04	0.03	X	38	2.41%	1.19%	52	50	X	690	1.93	X	X
SY024 16-17	16	17	0.03	0.02	X	29	3.05%	1.84%	32	60	X	700	1.94	X	0.1
SY024 17-18	17	18	0.11	0.03	X	52	3.36%	1.71%	58	260	X	640	2.39	X	0.1
SY024 18-19	18	19	0.55	0.05	X	24	8.38%	8.25%	62	180	X	640	5.48	X	X
SY024 19-20	19	20	0.07	X	X	22	11.50%	12.80%	24	200	X	110	4.88	X	0.2
SY024 20-21	20	21	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 21-22	21	22	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 22-23	22	23	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 23-24	23	24	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 24-25	24	25	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 25-26	25	26	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR
SY024 26-27	26	27	0.07	X	X	7	3.47%	11.40%	X	40	X	15.20%	0.61	20	X
SY024 27-28	27	28	0.08	X	X	13	4.27%	11.10%	6	50	X	16.30%	0.66	X	0.1
SY024 28-29	28	29	0.12	0.05	X	59	5.01%	9.54%	30	180	X	5.23%	2.96	X	0.1
SY024 29-30	29	30	0.05	X	X	21	4.36%	10.90%	X	100	X	16.80%	0.60	X	0.1
SY024 30-31	30	31	0.03	X	91	20	4.04%	11.10%	X	210	X	18.40%	0.76	X	X
SY024 31-32	31	32	0.09	0.02	X	17	6.44%	11.90%	21	200	X	12.00%	1.38	X	X
SY024 32-33	32	33	0.3	0.02	X	8	3.54%	11.60%	10	50	X	15.70%	0.72	X	X
SY024 33-34	33	34	0.3	0.04	X	X	6.08%	12.50%	23	40	X	7.67%	0.47	X	X
SY024 34-35	34	35	0.16	0.02	X	23	3.94%	6.06%	30	50	X	5.49%	1.2	X	0.1

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY025 00-01	0	1	0.8	0.22	X	29	4.61%	13.50%	32	380	X	5.45%	3.51	10	
SY025 01-02	1	2	1.48	0.22	X	82	7.62%	13.30%	45	590	X	1.30%	>5.00	20	
SY025 02-03	2	3	1.36	0.3	X	57	5.44%	14.40%	33	460	X	3.47%	>5.00	20	
SY025 03-04	3	4	0.67	0.19	X	33	4.01%	16.00%	34	280	X	8010	3.78	X	
SY025 04-05	4	5	0.51	0.27	X	15	3.07%	15.70%	32	160	X	5320	2.29	X	
SY025 05-06	5	6	0.37	0.23	X	7	2.75%	16.60%	25	100	X	5520	1.75	X	
SY025 06-07	6	7	0.25	0.1	X	X	2.38%	17.70%	22	50	X	2250	1.19	X	
SY025 07-08	7	8	0.3	0.14	X	11	3.00%	16.50%	25	110	X	5290	1.99	X	
SY025 08-09	8	9	0.19	0.34	X	86	2.49%	14.30%	26	100	X	2.39%	1.6	X	
SY025 09-10	9	10	0.42	0.36	X	30	3.81%	13.20%	41	180	X	1.49%	3.15	10	
SY025 10-11	10	11	0.25	0.21	X	45	4.56%	10.20%	51	130	X	1.05%	3.68	10	
SY025 11-12	11	12	0.3	0.2	X	45	4.70%	8.73%	58	120	X	1.51%	4.12	20	
SY025 12-13	12	13	0.24	0.03	X	32	4.05%	5.48%	50	80	X	1.14%	2.75	10	
SY025 13-14	13	14	0.15	0.04	X	39	4.65%	6.35%	57	80	X	5800	3.64	10	
SY025 14-15	14	15	0.05	X	X	33	3.25%	2.00%	39	50	X	1190	2.39	X	
SY025 15-16	15	16	0.02	X	X	31	3.16%	1.71%	36	50	X	980	2.37	X	
SY025 16-17	16	17	0.04	0.02	X	70	2.97%	1.46%	59	70	X	1020	2.3	20	
SY025 17-18	17	18	0.04	X	X	41	3.21%	2.17%	40	50	X	1110	1.85	X	
SY025 18-19	18	19	0.03	0.01	3	35	2.79%	2.12%	32	40	X	890	0.83	X	
SY025 19-20	19	20	0.07	0.04	3	33	3.25%	3.36%	36	60	X	2670	1.62	X	
SY025 20-21	20	21	0.08	0.03	X	28	3.03%	2.90%	35	40	X	1920	1.27	X	
SY025 21-22	21	22	0.04	0.03	X	26	3.24%	2.67%	28	30	X	1620	0.86	X	
SY025 22-23	22	23	0.06	0.03	X	23	2.96%	3.13%	31	40	X	4760	0.93	X	
SY025 23-24	23	24	0.07	0.02	X	39	3.31%	3.04%	36	50	X	1980	0.65	X	
SY025 24-25	24	25	0.07	0.12	X	24	3.68%	2.98%	33	50	X	1840	0.53	X	
SY025 25-26	25	26	0.04	0.02	X	41	3.04%	2.66%	30	40	X	1820	0.42	X	
SY025 26-27	26	27	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	
SY025 27-28	27	28	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	
SY025 28-29	28	29	0.09	0.02	X	23	7.79%	15.80%	20	100	X	3.62%	0.706	X	
SY025 29-30	29	30	0.34	0.02	X	22	4.81%	16.60%	38	30	X	4.28%	1.7	X	
SY025 30-31	30	31	0.1	0.02	X	14	3.94%	16.80%	36	20	X	4.50%	1.02	X	
SY025 31-32	31	32	0.18	X	X	18	7.02%	14.40%	26	30	X	6.82%	2.6	X	
SY025 32-33	32	33	0.07	X	5	18	7.01%	11.50%	16	30	X	13.40%	2.38	X	
SY025 33-34	33	34	0.06	X	6	19	7.75%	10.50%	14	40	X	14.00%	2.72	X	
SY025 34-35	34	35	0.07	X	X	19	5.55%	12.60%	14	30	X	12.00%	1.52	X	

Comstock Drill Hole Assays, August 2005

<i>ID</i> <i>Drill hole</i>	<i>from</i> <i>(metres)</i>	<i>to</i> <i>(metres)</i>	<i>Zn</i> <i>%</i>	<i>Pb</i> <i>%</i>	<i>Ag</i> <i>PPM</i>	<i>Cu</i> <i>PPM</i>	<i>Fe</i> <i>PPM</i>	<i>Mg</i> <i>PPM</i>	<i>Ni</i> <i>PPM</i>	<i>As</i> <i>PPM</i>	<i>Bi</i> <i>PPM</i>	<i>Ca</i> <i>PPM</i>	<i>S</i> <i>%</i>	<i>Sb</i> <i>PPM</i>	<i>Hg</i> <i>PPM</i>
SY026 00-01	0	1	1.91	1.12	X	43	6.92%	10.70%	91	650	X	8850	>5.00	40	
SY026 01-02	1	2	1.79	1.14	X	45	6.31%	12.20%	76	460	X	6170	>5.00	50	
SY026 02-03	2	3	1.94	1.29	X	33	6.88%	12.30%	139	450	X	9980	>5.00	70	
SY026 03-04	3	4	1.75	1.79	X	34	6.05%	12.90%	122	380	X	1.24%	>5.00	100	
SY026 04-05	4	5	1.71	1.64	5	25	5.79%	9.99%	137	280	X	2940	>5.00	90	
SY026 05-06	5	6	1.18	0.89	X	23	6.73%	8.89%	145	270	X	1970	>5.00	60	
SY026 06-07	6	7	1.57	1.52	X	61	5.79%	8.40%	189	270	X	4000	>5.00	90	
SY026 07-08	7	8	0.39	0.37	X	40	2.40%	2.36%	44	80	X	1990	1.33	30	
SY026 08-09	8	9	0.3	0.31	X	60	3.26%	2.27%	47	110	X	1090	1.9	30	
SY026 09-10	9	10	0.16	0.22	3	78	3.63%	2.40%	44	100	X	3100	2.19	20	
SY026 10-11	10	11	0.17	0.18	X	117	3.42%	1.58%	42	130	X	720	2.14	20	
SY026 11-12	11	12	0.11	0.13	3	95	3.53%	1.81%	49	90	X	460	1.96	20	
SY026 12-13	12	13	0.09	0.06	X	89	3.63%	2.50%	29	340	X	3440	1.53	20	
SY026 13-14	13	14	0.43	0.15	5	43	2.59%	1.21%	36	250	X	680	1.73	20	
SY026 14-15	14	15	0.16	0.12	4	66	2.74%	1.47%	31	50	X	620	0.77	10	
SY026 15-16	15	16	0.4	0.43	4	33	3.08%	2.30%	49	80	X	440	1.27	30	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY027 00-01	0	1	2.59	1.47	12	250	25.20%	2.80%	87	2410	X	410	>5.00	60	
SY027 01-02	1	2	4.97	1.51	12	168	17.00%	5.15%	129	1430	X	260	>5.00	60	
SY027 02-03	2	3	4.47	1	7	105	15.00%	6.47%	184	2830	X	180	>5.00	70	
SY027 03-04	3	4	2.08	0.87	13	142	14.00%	9.47%	104	940	X	240	>5.00	50	
SY027 04-05	4	5	1.85	0.45	4	55	7.42%	11.90%	84	410	X	260	>5.00	30	
SY027 05-06	5	6	0.88	0.19	X	41	5.95%	9.71%	71	180	X	610	4.27	20	
SY027 06-07	6	7	2.4	0.51	4	281	6.85%	12.20%	120	480	X	200	>5.00	30	
SY027 07-08	7	8	2.08	0.25	X	118	5.31%	13.30%	135	320	X	190	4.77	20	
SY027 08-09	8	9	1.65	0.24	X	91	4.35%	9.07%	139	360	X	280	4.45	20	
SY027 09-10	9	10	1.75	0.27	X	28	5.25%	13.90%	92	330	X	110	3.79	20	
SY027 10-11	10	11	0.58	0.23	X	32	2.61%	4.91%	53	150	X	280	2.22	10	
SY027 11-12	11	12	1.24	0.53	4	60	7.06%	9.17%	130	440	X	350	>5.00	30	
SY027 12-13	12	13	0.99	0.53	4	63	7.27%	8.44%	168	550	X	430	>5.00	40	
SY027 13-14	13	14	0.44	0.38	6	83	4.55%	3.57%	126	300	X	590	4.97	30	
SY027 14-15	14	15	0.13	0.14	5	83	3.00%	2.02%	63	110	X	670	2.43	20	
SY027 15-16	15	16	0.12	0.17	X	85	3.42%	2.29%	70	120	X	1710	3.05	20	
SY027 16-17	16	17	0.14	0.12	X	104	2.85%	2.42%	50	120	X	740	1.65	20	
SY027 17-18	17	18	0.12	0.08	4	144	2.49%	1.68%	51	90	X	380	1.85	10	
SY027 18-19	18	19	0.05	0.03	X	47	2.76%	1.92%	46	70	X	590	1.66	X	
SY027 19-20	19	20	0.04	0.02	X	35	4.53%	6.18%	46	70	X	1780	1.54	X	
SY027 20-21	20	21	0.41	0.31	X	57	5.34%	7.29%	81	190	X	2070	2.96	20	
SY027 21-22	21	22	0.11	0.08	X	71	4.88%	5.84%	53	100	X	1540	2.12	X	
SY027 22-23	22	23	0.04	0.03	X	36	3.57%	2.70%	27	40	X	840	1.22	X	
SY027 23-24	23	24	0.03	0.02	X	60	3.80%	2.36%	40	140	X	730	1.92	X	
SY027 24-25	24	25	0.07	0.05	X	61	3.69%	2.39%	29	100	X	770	1.75	X	
SY027 25-26	25	26	0.05	0.04	X	58	3.52%	2.26%	34	120	X	780	1.49	X	
SY027 26-27	26	27	0.07	0.05	X	46	3.73%	2.10%	33	100	X	730	1.36	X	
SY027 27-28	27	28	0.26	0.13	X	32	3.89%	2.67%	53	110	X	1340	2.01	X	
SY027 28-29	28	29	0.12	0.02	X	84	3.53%	1.88%	35	30	X	670	0.68	X	
SY027 29-30	29	30	0.02	X	X	58	3.70%	1.45%	31	30	X	650	0.97	X	
SY027 30-31	30	31	0.02	X	X	35	3.19%	1.15%	32	30	X	510	1.05	X	
SY027 31-32	31	32	0.02	X	X	23	2.66%	1.11%	22	20	X	610	0.48	X	
SY027 32-33	32	33	0.03	X	5	24	3.26%	1.29%	23	30	X	750	0.88	X	
SY027 33-34	33	34	0.16	0.02	X	73	2.93%	1.48%	24	30	X	930	0.45	X	
SY027 34-35	34	35	0.03	0.01	X	27	3.24%	1.48%	26	30	X	880	0.50	X	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY028 00-01	0	1	0.29	0.3	X	20	3.52%	14.10%	34	330	X	210	3.3	30	0.1
SY028 01-02	1	2	0.64	0.64	X	16	2.91%	17.00%	31	140	X	60	2.57	40	X
SY028 02-03	2	3	0.63	0.65	X	11	2.17%	12.90%	23	90	X	320	1.54	20	0.1
SY028 03-04	3	4	1.22	0.48	7	163	16.20%	6.72%	27	1860	X	260	18.8	40	0.2
SY028 04-05	4	5	4.21	1.05	19	114	7.94%	6.86%	62	790	X	170	9.65	50	0.2
SY028 05-06	5	6	12.9	1.83	43	251	7.60%	10.70%	110	420	X	170	12.7	90	0.3
SY028 06-07	6	7	12.4	2.58	45	110	8.76%	10.40%	41	220	X	190	13.3	100	0.3
SY028 07-08	7	8	1.08	0.74	9	31	4.75%	15.80%	41	190	X	100	4.22	30	X
SY028 08-09	8	9	1.05	0.5	5	42	4.82%	14.90%	51	360	X	180	4.52	30	0.1
SY028 09-10	9	10	23.3	8.36	120	187	9.46%	5.24%	43	340	40	230	22.3	190	0.3
SY028 10-11	10	11	25.3	4.27	65	536	16.70%	2.77%	33	1010	40	330	31.9	160	0.3
SY028 11-12	11	12	7.6	2.13	35	277	13.80%	8.45%	68	1420	X	230	18.1	100	0.2
SY028 12-13	12	13	3.11	0.59	13	192	15.70%	9.62%	77	930	X	180	17.20	50	0.1
SY028 13-14	13	14	2.72	0.72	13	119	9.53%	13.10%	55	730	X	110	9.24	50	0.1
SY028 14-15	14	15	1.55	0.32	5	47	5.72%	11.70%	55	290	X	120	4.74	20	X
SY028 15-16	15	16	1.04	0.31	5	50	5.18%	7.92%	66	210	X	480	3.52	20	0.2
SY028 16-17	16	17	1.04	0.47	4	34	8.18%	13.30%	110	220	X	130	5.38	30	X
SY028 17-18	17	18	1.76	1.15	16	83	13.20%	10.90%	97	900	X	190	12.30	60	X
SY028 18-19	18	19	1.76	0.74	7	57	6.34%	9.58%	59	430	X	150	5.32	40	0.1
SY028 19-20	19	20	1.46	0.79	5	32	4.53%	13.40%	54	320	X	190	3.45	60	0.2
SY028 20-21	20	21	1.23	0.94	6	22	4.47%	9.02%	82	410	X	2220	2.13	50	0.1
SY028 21-22	21	22	0.25	0.15	X	64	2.64%	2.53%	61	130	X	560	1.73	20	0.1
SY028 22-23	22	23	0.2	0.11	X	103	7.48%	7.52%	49	200	X	1440	4.04	20	0.2
SY028 23-24	23	24	0.23	0.14	X	85	4.93%	5.26%	40	80	X	750	2.17	10	0.2
SY028 24-25	24	25	0.71	0.45	7	60	4.00%	4.01%	38	220	X	500	3.06	20	0.2
SY028 25-26	25	26	0.05	0.05	X	63	2.59%	2.06%	24	40	X	490	0.86	X	0.1
SY028 26-27	26	27	0.04	0.04	X	83	2.74%	2.06%	29	50	X	710	1.17	X	0.1
SY028 27-28	27	28	0.06	0.03	X	41	2.62%	1.41%	26	40	X	530	1.42	X	0.1
SY028 28-29	28	29	0.06	0.03	X	19	2.47%	1.56%	14	20	X	470	0.54	X	X
SY028 29-30	29	30	0.14	0.14	X	21	3.06%	2.23%	23	60	X	540	1.35	X	X

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY029 00-01	0	1	0.41	0.02	X	7	1.42%	18.80%	41	70	X	50	0.72	X	
SY029 01-02	1	2	0.38	X	X	5	2.08%	19.40%	78	120	X	60	1.49	X	
SY029 02-03	2	3	0.44	0.03	X	X	1.81%	12.80%	77	120	X	150	1.72	X	
SY029 03-04	3	4	0.93	0.12	X	15	3.59%	15.90%	122	240	X	150	3.99		10
SY029 04-05	4	5	0.81	0.1	X	18	4.49%	16.30%	120	240	X	80	>5.00	X	
SY029 05-06	5	6	0.75	0.1	X	22	4.57%	15.10%	140	280	X	110	>5.00		10
SY029 06-07	6	7	0.77	0.12	X	11	6.57%	13.90%	229	380	X	90	>5.00		10
SY029 07-08	7	8	0.67	0.13	X	11	4.06%	10.90%	111	250	X	350	4.18		10
SY029 08-09	8	9	0.55	0.1	X	8	2.72%	10.60%	69	120	X	160	2.29		10
SY029 09-10	9	10	0.49	0.14	X	81	2.88%	8.77%	72	130	X	140	2.18		10
SY029 10-11	10	11	0.55	0.07		3	87	4.46%	3.37%	141	180	X	140	4.84	20
SY029 11-12	11	12	1.68	0.3		8	221	16.10%	7.37%	138	1280	X	160	>5.00	40
SY029 12-13	12	13	1.17	0.18		6	201	24.10%	4.84%	111	2280	X	280	>5.00	50
SY029 13-14	13	14	0.33	0.07	X		98	30.90%	2.82%	98	2270	X	440	>5.00	40
SY029 14-15	14	15	1.48	0.3		8	153	14.10%	7.04%	140	1750	X	340	>5.00	40
SY029 15-16	15	16	1.29	0.15		5	52	9.99%	11.70%	125	710	X	370	>5.00	30
SY029 16-17	16	17	0.72	0.1	X		7	6.51%	15.00%	107	280	X	250	>5.00	20
SY029 17-18	17	18	0.85	0.14		3	40	6.15%	12.00%	109	370	X	1560	4.84	20
SY029 18-19	18	19	0.45	0.08	X		82	3.99%	6.24%	79	230	X	1.69%	2.59	20
SY029 19-20	19	20	0.26	0.03	X		33	4.75%	7.38%	68	180	X	3.38%	1.52	20
SY029 20-21	20	21	0.09	0.1	X		38	2.87%	2.79%	58	110	X	3.47%	0.54	20
SY029 21-22	21	22	0.19	0.06	X		57	4.61%	4.90%	55	200	X	1.65%	2.12	20
SY029 22-23	22	23	0.12	0.03	X		42	5.13%	6.69%	33	140	X	2090	1.82	X
SY029 23-24	23	24	0.09	0.03	X		59	4.01%	4.93%	33	80	X	3210	1.40	X
SY029 24-25	24	25	0.05	0.03	X		94	4.85%	4.58%	30	150	X	2340	2.08	X
SY029 25-26	25	26	0.09	0.04	X		99	3.62%	2.66%	31	150	X	1170	2.04	X
SY029 26-27	26	27	0.04	0.02	X		52	3.03%	1.70%	30	100	X	1050	1.99	X
SY029 27-28	27	28	0.13	0.03	X		41	3.11%	2.70%	33	120	X	790	1.69	X
SY029 28-29	28	29	0.12	0.04	X		65	3.34%	2.73%	38	100	X	1500	1.68	X
SY029 29-30	29	30	0.08	1.29	X		41	2.87%	2.47%	26	90	X	1150	1.22	X
SY029 30-31	30	31	0.11	0.03	X		36	2.66%	2.15%	26	90	X	1350	1.28	X
SY029 31-32	31	32	0.15	0.05	X		40	3.09%	2.29%	35	150	X	2430	1.81	X
SY029 32-33	32	33	0.1	0.04	X		21	2.83%	1.79%	36	110	X	730	2.19	X
SY029 33-34	33	34	0.09	0.04	X		40	3.15%	1.69%	25	60	X	870	1.56	X
SY029 34-35	34	35	0.25	0.1	X		42	3.13%	2.31%	33	120	X	910	1.81	X

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY030 00-01	0	1	0.44	0.04	X	X	4.55%	14.80%	73	200	X	70	>5.00	X	
SY030 01-02	1	2	0.33	0.01	X		2.30%	9.70%	41	80	X	260	2.18	X	
SY030 02-03	2	3	0.48	0.03	X		3.47%	12.00%	76	190	X	410	3.52	10	
SY030 03-04	3	4	0.23	X	X		2.96%	11.80%	36	210	X	170	2.52	10	
SY030 04-05	4	5	0.23	X	X		4.07%	16.50%	37	220	X	80	3.54	10	
SY030 05-06	5	6	0.47	0.04	X		6.68%	12.30%	56	310	X	190	>5.00	10	
SY030 06-07	6	7	0.16	0.05		4	36	4.56%	2.41%	55	170	570	4.82	20	
SY030 07-08	7	8	0.13	0.03	X		32	3.87%	2.37%	49	150	310	3.77	10	
SY030 08-09	8	9	0.21	0.03	X		38	3.89%	2.52%	56	140	430	4.06	20	
SY030 09-10	9	10	0.11	0.02	X		46	3.61%	1.49%	66	110	760	3.79	20	
SY030 10-11	10	11	0.08	0.02	X		62	4.05%	1.74%	57	90	1130	3.92	10	
SY030 11-12	11	12	0.08	X	X		32	3.61%	2.55%	30	50	940	2.80	X	
SY030 12-13	12	13	0.04	0.01	X		40	3.27%	1.72%	46	60	790	2.69	10	
SY030 13-14	13	14	0.05	X	X		47	3.97%	2.50%	34	60	970	2.85	10	
SY030 14-15	14	15	0.03	X	X		42	3.26%	2.13%	29	60	910	2.33	10	
SY030 15-16	15	16	0.03	X	X		53	3.70%	1.83%	43	100	980	2.93	20	
SY030 16-17	16	17	0.03	X	X		60	3.79%	1.69%	44	80	990	3.07	20	
SY030 17-18	17	18	0.03	X	X		53	3.61%	1.70%	43	80	1010	2.87	20	
SY030 18-19	18	19	0.03	X	X		42	3.28%	1.82%	30	70	870	1.77	10	
SY030 19-20	19	20	0.02	X	X		37	2.95%	2.02%	22	50	830	1.46	X	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY031 00-01	0	1	0.19	0.19	5	117	6.44%	4.71%	78	370	X	710	>5.00	20	
SY031 01-02	1	2	0.33	0.18	3	34	7.79%	7.70%	56	410	X	1210	>5.00	20	
SY031 02-03	2	3	0.26	0.14	X	55	5.73%	5.02%	76	360	X	2090	>5.00	20	
SY031 03-04	3	4	0.26	0.11	3	59	5.75%	4.57%	72	500	X	1290	>5.00	20	
SY031 04-05	4	5	0.09	0.03	X	58	7.90%	5.45%	68	200	X	690	>5.00	20	
SY031 05-06	5	6	0.12	0.04	X	54	7.02%	5.21%	57	150	X	720	>5.00	20	
SY031 06-07	6	7	0.11	0.03	X	44	3.91%	2.88%	62	110	X	760	3.71	20	
SY031 07-08	7	8	0.07	0.01	X	37	3.41%	2.76%	45	80	X	710	3.33	X	
SY031 08-09	8	9	0.08	0.01	X	44	3.76%	3.69%	49	90	X	640	3.78	X	
SY031 09-10	9	10	0.06	0.02	X	45	3.77%	1.56%	50	100	X	850	3.84	10	
SY031 10-11	10	11	0.03	0.05	X	45	3.18%	1.18%	44	60	X	740	3.40	10	
SY031 11-12	11	12	0.02	0.02	X	48	3.48%	7720	51	50	X	580	3.52	10	
SY031 12-13	12	13	1.89	0.69	8	85	6.38%	5.94%	62	360	X	660	>5.00	30	
SY031 13-14	13	14	0.32	0.12	X	50	3.58%	1.49%	48	100	X	730	3.17	10	
SY031 14-15	14	15	0.39	0.15	3	52	4.16%	1.76%	48	150	X	700	3.71	20	
SY031 15-16	15	16	0.95	0.34	6	69	5.41%	4.70%	53	240	X	720	4.69	30	
SY031 16-17	16	17	0.17	0.06	X	80	3.54%	1.66%	49	80	X	2380	2.52	10	
SY031 17-18	17	18	0.04	0.02	X	72	3.23%	1.17%	60	90	X	810	2.48	20	
SY031 18-19	18	19	0.4	0.17	X	50	3.59%	3.55%	52	150	X	2810	2.14	20	
SY031 19-20	19	20	0.07	0.03	X	36	2.87%	1.70%	25	40	X	1510	0.87	X	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY032 00-01	0	1	0.02	0.03	5	9	1.23%	18.40%	X	50	X	370	0.18	X	X
SY032 01-02	1	2	0.02	0.02	9	8	2.04%	16.20%	X	50	X	6570	0.09	10	X
SY032 02-03	2	3	0.04	0.16	103	47	4.35%	13.80%	X	40	X	3.90%	0.09	240	0.4
SY032 03-04	3	4	2.87	6.61	171	1620	26.10%	3.53%	X	150	X	6060	28.40	200	0.4
SY032 04-05	4	5	2.09	4.13	167	1030	11.70%	9.39%	X	90	X	1.48%	12.80	210	0.6
SY032 05-06	5	6	6.55	3.15	118	1120	9.94%	9.71%	5	140	X	2.47%	13.10	180	0.3
SY032 06-07	6	7	36.3	5.05	130	292	8.92%	3.60%	12	180	X	1.01%	25.10	240	0.4
SY032 07-08	7	8	4.94	1.74	52	292	6.24%	11.80%	7	120	X	4.44%	7.02	80	0.1
SY032 08-09	8	9	4.45	0.76	28	137	4.81%	12.00%	5	60	X	5.29%	3.97	50	0.1
SY032 09-10	9	10	8.59	0.85	29	106	5.62%	10.70%	10	70	X	4.25%	6.43	50	0.1
SY032 10-11	10	11	34.3	1.98	91	188	9.25%	4.04%	14	110	X	1.54%	23.20	180	0.3
SY032 11-12	11	12	8.99	1.87	31	130	7.16%	8.54%	9	110	X	2.51%	9.14	100	0.1
SY032 12-13	12	13	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 13-14	13	14	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 14-15	14	15	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 15-16	15	16	12	2.18	33	89	6.63%	9.48%	8	90	X	7510	10.30	70	X
SY032 16-17	16	17	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 17-18	17	18	7.7	2.24	40	161	7.00%	9.22%	8	100	X	1.21%	9.98	60	0.1
SY032 18-19	18	19	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 19-20	19	20	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 20-21	20	21	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 21-22	21	22	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 22-23	22	23	-	-	-	-	-	-	-	-	-	-	-	-	-
SY032 23-24	23	24	3.63	0.88	21	173	6.31%	3.88%	27	120	X	9260	5.54	60	0.1
SY032 24-25	24	25	1.23	1.98	27	59	6.79%	10.30%	8	180	X	6.31%	2.77	40	0.1
SY032 25-26	25	26	0.97	2.03	22	48	7.83%	9.93%	8	160	X	5.51%	4.22	30	X
SY032 26-27	26	27	0.72	0.55	9	200	22.40%	3.64%	10	530	X	1.99%	16.5	40	0.2
SY032 27-28	27	28	0.61	0.39	9	120	36.30%	1.01%	6	2620	X	6880	34.3	60	0.2
SY032 28-29	28	29	0.56	0.67	11	74	31.70%	2.06%	20	2090	X	7770	28.7	60	0.1
SY032 29-30	29	30	0.71	1.43	16	74	18.80%	3.81%	39	740	X	1.51%	14.3	60	0.1
SY032 30-31	30	31	0.46	0.95	12	49	7.90%	3.21%	51	350	X	1.81%	4.10	40	0.1
SY032 31-32	31	32	0.44	0.79	12	52	7.87%	2.46%	51	320	X	1.13%	5.03	40	X
SY032 32-33	32	33	0.83	1.84	19	56	9.78%	3.48%	45	430	X	9440	7.25	50	X
SY032 33-34	33	34	0.55	1.27	21	98	9.44%	2.96%	47	330	X	5410	7.19	60	0.1
SY032 34-35	34	35	0.5	1.64	20	59	8.77%	2.17%	49	290	X	5250	7.81	50	0.1
SY032 35-36	35	36	0.28	0.63	11	91	9.58%	3.25%	49	210	X	6380	4.62	30	X
SY032 36-37	36	37	0.36	1.24	15	92	10.00%	2.89%	46	260	X	9120	6.69	50	X
SY032 37-38	37	38	0.49	1.16	12	54	7.74%	3.73%	37	240	X	1.14%	4.07	30	X
SY032 38-39	38	39	0.41	0.91	10	47	7.24%	3.86%	46	280	X	1.01%	3.87	30	X
SY032 39-40	39	40	0.32	0.56	9	109	6.21%	3.24%	46	460	X	6250	3.64	40	X
SY032 40-41	40	41	0.43	1.03	11	46	5.84%	3.23%	40	220	X	6720	3.61	40	X
SY032 41-42	41	42	0.31	0.43	6	51	4.75%	2.54%	48	200	X	3820	3.27	30	X
SY032 42-43	42	43	0.19	0.24	4	51	4.66%	1.96%	49	130	X	7430	3.34	30	X
SY032 43-44	43	44	0.37	0.54	6	55	6.42%	3.22%	48	220	X	5970	4.06	20	X
SY032 44-45	44	45	0.2	0.27	6	72	6.17%	2.38%	66	140	X	3470	4.83	30	X
SY032 45-46	45	46	0.33	0.34	4	29	3.86%	1.96%	21	160	X	3670	2.77	20	X

Comstock Drill Hole Assays, August 2005

<i>ID</i> <i>Drill hole</i>	<i>from</i> <i>(metres)</i>	<i>to</i> <i>(metres)</i>	<i>Zn</i> <i>%</i>	<i>Pb</i> <i>%</i>	<i>Ag</i> <i>PPM</i>	<i>Cu</i> <i>PPM</i>	<i>Fe</i> <i>PPM</i>	<i>Mg</i> <i>PPM</i>	<i>Ni</i> <i>PPM</i>	<i>As</i> <i>PPM</i>	<i>Bi</i> <i>PPM</i>	<i>Ca</i> <i>PPM</i>	<i>S</i> <i>%</i>	<i>Sb</i> <i>PPM</i>	<i>Hg</i> <i>PPM</i>
SY032 46-47	46	47	0.2	0.47	6	24	4.45%	2.77%	14	190 X		5480	3.13	20 X	
SY032 47-48	47	48	0.13	0.12	4	78	5.79%	1.17%	50	220 X		3470	5.52	20 X	
SY032 48-49	48	49	0.13	0.11	3	56	5.49%	1.16%	69	150 X		2510	5.48	20 X	
SY032 49-50	49	50	0.22	0.5	6	33	5.58%	2.74%	40	180 X		6370	4.02	30 X	
SY032 50-51	50	51	0.08	0.12 X		45	3.74%	1.38%	64	110 X		4200	3.10	30 X	
SY032 51-52	51	52	0.07	0.08 X		45	4.24%	1.33%	60	140 X		3760	3.71	30 X	
SY032 52-53	52	53	0.14	0.33	4	48	4.67%	2.04%	57	160 X		8950	3.71	30 X	
SY032 53-54	53	54	0.08	0.11 X		57	3.51%	1.17%	47	100 X		5520	3.01	30 X	
SY032 54-55	54	55	0.1	0.06 X		54	3.72%	1.37%	61	100 X		9190	3.12	30 X	
SY032 55-56	55	56	0.18	0.52	8	57	5.43%	2.97%	54	170 X		1.52%	3.99	40 X	
SY032 56-57	56	57	0.04	0.07 X		56	3.80%	1.44%	66	110 X		6220	3.06	30 X	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY033 00-01	0	1	0.05	0.06	X	15	7000	2.17%	X	40	X	220	0.13	X	X
SY033 01-02	1	2	0.04	0.02	X	9	1.00%	17.30%	X	20	X	220	0.11	X	X
SY033 02-03	2	3	0.07	0.11	X	17	1.01%	8.19%	5	40	X	940	0.29	20	X
SY033 03-04	3	4	0.06	0.1	4	16	1.02%	8.27%	6	40	X	260	0.29	10	X
SY033 04-05	4	5	1.7	0.63	16	46	2.43%	17.60%	7	50	X	570	2.10	40	0.1
SY033 05-06	5	6	0.78	0.27	7	34	1.87%	18.40%	11	50	X	490	1.46	30	X
SY033 06-07	6	7	0.41	0.19	X	13	1.69%	18.20%	15	40	X	380	1.19	30	X
SY033 07-08	7	8	0.37	0.34	X	11	2.15%	17.80%	11	40	X	1190	1.15	40	X
SY033 08-09	8	9	0.21	0.18	X	X	2.03%	18.20%	5	20	X	1470	0.36	30	X
SY033 09-10	9	10	0.19	0.17	X	5	1.54%	18.80%	11	20	X	4910	0.31	30	X
SY033 10-11	10	11	0.21	0.16	X	X	2.04%	18.20%	X	50	X	1.13%	0.29	40	X
SY033 11-12	11	12	0.28	0.31	X	10	2.11%	16.20%	5	50	X	4.02%	0.51	50	X
SY033 12-13	12	13	0.14	0.08	X	9	2.25%	12.60%	X	60	X	10.40%	0.28	40	X
SY033 13-14	13	14	2.71	0.66	16	127	9.44%	12.10%	X	220	X	3.52%	9.67	90	X
SY033 14-15	14	15	2.44	0.7	18	143	9.98%	12.70%	X	520	X	2.73%	10.7	60	X
SY033 15-16	15	16	3.54	1.12	34	106	11.50%	12.40%	X	4050	X	1.28%	14.1	100	X
SY033 16-17	16	17	4.9	2.63	63	149	12.10%	10.80%	6	1.40%	X	1.16%	14.9	220	X
SY033 17-18	17	18	1.77	1.01	28	57	7.85%	14.70%	14	1.79%	X	4100	7.99	200	X
SY033 18-19	18	19	0.57	0.28	5	14	3.26%	17.50%	10	1260	X	1300	2.05	40	X
SY033 19-20	19	20	1.9	1	23	67	7.30%	14.70%	12	7140	X	1.09%	8.02	120	X
SY033 20-21	20	21	1.01	0.69	14	29	5.73%	16.40%	10	3620	X	3990	5.49	70	X
SY033 21-22	21	22	0.97	0.48	13	22	4.65%	17.00%	10	1660	X	3180	4.22	50	X
SY033 22-23	22	23	3.1	0.39	15	28	5.10%	15.40%	11	860	X	5700	6.06	70	X
SY033 23-24	23	24	2.46	0.49	11	21	5.72%	15.40%	12	820	X	820	6.79	70	X
SY033 24-25	24	25	1.37	0.44	9	20	8.18%	14.30%	10	610	X	2190	8.85	50	X
SY033 25-26	25	26	0.84	0.3	6	18	4.40%	16.50%	10	640	X	4180	3.93	40	X
SY033 26-27	26	27	5.11	0.8	25	74	24.60%	6.56%	X	1570	X	1070	29.9	90	X
SY033 27-28	27	28	2.17	0.62	16	44	17.50%	7.11%	X	1050	X	5.89%	21.8	80	X
SY033 28-29	28	29	0.35	0.19	X	15	4.64%	15.30%	15	300	X	3.26%	2.84	30	X
SY033 29-30	29	30	0.12	0.03	X	10	3.33%	13.50%	10	100	X	12.10%	1.54	10	X
SY033 30-31	30	31	0.06	0.02	X	9	2.74%	12.00%	10	110	X	14.90%	1.19	10	X
SY033 31-32	31	32	0.3	0.15	X	26	5.73%	12.50%	12	570	X	7.60%	4.76	30	X
SY033 32-33	32	33	0.19	0.09	4	48	8.38%	4.91%	51	830	X	5.63%	8.80	30	0.3
SY033 33-34	33	34	0.08	0.04	4	69	5.02%	2.37%	76	220	X	1.43%	4.74	40	X
SY033 34-35	34	35	0.03	0.03	X	69	4.03%	1.63%	77	110	X	1930	3.65	20	X
SY033 35-36	35	36	0.07	0.04	3	92	4.94%	2.43%	79	150	X	5090	4.71	40	X
SY033 36-37	36	37	0.03	0.03	X	67	4.38%	1.98%	66	110	X	1640	3.86	20	X
SY033 37-38	37	38	0.37	0.11	5	158	6.83%	2.49%	67	240	X	1520	6.49	40	X
SY033 38-39	38	39	0.13	0.04	3	63	4.54%	1.06%	77	130	X	1520	4.73	40	X
SY033 39-40	39	40	0.38	0.13	5	57	6.09%	1.56%	66	300	X	2880	6.21	40	X
SY033 40-41	40	41	0.84	0.21	9	56	9.03%	2.12%	54	430	X	4340	10.10	60	X
SY033 41-42	41	42	0.75	0.16	8	51	7.67%	2.88%	47	340	X	6560	8.31	60	X
SY033 42-43	42	43	0.43	0.13	7	50	5.84%	1.86%	58	370	X	4260	6.57	50	X
SY033 43-44	43	44	2.66	0.34	14	64	11.40%	2.52%	39	600	X	6930	14.40	70	X
SY033 44-45	44	45	4.27	0.47	22	85	14.10%	1.46%	45	520	X	3440	18.40	90	0.1
SY033 45-46	45	46	2.07	0.33	16	110	11.00%	9990	56	390	X	2250	13.30	60	X

Comstock Drill Hole Assays, August 2005

<i>ID</i> <i>Drill hole</i>	<i>from</i> <i>(metres)</i>	<i>to</i> <i>(metres)</i>	<i>Zn</i> <i>%</i>	<i>Pb</i> <i>%</i>	<i>Ag</i> <i>PPM</i>	<i>Cu</i> <i>PPM</i>	<i>Fe</i> <i>PPM</i>	<i>Mg</i> <i>PPM</i>	<i>Ni</i> <i>PPM</i>	<i>As</i> <i>PPM</i>	<i>Bi</i> <i>PPM</i>	<i>Ca</i> <i>PPM</i>	<i>S</i> <i>%</i>	<i>Sb</i> <i>PPM</i>	<i>Hg</i> <i>PPM</i>
SY033 46-47	46	47	2.1	0.33	16	67	12.90%	1.77%	48	440 X		6670	15.80	60 X	
SY033 47-48	47	48	1.62	0.23	11	52	9.07%	1.85%	32	370 X		5160	11.10	50 X	
SY033 48-49	48	49	1.33	0.31	14	58	10.90%	1.60%	39	430 X		3990	13.20	60 X	
SY033 49-50	49	50	1.17	0.31	13	113	9.36%	1.68%	56	430 X		4180	11.40	50 X	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM	
SY034 00-01	0	1	0.02	0.02	X	50	6900	4430	6	10	X	550	0.37	X	X	
SY034 01-02	1	2	0.02	X	X	8	6000	1.62%	6	10	X	500	0.18	X	X	
SY034 02-03	2	3	0.02	X	X	8	1.86%	18.20%	6	20	X	840	0.15		20	X
SY034 03-04	3	4	0.02	X	X	8	1.19%	9.69%	6	X	X	350	0.18	X	X	
SY034 04-05	4	5	0.04	0.05	X	18	1.74%	18.40%	5	20	X	4750	0.12		30	X
SY034 05-06	5	6	0.03	X	X	X	1.84%	18.30%	X	30	X	4010	0.17		30	LNR
SY034 06-07	6	7	0.03	0.12	X	18	1.76%	18.20%	5	30	X	1.52%	0.10		40	X
SY034 07-08	7	8	0.06	0.24	X	19	2.00%	17.10%	7	50	X	3.03%	0.33		30	X
SY034 08-09	8	9	0.2	0.27	X	9	2.30%	16.30%	13	80	X	3.88%	0.48		30	X
SY034 09-10	9	10	0.17	0.16	X	5	1.34%	16.70%	6	30	X	4.28%	0.19		20	X
SY034 10-11	10	11	0.16	0.15	X	5	1.40%	17.50%	6	20	X	2.28%	0.17		20	X
SY034 11-12	11	12	0.33	0.13	X	X	2.40%	14.90%	X	20	X	6.35%	0.13		20	X
SY034 12-13	12	13	0.41	0.1	X	X	2.04%	14.80%	X	20	X	6.44%	0.35		20	X
SY034 13-14	13	14	0.3	0.08	X	X	1.72%	12.30%	X	20	X	9.84%	0.31	X		X
SY034 14-15	14	15	1.99	0.64	8	10	3.72%	11.90%	X	100	X	6.58%	2.41		30	X
SY034 15-16	15	16	9.47	1.48	35	42	5.80%	12.40%	10	240	X	1.85%	>5.00		70	0.1
SY034 16-17	16	17	1.24	0.38	5	13	3.47%	15.40%	8	110	X	2.83%	2.15		30	X
SY034 17-18	17	18	15.5	2.52	58	80	8.67%	10.10%	6	240	X	2.06%	>5.00		100	0.1
SY034 18-19	18	19	4.86	1.2	20	26	4.76%	10.80%	5	190	X	6.29%	>5.00		50	X
SY034 19-20	19	20	1.07	0.44	4	11	3.57%	14.50%	8	90	X	4.37%	1.88		30	X
SY034 20-21	20	21	0.5	0.19	X	X	3.09%	12.70%	6	60	X	9.01%	0.90		20	X
SY034 21-22	21	22	2.46	0.09	X	10	3.64%	11.70%	X	80	X	13.40%	1.99		20	X
SY034 22-23	22	23	0.6	0.09	X	5	2.76%	13.50%	X	60	X	14.10%	1.06	X		X
SY034 23-24	23	24	0.36	0.18	X	7	3.86%	13.70%	8	120	X	10.40%	2.22		10	X
SY034 24-25	24	25	14.1	1.24	32	49	16.00%	7.79%	15	1110	X	1.63%	>5.00		80	X
SY034 25-26	25	26	5.35	0.56	13	21	8.55%	11.20%	8	520	X	7.68%	>5.00		40	X
SY034 26-27	26	27	0.56	0.1	X	X	3.95%	16.00%	X	70	X	3.86%	1.25		10	X
SY034 27-28	27	28	0.38	0.06	X	X	2.06%	13.90%	6	20	X	10.20%	0.62		10	X
SY034 28-29	28	29	0.52	0.1	X	X	1.84%	11.50%	9	40	X	13.80%	0.98		10	X
SY034 29-30	29	30	0.67	0.08	X	X	2.79%	15.20%	X	40	X	6.07%	1.04		10	X
SY034 30-31	30	31	0.4	0.1	X	X	5.01%	12.50%	6	50	X	5.08%	0.99		10	X
SY034 31-32	31	32	2.57	1.43	23	183	19.30%	5.61%	9	130	X	3.47%	>5.00		40	X
SY034 32-33	32	33	0.51	0.6	14	283	28.80%	1.92%	19	510	X	7500	>5.00		40	0.1
SY034 33-34	33	34	0.91	0.31	8	105	10.90%	3.87%	49	350	X	2.86%	>5.00		40	0.1
SY034 34-35	34	35	0.5	0.17	5	54	4.23%	1.67%	53	210	X	6520	3.64		20	X
SY034 35-36	35	36	0.22	0.07	4	45	3.93%	1.02%	56	190	X	2480	3.71		20	X
SY034 36-37	36	37	0.6	0.13	5	57	4.37%	1.20%	54	160	X	3830	4.55		30	X
SY034 37-38	37	38	0.18	0.05	X	46	3.81%	1.04%	67	100	X	1950	3.78		30	X
SY034 38-39	38	39	0.21	0.05	X	62	3.63%	1.18%	68	100	X	1890	3.27		20	X
SY034 39-40	39	40	0.38	0.07	3	46	3.81%	1.30%	61	110	X	3180	3.98		20	X
SY035 00-01	0	1	6.15	2.43	61	246	21.80%	5.12%	5	2190	X	1870	28.5		70	0.1
SY035 01-02	1	2	5.52	6.62	120	151	26.30%	3.14%	8	2470	X	1480	33		100	X
SY035 02-03	2	3	3.63	1.45	24	165	13.30%	10.80%	10	1360	X	1270	16.1		40	0.1
SY035 03-04	3	4	0.9	0.56	8	42	7.46%	15.10%	7	680	X	2460	7.68		30	X
SY035 04-05	4	5	1.06	0.59	9	43	8.95%	13.20%	15	840	X	1440	9.34		30	X
SY035 05-06	5	6	2.38	1.38	21	125	14.30%	9.94%	19	1510	X	2200	15.8		50	0.2

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY035 06-07	6	7	1.57	1.35	20	38	7.42%	15.00%	22	730	X	610	8.13	50	0.2
SY035 07-08	7	8	1.74	0.54	8	27	6.16%	15.90%	25	630	X	640	6.53	40	0.2
SY035 08-09	8	9	1.67	0.87	8	44	7.80%	12.80%	37	730	X	2730	8.72	40	0.1
SY035 09-10	9	10	2.55	1.95	26	61	10.90%	12.30%	53	1100	X	2250	12.9	60	X
SY035 10-11	10	11	0.92	1.47	18	51	9.94%	14.40%	22	880	X	1600	10.3	30	0.1
SY035 11-12	11	12	0.57	0.19	X	41	5.20%	16.10%	8	150	X	1.07%	2.55	30	X
SY035 12-13	12	13	6.07	1.19	28	259	18.80%	5.93%	22	570	X	6500	21.2	40	0.3
SY035 13-14	13	14	1.13	0.35	10	143	15.20%	2.88%	18	600	X	6110	14.9	50	0.5
SY035 14-15	14	15	0.2	0.1	8	68	16.20%	1.43%	74	420	X	7060	16.6	60	0.3
SY035 15-16	15	16	0.97	0.38	12	55	4.74%	1.37%	63	100	X	5280	4.5	40	0.1
SY035 16-17	16	17	1.71	0.43	19	64	4.54%	1.17%	65	150	X	3610	5.01	40	0.1
SY035 17-18	17	18	0.76	0.27	13	60	4.20%	9030	62	110	X	2220	4.51	30	0.1
SY035 18-19	18	19	1.03	0.15	10	55	4.73%	1.12%	50	120	X	2900	5.02	30	0.1
SY035 19-20	19	20	0.25	0.09	8	48	4.57%	1.07%	61	210	X	1860	4.34	40	X
SY036 00-01	0	1	0.41	0.41	5	53	3.89%	15.50%	7	240	X	1090	2.84	30	X
SY036 01-02	1	2	0.62	0.64	7	66	3.96%	13.70%	10	270	X	880	3.18	40	X
SY036 02-03	2	3	0.56	0.65	7	56	3.64%	13.60%	13	240	X	340	2.91	50	X
SY036 03-04	3	4	0.1	0.31	X	48	1.84%	18.30%	X	70	X	80	0.48	40	X
SY036 04-05	4	5	0.15	0.42	X	70	2.15%	18.70%	X	120	X	70	0.81	40	X
SY036 05-06	5	6	0.18	0.58	X	166	2.66%	18.20%	7	130	X	350	1.32	40	X
SY036 06-07	6	7	0.26	0.56	X	164	3.19%	17.00%	6	140	X	7930	1.35	40	X
SY036 07-08	7	8	1.38	0.32	X	68	6.18%	13.50%	X	100	X	3.45%	1.97	30	X
SY036 08-09	8	9	6.36	3.52	42	101	9.30%	9.98%	X	140	X	3.80%	7.49	60	X
SY036 09-10	9	10	40.5	7.05	123	253	13.20%	1.16%	X	350	X	4750	29	100	0.3
SY036 10-11	10	11	37.5	10.2	134	223	11.20%	1.52%	7	320	X	6240	28.5	90	0.2
SY036 11-12	11	12	7.42	1.79	26	173	5.35%	11.60%	X	420	X	7.59%	8.17	40	X
SY036 12-13	12	13	2.9	0.77	10	136	3.79%	13.30%	9	720	X	9.68%	3.78	20	X
SY036 13-14	13	14	1.29	0.37	3	93	3.24%	13.00%	X	120	X	7.37%	1.92	10	X
SY036 14-15	14	15	0.93	0.26	3	21	3.17%	2.89%	11	60	X	1.57%	1.56	X	0.2
SY036 15-16	15	16	0.59	0.26	4	61	4.72%	2.33%	56	100	X	1.56%	3.16	20	0.2
SY036 16-17	16	17	0.62	0.17	4	55	5.22%	2.05%	67	140	X	1.20%	4.25	20	0.1
SY036 17-18	17	18	0.31	0.1	4	51	5.15%	1.96%	57	340	X	7880	3.76	20	X
SY036 18-19	18	19	0.57	0.14	7	49	4.51%	1.79%	57	200	X	6700	4.25	20	X
SY036 19-20	19	20	0.51	0.18	9	58	4.93%	1.19%	56	130	X	4120	5.02	20	X
SY037 00-01	0	1	0.3	0.12	X	27	4.97%	7.30%	13	100	X	8580	1.87	20	X
SY037 01-02	1	2	1.7	0.34	13	128	18.30%	1.53%	25	760	X	1.80%	20	80	0.2
SY037 02-03	2	3	2.03	0.17	9	186	32.70%	1.63%	14	2580	X	5040	38.8	20	0.2
SY037 03-04	3	4	0.66	0.27	6	103	26.20%	3.69%	16	2280	X	1.07%	28.9	X	0.1
SY037 04-05	4	5	0.45	0.11	3	67	11.40%	5.20%	37	620	X	2.21%	10.2	10	0.3
SY037 05-06	5	6	0.62	0.07	X	31	11.70%	10.60%	15	660	X	5.69%	9.5	20	0.2
SY037 06-07	6	7	0.19	0.06	5	41	23.10%	4.31%	23	1060	X	1.48%	25	40	0.5
SY037 07-08	7	8	0.42	0.09	4	68	14.80%	3.89%	36	830	X	2.81%	13.9	20	0.4
SY037 08-09	8	9	0.64	0.13	5	197	17.20%	5.45%	52	1020	X	4.23%	16.6	40	0.2
SY037 09-10	9	10	0.49	0.06	X	68	8.45%	11.00%	10	530	X	12.40%	7.96	20	0.1
SY037 10-11	10	11	0.56	0.11	X	58	8.55%	10.50%	6	590	X	13.30%	9.49	10	0.1
SY037 11-12	11	12	0.4	0.15	X	46	7.37%	11.10%	6	510	X	15.90%	7.96	10	0.1

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY037 12-13	12	13	0.38	0.06	X	86	7.32%	2.28%	61	340	X	2.06%	8.11	30	0.1
SY037 13-14	13	14	0.22	0.04	X	86	6.32%	1.40%	76	260	X	7250	6.75	40	0.1
SY037 14-15	14	15	0.2	0.04	X	107	6.30%	1.07%	85	230	X	3310	6.43	40	X
SY038 00-01	0	1	0.06	0.07	X	15	2.47%	10.60%	7	150	X	900	1.5	20	X
SY038 01-02	1	2	0.38	0.13	3	32	2.78%	10.10%	8	130	X	1390	1.89	20	X
SY038 02-03	2	3	2.44	0.26	8	45	4.21%	11.00%	6	260	X	10.50%	4.9	10	0.1
SY038 03-04	3	4	2.36	0.33	9	70	7.88%	9.83%	9	470	X	7.02%	8.49	20	0.1
SY038 04-05	4	5	LNR	LNR	LNR	-	-	-	-	-	-	-	LNR	-	LNR
SY038 05-06	5	6	1.86	0.3	9	100	11.40%	8.28%	14	760	X	3.85%	12.4	30	0.2
SY038 06-07	6	7	1.16	0.14	6	84	8.66%	4.90%	17	550	X	1.19%	8.78	20	X
SY038 07-08	7	8	1.26	0.22	9	78	10.80%	1.91%	11	700	X	2610	12.4	20	0.1
SY038 08-09	8	9	0.3	0.22	9	74	26.70%	1.50%	19	1900	X	2970	30.6	40	X
SY038 09-10	9	10	0.47	0.1	8	88	14.20%	1.23%	66	1000	X	1680	15.4	40	X
SY038 10-11	10	11	0.57	0.13	8	99	9.64%	1.31%	74	580	X	1690	10.9	40	0.2
SY038 11-12	11	12	0.79	0.24	9	144	9.84%	1.65%	66	480	X	4210	10.2	40	0.2
SY038 12-13	12	13	0.32	0.1	6	121	5.17%	1.17%	82	170	X	2180	5.66	50	X
SY038 13-14	13	14	0.08	0.03	X	142	5.44%	1.27%	91	140	X	3220	5.86	50	X
SY038 14-15	14	15	0.11	0.03	X	124	5.43%	1.21%	92	150	X	2950	5.84	40	0.1
SY039 00-01	0	1	18.7	1.98	48	270	12.30%	7.17%	11	1090	X	500	21.8	250	0.4
SY039 01-02	1	2	12.5	0.63	17	319	13.00%	4.65%	7	1480	X	2430	19.9	110	0.4
SY039 02-03	2	3	5.12	0.21	7	184	12.90%	8290	5	1710	X	740	17.9	60	0.8
SY039 03-04	3	4	1.17	0.12	5	87	6.59%	1.55%	47	540	X	1140	7.38	50	0.3
SY039 04-05	4	5	2.92	0.22	8	169	11.40%	1.32%	46	1160	X	1400	14	70	0.6
SY039 05-06	5	6	0.48	0.1	5	88	5.39%	9260	80	210	X	1030	5.82	70	0.1
SY039 06-07	6	7	0.31	0.52	17	96	4.89%	8700	80	110	X	810	5.33	80	0.1
SY039 07-08	7	8	0.26	0.46	19	148	5.40%	8550	78	160	X	800	5.87	80	X
SY039 08-09	8	9	0.2	0.25	12	91	5.87%	8120	77	160	X	910	6.25	90	0.1
SY039 09-10	9	10	0.23	0.35	15	109	5.30%	8540	76	130	X	940	5.67	80	0.1
SY040 00-01	0	1	35.6	8.76	210	1020	6.61%	2380	X	170	X	910	23.4	340	0.8
SY040 01-02	1	2	35.8	8.9	200	963	5.44%	1320	X	60	X	1590	21.7	270	0.7
SY040 02-03	2	3	15.1	2.35	77	501	11.80%	2940	X	970	X	990	19.3	190	0.6
SY040 03-04	3	4	2.98	0.73	22	121	9.72%	7390	31	550	X	1330	11.5	100	0.3
SY040 04-05	4	5	0.63	0.29	9	88	7.65%	1.47%	56	420	X	1230	8.13	80	0.3
SY040 05-06	5	6	0.48	0.16	6	98	5.88%	1.39%	75	190	X	1270	6.21	70	0.2
SY040 06-07	6	7	0.17	0.06	3	91	5.61%	1.09%	80	160	X	1140	5.99	70	0.1
SY040 07-08	7	8	0.11	0.27	8	80	5.32%	8220	92	140	X	990	6.29	90	0.1
SY040 08-09	8	9	0.4	0.11	7	95	5.28%	8500	74	150	X	1240	6.32	80	0.1
SY040 09-10	9	10	0.31	0.16	7	127	4.47%	9070	80	100	X	1120	5.03	70	0.1
SY041 00-01	0	1	0.14	0.04	X	12	1.59%	15.60%	X	40	X	240	0.413	20	X
SY041 01-02	1	2	0.05	0.01	9	X	1.66%	15.00%	X	20	X	120	0.168	20	X
SY041 02-03	2	3	0.06	0.03	6	11	1.75%	18.00%	X	20	X	90	0.163	20	X
SY041 03-04	3	4	0.05	0.12	12	31	2.49%	17.70%	X	70	X	100	0.27	60	X
SY041 04-05	4	5	2.34	1.09	25	175	16.50%	9.89%	6	500	X	230	18.6	130	X
SY041 05-06	5	6	14.8	1.91	53	175	12.60%	7.51%	10	310	X	560	19.5	160	0.3
SY041 06-07	6	7	11.6	2.45	44	206	15.40%	7.65%	21	490	X	1940	22.6	110	0.3
SY041 07-08	7	8	8.77	2.36	44	172	12.10%	8.63%	8	300	X	3790	15.1	110	0.2

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY041 08-09	8	9	12.4	3.77	58	501	24.80%	1.82%	23	300 X		1590	35	70	0.2
SY041 09-10	9	10	15	4.59	59	505	18.90%	3.92%	16	200 X		1920	26.3	80	0.2
SY041 10-11	10	11	28.5	4.25	74	216	10.20%	4.82%	5	110 X		3710	20.9	90	0.4
SY041 11-12	11	12	7.69	1.3	21	81	6.11%	12.00%	X	60 X		3880	7.22	40 X	
SY041 12-13	12	13	9.27	1.35	27	108	9.80%	8.35%	9	130 X		3110	12.5	60	0.1
SY041 13-14	13	14	3.52	0.86	14	95	7.91%	13.50%	7	160 X		2480	7.42	50	0.1
SY041 14-15	14	15	3.86	0.46	8	114	8.30%	13.40%	8	130 X		6440	6.53	40 X	
SY041 15-16	15	16	8.78	0.73	17	442	27.20%	2.64%	10	90 X		4540	24.6	40	0.1
SY041 16-17	16	17	21.5	0.6	22	363	25.50%	7600	20	240 X		1620	32.1	160	0.3
SY041 17-18	17	18	21.4	1.31	32	481	22.80%	9760	13	120 X		1790	30.3	130	0.2
SY041 18-19	18	19	10.8	1.09	20	438	14.70%	6.62%	11	150 X		4970	16.7	70	0.1
SY041 19-20	19	20	6.02	0.45	11	203	10.50%	9.09%	12	140 X		1.08%	10.2	50	0.1
SY041 20-21	20	21	6.83	0.7	16	210	11.30%	4.01%	38	200 X		6550	13.2	80	0.2
SY041 21-22	21	22	1.35	0.18	5	80	7.25%	5.11%	59	110 X		1.35%	5.15	40	0.1
SY041 22-23	22	23	0.58	0.1 X		133	5.62%	2.93%	63	90 X		1.37%	4.05	30	0.1
SY041 23-24	23	24	1.03	0.21	5	91	5.87%	2.10%	61	120 X		7650	5.15	40	0.2
SY042 00-01	0	1	0.16	0.08	5	25	1.11%	3.92%	X	60 X		290	0.618	20 X	
SY042 01-02	1	2	0.26	0.09	27	15	7900	9010 X		20 X		230	0.623	20 X	
SY042 02-03	2	3	1.47	2.01	44	79	4.76%	9.96%	13	120 X		1340	4.22	190	0.2
SY042 03-04	3	4	1.08	1.62	25	89	7.68%	8.77%	11	110 X		6840	4.39	100 X	
SY042 04-05	4	5	0.87	0.32	6	49	4.30%	15.60%	X	110 X		6130	2.74	30 X	
SY042 05-06	5	6	3.56	3.35	42	360	24.20%	5.72%	13	390 X		590	25.8	80	0.1
SY042 06-07	6	7	0.55	0.45	7	144	9.19%	13.10%	8	150 X		1790	6.24	50 X	
SY042 07-08	7	8	0.87	0.26	6	239	12.10%	11.50%	14	450 X		2550	12.6	50 X	
SY042 08-09	8	9	2.23	0.9	21	423	21.40%	3.15%	45	290 X		1040	24.5	50	0.2
SY042 09-10	9	10	2.49	3.67	46	693	32.10%	1.83%	49	400 X		950	36.7	50	0.1
SY042 10-11	10	11	0.52	0.87	11	117	8.52%	9.18%	5	260 X		2860	3.6	60 X	
SY042 11-12	11	12	0.14	0.15 X		21	7.34%	9.89%	8	330 X		3980	1.13	40 X	
SY042 12-13	12	13	3.15	0.88	10	73	7.10%	10.90%	6	100 X		3.37%	5.46	40 X	
SY042 13-14	13	14	18.7	2.34	38	564	15.00%	3.69%	27	150 X		2540	21.8	110	0.2
SY042 14-15	14	15	1.34	1.51	14	52	7.45%	11.90%	9	210 X		5840	2.62	70 X	
SY042 15-16	15	16	6.57	0.86	11	218	4.93%	6.72%	31	190 X		1400	6.71	90 X	
SY042 16-17	16	17	9.3	3.8	34	274	16.20%	3.27%	12	160 X		2210	17.7	60 X	
SY042 17-18	17	18	8.54	0.74	12	431	22.80%	2460	10	80 X		2470	21.1	30	0.1
SY042 18-19	18	19	5.97	0.43	9	292	12.60%	3510	11	60 X		2000	13	40 X	
SY042 19-20	19	20	LNR	LNR	LNR	-	-	-	-	-	-	-	LNR	-	LNR
SY042 20-21	20	21	4.21	0.75	10	191	13.00%	4.40%	36	150 X		1.97%	11.7	40	0.1
SY042 21-22	21	22	12.3	1.43	21	477	26.20%	3870	10	90 X		2150	26.3	40	0.1
SY042 22-23	22	23	0.99	0.64	6	98	6.86%	7.29%	35	120 X		1.21%	5.02	40 X	
SY042 23-24	23	24	0.64	0.61	6	99	6.76%	2.54%	70	90 X		8520	5.58	60 X	
SY042 24-25	24	25	0.51	0.17	4	78	5.54%	1.58%	65	90 X		7550	4.81	40	0.1

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY043 00-01	0	1	0.37	0.2	5	84	3.86%	2.02%	41	100 X		4990	2.65	40	
SY043 01-02	1	2	0.31	0.2	4	55	3.23%	1.25%	43	90 X		4300	2.52	20	
SY043 02-03	2	3	0.06	0.05 X		56	2.81%	1.17%	93	20 X		780	0.53 X		
SY043 03-04	3	4 X		X	X	75	5800	4400	9 X		X	210	0.16	10	
SY043 04-05	4	5	0.05	0.05 X		80	1.81%	4900	39	30 X		170	1.63	30	
SY043 05-06	5	6	0.03	0.04 X		36	6800	2680	18 X		X	160	0.37 X		
SY043 06-07	6	7	0.04	0.05 X		51	1.34%	4760	34	50 X		1190	1.03	20	
SY043 07-08	7	8 X		0.05 X		114	1.60%	4240	16	40 X		220	1.47	10	
SY043 08-09	8	9	0.04	0.09 X		81	1.21%	4850	24	30 X		360	0.89	10	
SY043 09-10	9	10 X		0.04 X		99	1.47%	3350	17	50 X		130	1.48	10	
SY043 10-11	10	11	0.02	1.42 X		61	1.10%	4200	12	20 X		250	0.92 X		
SY043 11-12	11	12	0.02	0.05 X		49	1.53%	7030	24	40 X		180	1.36 X		
SY043 12-13	12	13	0.06	0.02 X		25	5.41%	3.29%	47	60 X		250	>5.00	10	
SY043 13-14		14	0.04	0.03 X		33	3.42%	1.60%	42	50 X		300	3.08 X		
SY043 14-15	14	15 X		0.03 X		18	2.09%	9260	25	40 X		180	1.87	10	
SY043 15-16	15	16	0.02	0.02 X		23	2.23%	1.06%	28	50 X		550	1.95	10	
SY043 16-17	16	17	0.02	0.31 X		33	3.63%	1.31%	50	60 X		620	3.57	10	
SY043 17-18	17	18	0.03	0.54	3	13	1.69%	1.06%	20	40 X		650	1.39 X		
SY043 18-19	18	19	0.02	0.22 X		22	2.32%	1.21%	23	60 X		670	1.77	20	
SY043 19-20	19	20	0.02	0.22 X		19	1.90%	1.08%	26	50 X		530	1.39 X		
SY043 20-21	20	21	0.02	0.36 X		14	2.12%	1.26%	18	30 X		580	1.14 X		
SY043 21-22	21	22	0.03	0.14 X		16	1.74%	1.33%	17	30 X		1100	0.90 X		
SY043 22-23	22	23	0.12	0.1 X		16	2.02%	2.04%	24	50 X		3250	1.17 X		
SY043 23-24	23	24	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	LNR	
SY043 24-25	24	25	0.1	0.09 X		22	2.31%	3.00%	29	50 X		2850	1.31	10	

Comstock Drill Hole Assays, August 2005

ID Drill hole	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
SY044 00-01	0	1	0.09	0.01	4	123	8.98%	2.26%	104	20	X	570	0.18	X	
SY044 01-02	1	2	0.28	X	4	187	8.01%	2.49%	175	20	X	1630	0.31	X	
SY044 02-03	2	3	0.27	X	X	149	9.79%	3.88%	180	20	X	2260	0.22	X	
SY044 03-04	3	4	0.15	X	X	163	10.40%	4.43%	147	10	X	2420	0.17	X	
SY044 04-05	4	5	0.18	X	3	158	11.50%	5.01%	134	20	X	2040	0.25	X	
SY044 05-06	5	6	0.22	X	3	155	10.40%	3.54%	157	30	X	2400	0.49	X	
SY044 06-07	6	7	0.1	X	3	162	11.40%	4.17%	100	X	X	1920	0.13	X	
SY044 07-08	7	8	0.11	X	X	181	11.00%	3.69%	101	10	X	2200	0.18	X	
SY044 08-09	8	9	0.11	X	X	163	11.40%	4.23%	98	X	X	1620	0.12	X	
SY044 09-10	9	10	0.18	X	X	127	9.45%	3.46%	73	10	X	1150	0.38	X	
SY044 10-11	10	11	0.7	0.04	X	151	11.40%	4.26%	132	70	X	1550	2.84	X	
SY044 11-12	11	12	0.79	X	X	150	10.30%	4.39%	130	70	X	1720	1.88	X	
SY044 12-13	12	13	0.56	0.02	3	143	9.41%	3.47%	158	60	X	1910	3.18	10	
SY044 13-14	13	14	0.67	0.01	X	141	10.60%	3.99%	196	60	X	1880	3.37	10	
SY044 14-15	14	15	0.56	X	X	135	10.60%	4.31%	221	50	X	1490	1.87	X	
SY044 15-16	15	16	0.11	X	X	125	9.23%	5.10%	87	10	X	1990	0.25	X	
SY044 16-17	16	17	0.14	X	X	127	10.40%	5.34%	106	40	X	1870	1.32	X	
SY044 17-18	17	18	0.22	X	X	161	11.60%	5.44%	166	80	X	2020	2.64	20	
SY044 18-19	18	19	0.28	X	X	121	9.36%	5.22%	145	40	X	1690	1.04	X	
SY044 19-20	19	20	0.12	X	X	87	8.81%	5.17%	104	40	X	1430	1.36	X	
SY044 20-21	20	21	0.31	X	X	131	9.34%	5.01%	142	50	X	1520	1.18	10	
SY044 21-22	21	22	0.17	0.01	X	84	7.43%	4.52%	252	110	X	1260	1.91	20	
SY044 22-23	22	23	0.45	0.03	X	74	5.63%	2.33%	96	70	X	1550	2.70	20	
SY044 23-24	23	24	0.85	0.11	4	106	5.11%	2.00%	66	50	X	1280	2.63	20	
SY044 24-25	24	25	0.2	0.13	X	84	2.70%	1.50%	31	40	X	1550	1.19	X	
SY044 25-26	25	26	0.39	0.21	4	96	3.00%	1.23%	28	30	X	1580	2.09	10	
SY044 26-27	26	27	0.42	0.09	X	113	7.07%	2.75%	101	80	X	1710	3.07	X	

Oceana Drill Hole Assays
August 2005

Sample Units	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
ZZE1 0-1	0	1	0.9	2.94	77	139	1.00%	4230	120	260	X	280	1.77	100	3.3
ZZE1 1-2	1	2	1.25	2.86	15	64	9300	5340	133	30	X	190	2.34	230	2.6
ZZE1 2-3	2	3	4.09	3.69	6	44	3.84%	5540	719	90	X	320	7.17	150	1.6
ZZE1 3-4	3	4	3.51	3.31	6	83	2.48%	5470	428	60	X	220	5.41	150	1.3
ZZE1 4-5	4	5	2.54	3.47	3	58	3.09%	7610	458	50	X	560	5.02	170	0.9
ZZE1 5-6	5	6	2.38	3.16	3	41	2.57%	6300	373	50	X	290	4.93	140	0.9
ZZE1 6-7	6	7	0.92	1.77	X	65	1.67%	6870	218	30	X	480	2.63	100	0.7
ZZE1 7-8	7	8	0.71	1.38	3	64	1.45%	6640	212	30	X	440	2.42	100	0.6
ZZE1 8-9	8	9	1.56	1.61	X	89	5.76%	2.30%	381	70	X	1070	3.66	70	0.8
ZZE1 9-10	9	10	0.83	1.53	X	53	2.43%	9510	327	40	X	510	2.77	90	0.6
ZZE1 10-11	10	11	0.86	1.35	X	47	2.31%	9410	305	40	X	840	3.00	80	0.6
ZZE1 11-12	11	12	0.6	0.86	X	32	2.41%	7620	249	40	X	590	3.04	60	0.5
ZZE1 12-13	12	13	0.39	0.46	X	30	3.29%	9910	195	50	X	1010	3.56	40	0.4
ZZE1 13-14	13	14	0.28	0.31	X	23	2.99%	7890	155	30	X	590	3.35	30	0.4
ZZE1 14-15	14	15	0.24	0.44	4	33	2.51%	8070	120	20	X	1290	2.73	40	0.5
ZZE1 15-16	15	16	0.4	0.56	X	39	2.88%	1.18%	150	40	X	1780	2.33	40	0.5
ZZE1 16-17	16	17	0.03	0.03	X	8	3.33%	2.10%	29	X	X	15.30%	1.10	X	0.2
ZZE1 17-18	17	18	0.03	0.02	X	6	2.59%	2.03%	21	X	X	19.60%	0.81	X	0.2
ZZE1 18-19	18	19	0.22	0.32	X	15	2.50%	2.50%	55	20	X	14.40%	1.45	30	0.2
ZZE1 19-20	19	20	0.02	0.02	X	7	2.31%	2.01%	17	X	X	21.50%	0.83	X	0.2
ZZE1 20-21	20	21	0.04	0.03	X	6	2.70%	3.26%	21	X	X	17.40%	1.14	10	0.2
ZZE1 21-22	21	22	0.03	0.02	X	5	3.21%	2.52%	17	X	X	19.90%	0.86	X	0.2
ZZE1 22-23	22	23	0.02	0.01	X	X	2.61%	2.33%	15	X	X	21.90%	0.81	X	0.2
ZZE1 23-24	23	24	0.02	X	X	5	3.02%	2.44%	19	X	X	20.00%	1.28	X	0.2
ZZE1 24-25	24	25	0.03	0.02	X	6	2.50%	1.73%	23	X	X	20.60%	1.48	X	0.2
ZZE1 25-26	25	26	0.03	0.01	X	7	3.04%	2.32%	21	X	X	20.50%	1.32	X	0.2
ZZE1 26-27	26	27	0.05	0.02	X	13	5.55%	2.37%	29	X	X	11.90%	1.79	10	0.2
ZZE1 27-28	27	28	0.07	0.12	X	14	5.46%	3.96%	41	20	X	9.16%	1.89	20	0.3
ZZE1 28-29	28	29	0.03	0.03	X	13	4.64%	4.55%	28	10	X	8.78%	1.96	20	0.2
ZZE1 29-30	29	30	0.08	0.05	X	23	4.13%	4.03%	30	20	X	8.29%	1.71	20	0.2
ZZE1 30-31	30	31	0.06	0.05	X	21	5.70%	3.22%	32	20	X	5.93%	2.15	20	0.2
ZZE1 31-32	31	32	0.19	0.12	X	25	6.85%	2.44%	56	60	X	3.98%	3.93	60	0.4
ZZE1 32-33	32	33	0.06	0.05	X	15	4.14%	4.25%	33	20	X	7.95%	1.87	30	0.2
ZZE1 33-34	33	34	0.07	0.06	X	14	4.22%	5.22%	33	10	X	10.10%	2.05	20	0.2
ZZE1 34-35	34	35	0.21	0.17	X	14	4.78%	4.80%	34	20	X	9.67%	2.45	20	0.3
ZZE1 35-36	35	36	0.02	0.04	X	7	4.59%	4.17%	18	X	X	15.20%	1.36	20	0.2
ZZE1 36-37	36	37	0.02	0.02	X	8	3.80%	4.56%	21	X	X	13.60%	1.29	20	0.2
ZZE1 37-38	37	38	0.02	0.03	X	7	3.48%	2.67%	19	10	X	18.20%	1.19	20	0.2
ZZE1 38-39	38	39	0.01	0.03	X	X	3.64%	1.33%	13	X	X	24.10%	0.83	X	0.1
ZZE1 39-40	39	40	0.05	0.04	X	10	5.41%	1.48%	28	10	X	18.70%	1.57	20	0.2
ZZE1 40-41	40	41	0.04	0.04	X	9	3.38%	2.60%	31	10	X	15.80%	1.63	20	0.2
ZZE1 41-42	41	42	0.03	0.03	X	8	4.53%	2.72%	19	X	X	18.50%	1.27	10	0.1
ZZE1 42-43	42	43	0.06	0.06	X	10	3.13%	2.37%	23	10	X	20.00%	1.33	20	0.2
ZZE1 43-44	43	44	0.08	0.04	X	8	2.32%	2.70%	22	X	X	20.00%	1.14	10	0.2

Oceana Drill Hole Assays
August 2005

Sample Units	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
ZZE2 0-1	0	1	X	0.02	X	X	4600	1610	12	X	X	670	0.02	10	0.1
ZZE2 1-2	1	2	X	0.02	X	X	5000	1460	12	X	X	410	0.02	10	0.2
ZZE2 2-3	2	3	1.33	0.17	X	10	13.40%	1580	45	X	X	4510	0.42	X	0.4
ZZE2 3-4	3	4	2.7	0.31	X	9	19.20%	1750	78	10	X	7280	1.03	X	0.5
ZZE2 4-5	4	5	1.86	0.28	X	12	11.90%	1850	63	X	X	4270	0.87	X	0.5
ZZE2 5-6	5	6	3.05	0.58	X	20	16.30%	2360	96	20	X	6000	1.72	20	0.8
ZZE2 6-7	6	7	2.31	0.38	X	16	14.70%	2550	78	20	X	5690	1.17	X	0.7
ZZE2 7-8	7	8	2.97	0.68	X	16	17.80%	2040	81	10	X	7540	1.45	X	1.1
ZZE2 8-9	8	9	2.5	0.72	X	13	18.00%	1770	61	X	X	6910	0.95	X	1
ZZE2 9-10	9	10	2.51	1.38	X	11	18.50%	2070	57	10	X	7590	0.95	10	1.3
ZZE2 10-11	10	11	2.45	1.99	X	16	16.40%	1750	53	10	X	7930	1.01	10	1.6
ZZE2 11-12	11	12	1.96	5.17	X	20	12.90%	2800	51	20	X	5290	1.90	40	2.9
ZZE2 12-13	12	13	2.16	18.5	X	25	8.98%	2910	56	20	X	2510	4.43	90	6.6
ZZE2 13-14	13	14	1.74	11.3		29	7.28%	2720	43	20	X	2390	3.13	80	4.8
ZZE2 14-15	14	15	1.43	9.43	4	26	6.47%	2360	43	10	X	2270	2.45	60	4
ZZE2 15-16	15	16	0.83	7.19	22	37	3.04%	2640	26	X	X	1100	1.72	50	3.4
ZZE2 16-17	16	17	1.38	4.39	10	36	1.50%	1280	19	X	X	490	1.55	60	2.9
ZZE2 17-18	17	18	0.31	4.78	9	37	9100	1100	20	X	X	310	1.13	70	1.5
ZZE2 18-19	18	19	0.21	2.64	5	20	8000	670	16	X	X	370	0.64	40	1.1
ZZE2 19-20	19	20	1.65	2.81	7	34	4900	600	13	X	X	150	1.31	60	2.6
ZZE2 20-21	20	21	1.48	4.12	10	39	6800	880	16	X	X	200	1.42	50	2.8
ZZE2 21-22	21	22	0.4	3.6	6	29	5400	820	15	X	X	150	0.82	50	1.1
ZZE2 22-23	22	23	0.26	5.01	8	30	1.10%	1090	18	X	X	410	0.95	50	1.3
ZZE2 23-24	23	24	0.27	2.01	5	22	1.52%	880	18	X	X	450	0.40	30	1
ZZE2 24-25	24	25	0.74	3.62	16	69	14.60%	740	24	X	X	870	0.52	50	2.6
ZZE2 25-26	25	26	0.99	11.1	27	93	28.70%	740	29	20	X	580	0.43	140	3.3
ZZE2 26-27	26	27	1.14	17.5	74	152	34.70%	320	31	20	X	240	0.20	140	7.2
ZZE2 27-28	27	28	1.67	8.05	39	114	23.60%	940	28	20	X	560	0.84	160	6.1
ZZE2 28-29	28	29	2.36	7.18	21	74	12.70%	1630	34	10	X	2370	1.71	90	4.6
ZZE2 29-30	29	30	1.43	9.24	19	63	7.33%	1680	34	20	X	2150	1.03	60	3.3
ZZE2 30-31	30	31	1.9	10.3	21	83	10.10%	1440	36	10	X	2830	1.13	70	5.1
ZZE2 31-32	31	32	1.48	10.1	58	68	19.80%	1380	20	X	X	1510	0.39	X	10.4
ZZE2 32-33	32	33	1.66	8.97	31	138	35.00%	860	35	30	X	390	0.41	200	5.9
ZZE2 33-34	33	34	1.34	3.93	23	115	47.60%	390	30	30	X	80	0.10	170	4.2
ZZE2 34-35	34	35	1.08	6.01	22	101	43.30%	510	28	20	X	210	0.18	200	3.9
ZZE2 35-36	35	36	0.89	3.92	14	60	45.00%	420	24	20	X	170	0.15	160	2.4
ZZE2 36-37	36	37	0.9	5.66	21	58	44.90%	470	24	20	X	110	0.14	140	3.1
ZZE2 37-38	37	38	1.21	7.77	19	47	39.60%	630	28	20	X	170	0.17	100	2.5
ZZE2 38-39	38	39	0.91	12.1	15	39	24.30%	1820	31	20	X	370	0.20	80	1.9
ZZE2 39-40	39	40	1.02	11.4	17	37	20.80%	2350	33	20	X	530	0.32	50	2.8
ZZE3 00-01	0	1	0.19	3.03	9	21	3.80%	6210	10	20	X	1100	0.152	20	0.8
ZZE3 01-02	1	2	0.12	0.75	3	24	1.24%	6440	6	100	X	970	0.23	20	0.4
ZZE3 02-03	2	3	0.05	0.51	5	31	6700	6620	11	10	X	510	0.535	20	0.6
ZZE3 03-04	3	4	0.37	0.71	4	30	7600	5840	20	10	X	380	0.847	40	0.6
ZZE3 04-05	4	5	0.27	0.88	5	23	8900	5610	17	10	X	940	0.601	30	0.7
ZZE3 05-06	5	6	0.25	0.56	4	23	5600	5850	20	X	X	820	0.599	30	0.7

Oceana Drill Hole Assays
August 2005

Sample Units	from (metres)	to (metres)	Zn %	Pb %	Ag PPM	Cu PPM	Fe PPM	Mg PPM	Ni PPM	As PPM	Bi PPM	Ca PPM	S %	Sb PPM	Hg PPM
ZZE3 06-07	6	7	0.38	0.71	4	26	8400	5330	38	X	X	670	0.834	30	0.9
ZZE3 07-08	7	8	0.54	0.48	X	29	9800	6570	59	20	X	920	1.47	30	0.9
ZZE3 08-09	8	9	0.64	0.37	3	20	9100	4270	51	20	X	1060	1.34	20	0.8
ZZE3 09-10	9	10	0.2	0.19	X	9	5500	6190	16	X	X	850	0.305	10	0.3
ZZE3 10-11	10	11	0.4	0.1	X	24	8500	8210	39	20	X	280	0.794	X	0.2
ZZE3 11-12	11	12	0.47	0.4	X	25	2.21%	8020	76	20	X	920	1.94	20	0.4
ZZE3 12-13	12	13	0.38	0.15	X	25	2.55%	7360	130	40	X	1920	2.88	30	0.3
ZZE3 13-14	13	14	0.29	0.59	X	24	1.88%	7300	94	30	X	2150	1.82	20	0.5
ZZE3 14-15	14	15	0.23	0.34	X	30	2.36%	2.52%	43	20	X	6.77%	1.42	20	0.3
ZZE3 15-16	15	16	0.23	0.06	X	17	1.63%	1.39%	60	20	X	4.86%	1.48	10	0.2