

Hole No./Depth	Sn	W	Lab	Resampling Designation	Laboratory WBH Mittersill						Difference external Lab - Lab. Mittersill				
					WO3, ppm	Multielement		Bpress	Epress	WO3, ppm	WO3, ppm	WO3, ppm	WO3, ppm	WO3, ppm	WO3, ppm
						WO3, ppm	Sn, %	WO3, %							
ABRC001 18-19	17200	160	ALS	ABRC CHECK 01	202	240		0.016			160	38	-42		-42
ABRC001 51-52	247	200	ALS	ABRC CHECK 02	252	372		0.025			250	120	-2		-2
ABRC001 52-53	174	100	ALS	ABRC CHECK 03	126	150		0.011			110	24	-16		-16
ABRC001 53-54	307	150	ALS	ABRC CHECK 04	189	130		0.008			80	-59	-109		-109
ABRC001 55-56	8110	60	ALS	ABRC CHECK 05	76	64		0.021			210	-12	134		134
ABRC001 70-71	2610	370	ALS	ABRC CHECK 06	466	548		0.047			470	82	4		4
ABRC001 71-72	2570	160	ALS	ABRC CHECK 07	202	326		0.025			250	124	48		48
ABRC001 86-87	128	750	ALS	ABRC CHECK 08	945	1,550			1,550	1,550	605			605	605
ABRC001 106-107	87	280	ALS	ABRC CHECK 09	353	494		0.039		1,550	390	141	37		37
ABRC001 115-116	60	150	ALS	ABRC CHECK 10	189	250		0.016			160	61	-29		-29
ABRC002 47-48	9650	100	ALS	ABRC CHECK 11	126	120		0.014			140	-6	14		14
ABRC002 48-49	2430	90	ALS	ABRC CHECK 12	113	140		0.014			140	27	27		27
ABRC002 70-71	406	40	ALS	ABRC CHECK 13	50	24		0.010			100	-26	50		50
ABRC002 71-72	4060	620	ALS	ABRC CHECK 14	781	1,390			1,290	1,290	609			509	509
ABRC002 72-73	2120	550	ALS	ABRC CHECK 15	693	802		0.060			600	109	-93		-93
ABRC003 66-67	27900	30	ALS	ABRC CHECK 16	38	120		0.008			80	82	42		42
ABRC003 74-75	229	470	ALS	ABRC CHECK 17	592	426		0.033			330	-166	-262		-262
ABRC003 90-91	889	270	ALS	ABRC CHECK 18	340	413		0.032			320	73	-20		-20
ABRC003 99-100	625	170	ALS	ABRC CHECK 19	214	231		0.025			250	17	36		36
ABRC003 121-122	371	300	ALS	ABRC CHECK 20	378	404		0.031			310	26	-68		-68
ABRC003 122-123	148	140	ALS	ABRC CHECK 21	176	260		0.020			200	84	24		24
ABRC003 123-124	349	220	ALS	ABRC CHECK 22	277	190		0.026			260	-87	-17		-17
ABRC004 41-42	3860	170	ALS	ABRC CHECK 23	214	190		0.016			160	-24	-54		-54
ABRC005 52-53	210	910	ALS	ABRC CHECK 24	1,147	2,000			1,690	1,690	853			543	543
ABRC005 53-54	94	100	ALS	ABRC CHECK 25	126	140		0.011			110	14	-16		-16
ABRC005 70-71	538	150	ALS	ABRC CHECK 26	189	160		0.017			170	-29	-19		-19
ABRC005 90-91	27100	60	ALS	ABRC CHECK 27	76	97		0.008			80	21	4		4
ABRC005 96-97	2050	140	ALS	ABRC CHECK 28	176	140		0.013			130	-36	-46		-46
ABRC005 97-98	1120	110	ALS	ABRC CHECK 29	139	120		0.010			100	-19	-39		-39
ABRC005 104-105	4450	40	ALS	ABRC CHECK 30	50	0		0.009			90	-50	40		40
ABRC005 115-116	473	110	ALS	ABRC CHECK 31	139	0		0.047			470	-139	331		331
ABRC005 116-117	241	30	ALS	ABRC CHECK 32	38	0		0.004			40	-38	2		2
ABRC005 117-118	957	150	ALS	ABRC CHECK 33	189	230		0.020			200	41	11		11
ABRC005 118-119	642	100	ALS	ABRC CHECK 34	126	130		0.011			110	4	-16		-16
ABRC005 119-120	3510	60	ALS	ABRC CHECK 35	76	0		0.011			110	-76	34		34
ABRC005 119-120D	3170	60	ALS	ABRC CHECK 36	76	78		0.011			110	2	34		34
ABRC005 120-121	21000	50	BURNIE	ABRC CHECK 37	63	18		0.004			40	-45	-23		-23
ABRC006A 20-21	180	520	BURNIE	ABRC CHECK 38	655	24		0.018			180	-631	-475		-475
ABRC006A 53-54	220	640	BURNIE	ABRC CHECK 39	806	170		0.011			110	-636	-696		-696
ABRC006A 74-75	480	2010	BURNIE	ABRC CHECK 40	2,533	1,800			1,570	1,570	-733			-963	-963
ABRC007 11-12	330	500	BURNIE	ABRC CHECK 41	630	1,750			1,760	1,760	1,120			1,130	1,130
ABRC007 12-13	2490	560	BURNIE	ABRC CHECK 42	706	120		0.008			80	-586	-626		-626
ABRC007 36-37	210	570	BURNIE	ABRC CHECK 43	718	489		0.034			340	-229	-378		-378
ABRC007 43-44	40	540	BURNIE	ABRC CHECK 44	680	0		0.002			20	-680	-660		-660
ABRC009 58-59	210	600	BURNIE	ABRC CHECK 45	756	186		0.015			150	-570	-606		-606
ABRC009 62-63	520	2350	BURNIE	ABRC CHECK 46	2,961	1,530			1,360	1,360	-1,431			-1,601	-1,601
ABRC009 63-64	1110	2040	BURNIE	ABRC CHECK 47	2,570	230		0.014			140	-2,340	-2,430		-5,001
ABRC009 64-65	5980	560	BURNIE	ABRC CHECK 48	706	238		0.026			260	-468	-446		-446
ABRC009 65-66	710	700	BURNIE	ABRC CHECK 49	882	344		0.033			330	-538	-552		-552
ABRC009 66-67	780	1380	BURNIE	ABRC CHECK 50	1,739	no sample					0				0
ABRC009 73-74	7360	350	BURNIE	ABRC CHECK 51	441	120		0.006			60	-321	-381		-381
ABRC009 80-81	3110	560	BURNIE	ABRC CHECK 52	706	no sample					0				0
ABRC009 81-82	480	330	BURNIE	ABRC CHECK 53	416	46		0.005			50	-370	-366		-366
ABRC009 82-83	520	620	BURNIE	ABRC CHECK 54	781	200		0.018			180	-581	-601		-601
ABRC010 36-37	25680	290	BURNIE	ABRC CHECK 55	365	0		0.012			120	-365	-245		-245
ABRC010 56-57	13830	340	BURNIE	ABRC CHECK 56	428	11		0.016			160	-417	-268		-268
ABRC010 57-58	450	270	BURNIE	ABRC CHECK 57	340	0		0.008			80	-340	-260		-260
ABRC010 58-59	5360	250	BURNIE	ABRC CHECK 58	315	0		0.004			40	-315	-275		-275

ABRC011 36-37	690	970	BURNIE	ABRC CHECK 59	1,222	762	0.062	620	-460	-602	-602
ABRC011 47-48	2230	320	BURNIE	ABRC CHECK 60	403	0	0.008	80	-403	-323	-323
ABRC011 105-106	20	240	BURNIE	ABRC CHECK 61	302	0	0.002	20	-302	-282	-282
ABRC011 106-107	20	3000	BURNIE	ABRC CHECK 62	3,780	0	0.015	150	-3,780	-3,630	-3,630
ABRC011 107-108	30	330	BURNIE	ABRC CHECK 63	416	130	0.012	120	-286	-296	-296
ABRC011 111-112	3600	280	BURNIE	ABRC CHECK 64	353	130	0.004	40	-223	-313	-313
ABRC012 54-55	770	1920	BURNIE	ABRC CHECK 65	2,419	2,330		1,910	1,910	-69	-509
ABRC012 59-60	730	3280	BURNIE	ABRC CHECK 66	4,133	1,990		1,700	1,700	-2,143	-2,433
ABRC012 59-60D	720	3650	BURNIE	ABRC CHECK 67	4,599	2,490		2,120	2,120	-2,109	-2,479
ABRC012 70-71	11150	330	BURNIE	ABRC CHECK 68	416	100	0.007	70	-316	-346	-346
ABRC012 77-78	3250	350	BURNIE	ABRC CHECK 69	441	42	0.017	170	-399	-271	-271
ABRC012 81-82	3450	560	BURNIE	ABRC CHECK 70	706	231	0.019	190	-475	-516	-516
ABRC012 95-96	2980	290	BURNIE	ABRC CHECK 71	365	0	0.016	160	-365	-205	-205
ABRC012 101-102	3780	250	BURNIE	ABRC CHECK 72	315	0	0.002	20	-315	-295	-295