



Burnie RESEARCH LABORATORY

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

A Division of AMMTEC Ltd
ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

ANALYSIS REPORT FOR STELLAR RESOURCES

REPORT NO / NAME	SBR (2)
REPORT DATE	19 th December 2007
FROM	SBR 51
TO	SBR 68
METHOD CODES AND DETECTION LIMITS	AAS-1 Zn, Ni 1ppm FA-1 Au 0.01ppm CS-1 S 0.01%
CHIEF CHEMIST	RICKY GELSTON
SIGNATURE	 _____



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd
ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Zn	Ni	Au	S
	ppm	ppm	ppm	%
SBR 51	55	1509	<0.01	0.50
SBR 52	60	1734	<0.01	0.45
SBR 53	52	1754	<0.01	0.46
SBR 54	67	2334	<0.01	0.47
SBR 55	57	2112	<0.01	0.47
SBR 56	76	585	<0.01	0.59
SBR 57	48	1210	<0.01	0.45
SBR 58	49	780	<0.01	0.60
SBR 59	44	2445	<0.01	0.45
SBR 60	44	2201	<0.01	0.46
SBR 61	38	2098	<0.01	0.44
SBR 62	38	2262	<0.01	0.49
SBR 63	34	2244	<0.01	0.51
SBR 64	46	2604	<0.01	0.46
SBR 65	40	1828	<0.01	0.44
SBR 66	151	104	<0.01	0.45
SBR 67	114	90	<0.01	0.45
SBR 68	34	1901	<0.01	0.45

Duplicates

Sample	Zn	Ni	Au	S
	ppm	ppm	ppm	%
SBR 58	52	768	n/a	n/a
SBR 61	n/a	n/a	<0.01	n/a