

ANALYSIS REPORT FOR STELLAR RESOURCES

REPORT NO / NAME	SIR
REPORT DATE	19 th December 2007
FROM	SIR-1
TO	SIR-9
METHOD CODES AND DETECTION LIMITS	AAS-1 Ni 1ppm Fe 0.01% FA-1 Au 0.01ppm
CHIEF CHEMIST	RICKY GELSTON
SIGNATURE	 _____



Burnie RESEARCH LABORATORY

A Division of AMMTEC Ltd
ABN: 40 396 637 856

*Hydrometallurgy Consultants &
Flotation Technology Specialists*

39 River Road, Wivenhoe, PO Box 952, Burnie, TAS 7320 Tel: 61 3 6431 6333 Fax: 61 3 6431 6896

Sample	Fe	Ni	Au
	%	ppm	ppm
SIR-1	42.0	503	<0.01
SIR-2	41.9	827	0.05
SIR-3	39.4	942	<0.01
SIR-4	50.2	306	<0.01
SIR-5	38.2	500	<0.01
SIR-6	42.3	3748	<0.01
SIR-7	39.5	1550	<0.01
SIR-8	42.9	2985	<0.01
SIR-9	30.4	2366	<0.01

Duplicates

Sample	Fe	Ni	Au
	%	ppm	ppm
SIR-9	30.50	2345	n/a