

DIAMOND DRILL HOLE MS2
ASSAY RESULTS

ELEMENTS	Au	Ag	As	Ba	Bi	Co	Cr	Cu	Fe	Mn
UNITS	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm
DETECTION	0.01	0.2	2	0.1	0.01	0.1	5	1	0.01	1
METHOD	FA50/AAS	A/MS	A/MS	A/MS	A/MS	A/MS	A/OES	A/OES	A/OES	A/OES
COMMENTS:	134.3/0812054 (14/10/2008) CLIENT O/N: 4500769831 1/1									

SAMPLE NUMBERS										
379457	X	X	20	197.1	0.15	14	14	11	1.94	88
379458	X	X	16	312	0.12	8.5	12	14	2.08	114
379459	X	X	3	357.3	0.07	4.7	X	6	0.56	52
379460	X	0.3	39	574.7	0.45	19.5	101	97	4.95	458
379461	X	X	910	40.3	0.04	7.1	51	37	21.15	651
379462	X	X	26	370.8	0.08	31.8	312	47	5.21	1367
379463	X	0.4	41	279.8	0.38	18.8	98	82	6.67	691
379464	X	0.7	14	242.2	0.3	6.5	19	117	1.76	342
379465	X	X	10	399.2	0.06	16.3	51	40	2.82	942
379466	X	0.3	14	402.7	0.05	17.1	24	124	1.23	704
379467	X	X	X	1575.4	0.08	16.2	137	13	5.21	1846
379468	X	1.6	3	539.8	0.14	24.1	132	157	6.33	1835
379469	X	0.4	6	1556.8	0.12	18.4	131	25	5.22	1867
379470	X	0.2	4	1533.7	0.25	18.2	115	29	5.25	1731
379471	X	0.3	22	1547.1	2.46	12.6	36	26	3.4	779
379472	X	2.3	17	1536.9	0.13	24.8	101	66	4.09	1666
379473	X	0.3	14	838.1	0.17	18.3	142	29	5.22	1877
379474	X	0.4	2	1089.7	0.15	33	233	77	7.11	2233
379475	X	0.4	4	1166.6	0.16	30.4	194	68	6.62	2465
379476	X	X	8	1022.4	0.21	31.8	286	15	6.36	3165
379477	0.1	0.4	106	601.8	0.43	62.4	850	391	8.73	388
379478	X	X	9	913	0.14	32.3	290	18	6.71	3517
379479	X	0.4	23	905.2	0.29	45.3	543	107	5.77	2218
379480	X	0.5	33	670	0.35	49.7	377	84	5.48	1923
379481	0.02	0.4	12	1643.7	0.3	38.7	361	128	5.2	2349
379482	X	0.6	36	357.3	0.34	55.9	412	121	6.76	2155
379483	X	0.4	12	1050.8	0.27	37.2	378	105	5.57	2770
379484	X	0.7	24	418.5	0.42	50.4	360	120	6.35	2491
379485	X	0.6	24	1667.8	0.29	47.9	386	96	6.81	2481
379486	X	X	9	2482.8	0.23	42.8	411	60	5.54	2500
379487	0.1	0.4	106	615.7	0.44	62.1	1054	399	9	402
CHECKS										
379457	X	X	19	198.4	0.15	14.1	20	11	1.97	94
379477	0.1	0.4	105	610	0.43	63.1	856	394	8.94	396
STANDARDS										
OxN62	7.86									
SARM4		X	X	84.5	0.03	58.9	18	14	6.16	1287
OxP61	15.12									
SY-4		X	X	327.7	0.02	2.2	12	7	4.35	753
BLANKS										
Control Blank	X	X	X	X	X	X	X	X	X	X
Control Blank		X	X	X	0.02	X	X	X	X	X
Acid Blank		X	X	X	0.01	X	X	X	X	X

DIAMOND DRILL HOLE MS2
ASSAY RESULTS

Mo	Pb	Sb	Sn	Tl	W	Zn
ppm						
0.1	2	0.05	0.1	0.02	0.1	1
A/MS	A/MS	A/MS	A/MS	A/MS	A/MS	A/OES

2.1	19	1.42	0.8	0.11	1	13
9.6	16	1.17	0.8	0.19	0.9	15
1.6	4	0.49	0.8	0.13	0.7	17
4	26	3.33	2.4	0.75	1.9	97
20.1	7	3.86	0.2	19.12	0.3	34
1.2	6	1.15	0.8	0.41	1.2	53
1.5	48	3.9	1.9	0.67	1.3	67
6.7	2653	1.55	2.1	0.5	1	26
0.8	16	1.18	2.5	0.13	0.7	55
0.3	94	0.44	1.7	0.51	0.5	3556
0.5	31	0.66	1.5	0.3	1.5	517
1.5	1526	2.31	1.3	0.17	1.6	5294
0.5	805	0.95	1.4	0.29	1.5	944
0.7	140	0.85	1.6	0.31	1.7	866
7.3	18	1.7	2.6	1.39	0.7	5971
0.8	6961	1.97	2.1	0.22	1.4	5339
0.7	867	0.34	1.6	0.19	1.6	4055
4.1	50	0.67	1.5	0.28	1.3	112
2.2	263	0.82	1.5	0.33	1.4	297
0.7	9	0.93	1.5	0.34	1.7	970
8.7	151	12.82	3.6	1.01	32.4	643
2.5	8	1.2	1.5	0.25	1.7	606
1.8	44	1.28	1.2	0.4	1.5	635
2.3	63	1.54	1.2	0.29	1.4	942
1.1	48	1.3	1.2	0.52	2	803
3.9	41	1.99	1.2	0.48	1.8	1095
1.2	18	1.25	1.3	0.33	1.4	719
2.9	409	1.89	1.2	0.28	1.4	2053
3.4	119	1.77	1.2	0.54	2	1859
0.6	27	1.38	1.2	0.67	1.9	2757
8.6	154	13.01	3.7	1.01	33.8	680
2	19	1.49	0.8	0.1	1.1	11
8.6	153	12.82	3.8	1.02	31.6	667
0.9	3	0.1	0.2	X	0.4	60
0.3	9	0.08	7.6	0.25	0.3	96
X	X	X	0.1	X	0.1	2
X	X	0.09	X	X	X	3
X	X	X	X	X	X	X