

EL54/2004 Waratah
Rock Chip Assay Results



BHID	SAMPLE	FROM	TO	LENGTH (CM)	TENEMENT / COMMENT	Sample	Cu	Pb	Zn	Ag	As	Fe	Ba	Sn	Au
							ppm	ppm	ppm	ppm	ppm	%	%	ppm	ppm
MAGRCP1	300460	0.00	1.00	100.00	magnet rock chips - scheer's adit from road	303460	64	2296	3274	8	632	8.96	1.23	80	<0.01
MAGRCP1	300461	1.00	2.00	100.00		303461	32	1475	9700	20	1284	10.6	1.46	100	<0.01
MAGRCP1	300462	2.00	3.00	100.00		303462	30	42	492	2	364	7.29	1.13	60	<0.01
MAGRCP1	300463	3.00	4.00	100.00		303463	31	781	4451	13	870	10.3	1.35	50	<0.01
MAGRCP1	300464	4.00	5.00	100.00		303464	20	1575	11800	12	1425	32.2	3.22	150	<0.01
MAGRCP1	300465	5.00	6.00	100.00		303465	26	2670	13500	16	2147	21.3	2.43	170	<0.01
MAGRCP1	300466	6.00	7.00	100.00		303466	33	3436	40700	28	2690	30.4	3.19	210	<0.01
MAGRCP1	300467	7.00	8.00	100.00		303467	135	3351	71600	120	4596	17.7	2.80	450	<0.01
MAGRCP1	300468	8.00	9.00	100.00		303468	46	5140	33200	71	4495	29.5	3.23	220	0.01
MAGRCP1	300469	9.00	10.00	100.00		303469	10	340	1824	3	432	6.48	1.08	350	<0.01
MAGRCP1	300470	10.00	11.00	100.00	303470	12	246	1681	3	109	5.64	1.01	330	<0.01	
MAGRCP2	300471	0.00	1.00	100.00	magnet rock chips - fw of main gossan from road	303471	37	663	6460	38	56	10.5	1.23	60	<0.01
MAGRCP2	300472	1.00	2.00	100.00		303472	44	34	916	3	106	6.08	1.15	100	<0.01
MAGRCP2	300473	2.00	3.00	100.00		303473	40	10	6266	20	226	8.10	1.12	30	<0.01
MAGRCP2	300474	3.00	4.00	100.00		303474	44	46	6400	4	109	8.01	1.12	80	<0.01
MAGRCP2	300475	4.00	5.00	100.00		303475	29	12	952	1	86	7.72	1.13	90	<0.01
MAGRCP2	300476	5.00	6.00	100.00		303476	32	106	1940	2	377	7.96	1.11	90	<0.01
MAGRCP2	300477	6.00	7.00	100.00		303477	50	154	4928	7	608	7.93	1.10	50	<0.01
MAGRCP2	300478	7.00	8.00	100.00		303478	42	57	2877	4	395	7.13	1.04	90	<0.01
MAGRCP2	300479	8.00	9.00	100.00		303479	26	439	6282	8	652	10.8	1.39	100	<0.01
MAGRCP2	300480	9.00	10.00	100.00		303480	16	924	5788	6	538	10.2	1.37	80	<0.01
MAGRCP2	300481	10.00	11.00	100.00		303481	32	2741	11800	17	1082	15.6	1.77	100	<0.01
MAGRCP2	300482	11.00	12.00	100.00		303482	336	49500	16600	720	841	27.1	2.68	600	0.03
MAGRCP2	300483	12.00	13.00	100.00	303483	75	13600	10900	54	5046	27.2	2.69	220	0.03	
MAGRCP3	300484	0.00	1.00	100.00	magnet gossan grab 1	303484	56	2583	12600	35	818	19.8	2.14	130	<0.01
MAGRCP4	300485	0.00	1.00	100.00	magnet gossan grab 2	303485	217	17000	26100	156	2582	24.3	2.41	460	0.05
MAGRCP5	300486	0.00	1.00	100.00	magnet gossan grab 3	303486	114	28600	23500	137	617	21.8	2.42	350	<0.01
MAGRCP6	300487	0.00	1.00	100.00	magnet gossan grab 4	303487	54	1145	2827	7	503	15.3	1.66	80	<0.01
MAGRCP7	300488	0.00	1.00	100.00	magnet rock chips - main gossan from road	303488	60	5615	6679	29	852	10.4	1.35	60	<0.01
MAGRCP7	300489	1.00	2.00	100.00		303489	43	980	8532	70	800	11.0	1.37	50	<0.01
MAGRCP7	300490	2.00	3.00	100.00		303490	50	12000	6089	77	556	9.89	1.39	40	<0.01
MAGRCP7	300491	3.00	4.00	100.00		303491	44	11700	13800	253	752	20.5	2.26	120	<0.01
MAGRCP7	300492	4.00	5.00	100.00		303492	25	23500	5554	23	318	13.0	1.67	30	<0.01
MAGRCP7	300493	5.00	6.00	100.00		303493	55	9762	6660	25	788	9.45	1.39	40	<0.01
MAGRCP7	300494	6.00	7.00	100.00		303494	50	28500	9400	37	703	10.5	1.67	20	<0.01
MAGRCP7	300495	7.00	8.00	100.00		303495	70	35300	7259	91	889	13.8	1.95	60	<0.01
MAGRCP7	300496	8.00	9.00	100.00	303496	87	23300	5168	22	699	10.9	1.53	50	<0.01	

EL54/2004 Waratah
Rock Chip Assay Results



MAGRCP7	300497	9.00	10.00	100.00		303497	86	36500	8946	80	930	17.3	2.08	40	<0.01
MAGRCP7	300498	10.00	11.00	100.00		303498	84	26900	13100	133	1536	18.4	2.04	160	<0.01
MAGRCP7	300499	11.00	12.00	100.00		303499	77	42600	11800	119	2359	16.4	2.23	80	<0.01
MAGRCP8	300500	0.00	1.00	100.00	magnet rock chips - gossan fw skin	303500	143	46800	20400	139	2092	24.2	2.74	230	0.02
MAGRCP9	300501	0.00	1.00	100.00	magnet rock chips - gossan brx fw skin	303501	31	5315	6983	17	870	12.0	1.60	90	<0.01
MAGRCP9	300502	1.00	2.00	100.00	from down slope directed up slope	303502	32	3040	26400	27	1359	21.6	2.40	200	<0.01
MAGRCP9	300503	2.00	3.00	100.00		303503	72	1733	22500	48	422	14.2	2.03	290	<0.01
MAGRCP9	300504	3.00	4.00	100.00		303504	60	9462	16800	113	741	20.6	2.33	180	<0.01
MAGRCP9	300505	4.00	5.00	100.00		303505	36	3308	16300	23	274	21.0	2.25	280	<0.01
MAGRCP9	300506	5.00	6.00	100.00		303506	88	12900	41100	163	517	25.1	2.86	380	0.02
MAGRCP10	300507	0.00	1.00	100.00	magnet rock chips - gossan brx fw skin	303507	896	42700	84300	977	666	33.6	3.54	1180	0.07
MAGRCP10	300508	1.00	2.00	100.00	from down slope directed up slope	303508	62	20500	37000	105	3733	30.6	3.35	260	0.02
MAGRCP10	300509	2.00	3.00	100.00	2.5m along strike from 501-506	303509	46	20100	26700	225	2469	32.2	3.43	200	0.01
MAGRCP10	300510	3.00	4.00	100.00		303510	34	3107	25400	35	376	14.8	1.79	270	0.01
MAGRCP10	300511	4.00	5.00	100.00		303511	43	4562	45500	68	842	24.5	2.65	190	0.01
MAGRCP10	300512	5.00	6.00	100.00		303512	60	4725	36800	96	426	17.2	2.10	270	<0.01
MAGRCP10	300513	6.00	7.00	100.00		303513	65	6120	32300	56	325	20.4	2.28	340	<0.01
MAGRCP10	300514	7.00	8.00	100.00		303514	127	14200	54400	109	541	23.9	2.78	440	0.01
MAGRCP10	300515	8.00	9.00	100.00		303515	37	5609	50500	43	727	23.9	2.83	270	0.02
MAGRCP	300516				STANDARD - GBM903-15	303516	628	10300	30500	12	<10	4.50	1.20	100	1.15
MAGRCP	300517				BLANK.....submission 20081016, PO1447	303517	12	232	1069	2	<10	1.69	0.72	<10	<0.01