

SITE ID	From (m)	To (m)	Sample ID		Al2O3%	Fe%	P2O5%	SiO2%	SO3%	SnO2%
KWRC002	0	1	7215	0.81 58.4	0.077 13	0.03	<0.01			
KWRC002	1	2	7216	1.9 60	0.12 8.8	0.04	0.01			
KWRC002	2	3	7217	2.5 57.7	0.22 8.9	0.05	0.02			
KWRC002	3	4	7218	3.3 56.7	0.21 10.5	0.06	<0.01			
KWRC002	4	5	7219	2.4 62.9	0.1 5.7	0.03	<0.01			
KWRC002	5	6	7220	1.8 49.3	0.083 25.8	0.02	<0.01			
KWRC002	6	7	7221	1.6 60	0.1 10.5	0.02	<0.01			
KWRC002	7	8	7222	2.4 55.4	0.22 15	0.03	<0.01			
KWRC002	8	9	7223	15.3 12.6	0.28 53.9	0.06	0.01			
KWRC002	27	28	7224	1.1 50.6	0.16 23.8	<0.01	<0.01			
KWRC002	28	29	7225	1.3 48.6	0.16 25.4	0.02	<0.01			
KWRC002	29	30	7226	0.93 17.6	0.21 65.4	0.02	<0.01			
KWRC003	0	1	7227	0.82 53.2	0.065 19.8	0.04	<0.01			
KWRC003	1	2	7228	2.9 31.1	0.041 50.1	0.09	<0.01			
KWRC003	7	8	7230	8 41.6	0.27 25.9	0.05	<0.01			
KWRC003	8	9	7231	2.6 49.6	0.16 23.9	0.03	<0.01			
KWRC003	9	10	7232	6.9 34	0.18 39.1	0.1	<0.01			
KWRC003	10	11	7233	5.7 44.1	0.12 26.9	0.08	<0.01			
KWRC003	23	24	7234	1.7 35.6	0.24 38.4	0.06	<0.01			
KWRC003	24	25	7235	2.1 38.8	0.14 37.6	0.05	<0.01			
KWRC003	25	26	7236	2.2 32.1	0.22 40.9	0.06	0.01			
KWRC003	30	31	7237	0.67 54.1	0.23 11.7	0.01	<0.01			
KWRC003	31	32	7238	0.68 57.7	0.24 5.3	0.03	<0.01			
KWRC003	32	33	7239	0.76 55.7	0.26 5.3	0.02	<0.01			
KWRC003	33	34	7240	1.4 48.7	0.29 15.6	0.03	<0.01			
KWRC004	3	4	7241	5.5 40.8	0.39 9.3	0.26	0.04			
KWRC004	4	5	7242	1.9 53.2	0.17 3.3	0.1	<0.01			
KWRC004	5	6	7243	1.8 50.3	0.21 3.2	0.1	0.02			
KWRC004	6	7	7244	1.8 49.2	0.29 7	0.1	0.02			
KWRC004	53	54	7247	17 4.3	0.081 63.4	2.8	0.01			
KWRC004	54	55	7248	17.3 5.6	0.067 60.9	4.2	<0.01			
KWRC004	55	56	7249	17.7 3.8	0.062 64	2.9	0.01			
KWRC004	56	57	7250	17.9 3.8	0.07 63.7	3.1	0.01			
KWRC004	57	58	7251	17.4 4	0.084 63.4	2.5	<0.01			
KWRC004	58	59	7252	17.3 5	0.094 61.2	5.4	<0.01			
KWRC005	0	1	7253	0.91 58.9	0.052 12.9	0.04	0.01			
KWRC005	1	2	7254	2.3 51.1	0.075 20.9	0.06	<0.01			
KWRC005	6	7	7255	4.6 53.8	0.25 12.9	0.07	<0.01			
KWRC005	7	8	7256	2.8 56.7	0.22 11.4	0.09	<0.01			
KWRC005	8	9	7257	3 60.9	0.14 6.8	0.06	<0.01			
KWRC005	9	10	7258	3.1 62.4	0.055 5.4	0.05	<0.01			

KWRC005 10	11	7259	2.5	57.9	0.17	6	2.9	<0.01
KWRC005 11	12	7260	3	58.8	0.068	9.7	0.53	<0.01
KWRC005 12	13	7261	3.9	56.4	0.12	11.5	0.5	<0.01
KWRC005 13	14	7262	3.5	56.3	0.23	10.1	0.12	<0.01
KWRC005 14	15	7263	2.5	53.3	0.18	16.7	0.08	<0.01
KWRC005 15	16	7264	2.6	40.2	0.23	33.5	0.08	0.02
KWRC005 16	17	7265	2.8	59.5	0.19	8.6	0.05	0.01
KWRC005 17	18	7266	2	62.3	0.15	5.8	0.02	0.01
KWRC005 18	19	7267	8.4	47.4	0.2	17.4	0.03	<0.01
KWRC005 19	20	7268	4	52.4	0.17	16.5	0.03	<0.01

EOF