

MOINA QEMSCAN INTERPRETATION For Mineral Processing

- Head and Available Metal
- Grade-Recovery
- Gravity Separation
- Flowsheet Simulation

MOINA QEMSCAN INTERPRETATION For Mineral Processing

- Head and Available Metal
- Grade-Recovery
- Gravity Separation
- Flowsheet Simulation



QEMSCAN Sample – Head Assay Recoverable Minerals


Head Assay	
%	
F	7.92
W	0.070
Sn	0.20
Bi	0.046

	F	W	Sn	Bi
Fluorite	92.1			
Scheelite		94.8		
Cassiterite			48.3	
Bi-Minerals				100.0
Actinolite/Cummingtonite	0.80			
Biotite	1.25			
Ca-Fe Carb/Ox				
Calcite				
Chlorite	0.15			
Chlorite(F)	0.53			
Clays				
Diopside/Salite	0.082			
Fe-Ca-Amphibole(LowAl&K)	2.07			
Garnet			36.8	
K-Feldspar				
Plagioclase				
Pyrite				
Quartz				
Sericite/Muscovite	0.36			
Sn-Fe Oxide			14.9	
Sphene				
Vesuvianite/Epidote	2.67			
Other	0.001	5.23		
Other Silicates				
Other Sulphides				
Other Carbonates				
TOTAL	100.0	100.0	100.0	100.0


MOINA QEMSCAN INTERPRETATION For Mineral Processing

- Head and Available Metal
- **Grade-Recovery**
- Gravity Separation
- Flowsheet Simulation


Grade-Recovery - Particle Sorting (+63 μm)




Grade-Recovery - Grade-Recovery Coarsest Fraction




Grade-Recovery - Grade-Recovery All Fractions



Grade-Recovery - Grade-Recovery
Total Sample (Calculated)




Overall QEMSCAN data are related to the Sample after Crushing



Simulation Procedure for Finer Grind


	Mass % QS Feed	Simulated Finer Grinding					
		-63 μm		-45 μm		-20 μm	
+63 μm	29.8						
-63/+45 μm	12.9	12.9	18.3				
-45/+20 μm	19.0	19.0	27.0	19.0	33.1		
-20 μm	38.4	38.4	54.7	38.4	66.9	38.4	100.0
Total	100.0	70.2	100.0	57.4	100.0	38.4	100.0



Assumption that after more grinding:

Coarser fractions will be the same as finer fractions


Simulation Procedure for Finer Grind



After finer grinding: Recovery improves from 65% to 90%

Fluorspar Grade and Contaminants

Fluorspar Grade is limited by:



$\text{CaF}_2 > 97\%$

$\text{SiO}_2 < 1\%$

$\text{CaCO}_3 < 1\%$

$S_T < 0.02\%$

$\text{Fe}_2\text{O}_3 < 1\%$



Fluorspar Grade and Recovery Mineralogically Limiting (Best Possible)


Grade and Recovery

K80 = 75 μm

	Assay, %	Recovery, %
CaCO ₃	1	
CaF₂	97	65
SiO ₂	0.9	
S	0.01	
WO ₃	0.05	
Sn	0.01	
Fe ₂ O ₃	0.43	

-20 μm

	Assay, %	Recovery, %
CaCO ₃	1	
CaF₂	97.2	83
SiO ₂	0.6	
S	0.005	
WO ₃	0.0252	
Sn	0.013	
Fe ₂ O ₃	0.286	






Agglomeration
Will be
Required



Grade and Recovery





Scheelite, Cassiterite, Bismuth



MOINA QEMSCAN INTERPRETATION For Mineral Processing

- Head and Available Metal
- Grade-Recovery
- Gravity Separation
- Flowsheet Simulation

Gravity Recovery at K80 = 75 μm



MOINA QEMSCAN INTERPRETATION For Mineral Processing


- Head and Available Metal
- Grade-Recovery
- Gravity Separation
- Flowsheet Simulation



Flowsheet

Primary Grind: K80 = 75 μm

Regrind: K80 ~ 20-30 μm





S-Flotation

% S in Particle:

- >= 10% : Float
- 5-10% : Likely Float
- 1-5%: Needs Aggressive Flotation
- <1%: Will not Float

Mass Recovery, %					
	+63um	-63/+45um	-45/+20um	-20um	Total
S=0%	94.0	97.1	97.8	97.3	96.4
S<1%	3.89	1.13	0.83	1.83	2.16
S<5%	1.21	0.66	0.54	0.13	0.59
S<10%	0.26	0.19	0.12	0.11	0.17
S>=10%	0.63	0.88	0.68	0.67	0.69
Total	100.0	100.0	100.0	100.0	100.0

S-Recovery, %					
	+63um	-63/+45um	-45/+20um	-20um	Total
S=0%					
S<1%	3.15	1.26	1.04	0.93	1.59
S<5%	11.5	4.40	3.92	1.03	4.91
S<10%	7.35	4.30	3.18	2.86	4.34
S>=10%	78.0	90.0	91.9	95.2	89.2
Total	100.0	100.0	100.0	100.0	100.0

Bi-Recovery, %					
	+63um	-63/+45um	-45/+20um	-20um	Total
S=0%					
S<1%	18.9	10.8	6.83	0.62	5.89
S<5%	61.4	45.7	39.5	1.66	21.8
S<10%	17.5	28.4	18.5	5.82	11.7
S>=10%	2.17	15.1	35.1	91.9	60.6
Total	100.0	100.0	100.0	100.0	100.0


Simulation Conditions:

- S>5 Particles containing more than 5% S
- Si Float Particles with a combined mass of 10% or more of: biotite+chlorite+chlorite(F)+clays+sericite/muscovite
- CaF₂ Particles containing 10% or more fluorspar
- W Particles containing 10% or more scheelite
- Sn Particles containing 10% or more cassiterite
- Calcite Particles containing 10% or more calcite
- Ca Min Particles containing 10% or more of fluorspar+scheelite+cassiterite+calcite
- Other Ca Particles containing 10% or more of the element Ca
- Left Over The rest

	Overall Recovery, % (Total Sample)				
	Mass	Bi-Minerals	Fluorspar	Scheelite	Cassiterite
S>5	0.86	72.3	0.29	0.40	0.21
Si Float	10.2	1.33	1.14	0.54	2.05

	Overall Recovery, % (Total Sample)				
	Mass	Bi-Minerals	Fluorspar	Scheelite	Cassiterite
CaF ₂	23.1	8.45	94.1	19.5	17.2
W	0.20		0.011	76.6	
Sn	0.079	0.036	0.006		74.9
Calcite	1.31		0.036		
Ca Min	0.38	0.15	0.23	0.55	0.88
Other Ca	37.0	11.9	3.08	1.71	2.08
Fatty Acid	62.1	20.5	97.5	98.3	95.1

Too Much Mass: 62.1%



Can the Mass be reduced by Finer Grinding?

	Fatty Acid Float Recoveries, %				
	Mass	Bi-Minerals	Fluorspar	Scheelite	Cassiterite
Full Sample	62.1	20.5	97.5	98.3	95.1
-63 µm	58.9	9.42	98.7	99.2	96.9
-45 µm	58.2	4.95	99.1	99.7	98.8
-20 µm	58.3	1.46	99.5	99.7	99.7

Not Significantly

Needs **Depression**

Flotation with Depression

Calcite and Ca-Minerals are Depressed

But also

CaF₂, W, Sn

(to a lesser degree)

	Limits for Flotation	
	No Depression	With Depression
S>5	5%	5%
Si Float	10%	10%
CaF ₂	10%	15%
W	10%	15%
Sn	10%	30%
Calcite	10%	80%
Ca Min	10%	20%
Other Ca	10%	22%



Ca-Flotation with Depression

Without Depression

	Overall Recovery, % (Total Sample) Without Depression				
	Mass	Bi-Minerals	Fluorspar	Scheelite	Cassiterite
S>5	0.86	72.3	0.29	0.40	0.21
Si Float	10.2	1.33	1.14	0.54	2.05
CaF2	23.1	8.45	94.1	19.5	17.2
W	0.20	0.011	0.011	76.6	
Sn	0.079	0.036	0.006		74.9
Calcite	1.31		0.036		
Ca Min	0.38	0.15	0.23	0.55	0.88
Other Ca	37.0	11.9	3.08	1.71	2.08
Left Over	26.9	5.86	1.07	0.75	2.67
Total	100.0	100.0	100.0	100.0	100.0

Sulphide	0.86	72.3	0.29	0.40	0.21
Fatty Acid	62.1	20.5	97.5	98.3	95.1


With Depression

	Overall Recovery, % (Total Sample) With Depression				
	Mass	Bi-Minerals	Fluorspar	Scheelite	Cassiterite
S>5	0.86	72.3	0.29	0.40	0.21
Si Float	10.2	1.33	1.14	0.54	2.05
CaF2	19.7	6.78	91.0	13.6	6.6
W	0.20	0.023	0.023	80.3	
Sn	0.060		0.007		76.0
Calcite	0.78		0.030	0.047	0.173
Ca Min	0.46		0.06	0.37	7.61
Other Ca	7.4	0.3	0.95	0.17	
Left Over	60.3	19.29	6.47	4.55	7.29
Total	100.0	100.0	100.0	100.0	100.0

Sulphide	0.86	72.3	0.29	0.40	0.21
Fatty Acid	28.6	7.1	92.1	94.5	90.4

Much less mass

Lower Recoveries






Ca-Flotation with Depression – Upgrading/Separation

Bulk Ca-Float (with Depression) Cleaning:



Particle must contain >20% of Fluorspar+Scheelite+Cassiterite

Bulk Flotation Concentrate	
	Recovery, %
Mass	17.9
Fluorspar	88.7
Scheelite	94.2
Cassiterite	90.1



Gravity Separation of Bulk Flotation Concentrate

Fine Gravity Separation: MGS or Similar



Grind	Recovery, %		
	Lights Fluorspar	Heavies Scheelite Cassiterite	
K80 = 75 µm	99.8	76.5	78.5
-63 µm	99.8	82.4	79.8
-45 µm	99.9	84.3	84.8
-20 µm	99.9	85.6	86.0

Gravity Separation: Coarser is EASIER/Cheaper

MOINA QEMSCAN INTERPRETATION For Mineral Processing


- Head and Available Metal
- Grade-Recovery
- Gravity Separation
- Flowsheet Simulation
- **Magnetic Separation**

Assumptions:

All Fe-Oxide Minerals = Magnetite

Sn-Fe-Oxides Minerals = Cassiterite + Magnetite

Grind	Recovery in Magnetic Concentrate				
	Mass	Fluorspar	Fe	Scheelite	Cassiterite
K80 = 75 µm	25.3	6.77	72.1	4.70	45.4
-64 µm	24.9	3.91	73.7	1.77	42.3
-45 µm	23.6	2.79	72.6	0.91	34.5
-20 µm	19.7	1.66	68.2	0.17	25.7



MOINA QEMSCAN INTERPRETATION For Mineral Processing

- Simulated Recoveries

Fluorspar:

The fluorspar concentrate will need to be reground and will be too fine to market without agglomeration. The concentrate grade will be limited by the 1% limit of CaCO₃.

The maximum fluorspar recovery will be 83% (@ -20 µm). This equates to the F-recovery of 76.4%.

The recovery of fluorspar from the sample will be dictated by the concentrate quality.

Scheelite:

At target grade of 60% WO₃, the scheelite recovery would be 87% without regrinding and 97% for a fine regrind of -20 µm.

The WO₃ recoveries will be 82.5% and 92% for no regrinding or -10 µm regrinding, respectively.

Cassiterite:

Target grade = 70% Sn. The cassiterite recovery would be 45% without regrinding and 75% for a fine regrind of -20 μm .

Since only 48.3% of the Sn is in cassiterite, the Sn-recoveries will be 22% and 36% for no regrinding or -20 μm regrinding, respectively.

Bismuth:

Assuming the processing of the Bi-concentrate will likely be a leaching process. May be able to accept low-grade concentrate, below 20% Bi, or even 10%Bi. Recoveries (based on grade-recovery) can be over 90%.

Coarse flotation at start: maximum 73% Bi Recovery.