

Sample Number	Hole ID	From	To	Interval	Recovery	SiO2 %	Al2O3 %	CaO %	Fe2O3 %
2446	CSD-03	4	6.3	2.3	0.45	99.78	0.077	0.052	0.037
2447	CSD-03	6.3	7.7	1.4	1.4	99.92	0.042	0.009	0.006
2448	CSD-03	7.7	8.7	1	1	98.48	0.692	0.006	0.278
2449	CSD-03	8.7	10	1.3	1	96.74	1.58	0.005	0.548
2450	CSD-03	10	11	1	1	95.59	2.04	0.003	0.88
2451	CSD-03	11	12	1	1	99.65	0.166	0.004	0.107
2452	CSD-03	12	13	1	1	99.33	0.41	0.005	0.085
2453	CSD-03	13	14	1	1	99.77	0.164	0.003	0.011
2454	CSD-03	14	15	1	1	99.39	0.331	0.003	0.09
2455	CSD-03	15	16	1	1	99.58	0.232	0.004	0.058
2456	CSD-03	16	17	1	1	99.65	0.198	0.003	0.053
2457	CSD-03	17	18	1	0.68	99.65	0.231	0.004	0.035
2458	CSD-03	18	19	1	0.54	99.65	0.214	0.003	0.042
2459	CSD-03	19	20.4	1.4	1.1	98.87	0.814	0.004	0.067
2460	CSD-04	0.5	2	1.5	0.5	99.9	0.059	0.004	0.01
2461	CSD-04	2	3	1	1	99.61	0.217	0.003	0.076
2462	CSD-04	3	4	1	1	99.72	0.166	0.004	0.041
2463	CSD-04	4	5	1	1	99.85	0.053	0.003	0.073
2464	CSD-04	5	6	1	1	99.92	0.04	0.003	0.009
2465	CSD-04	6	7	1	1	99.94	0.026	0.003	0.007
2466	CSD-04	7	8	1	1	99.95	0.023	0.003	0.006
2467	CSD-04	8	9	1	1	99.73	0.149	0.003	0.046
2468	CSD-04	9	10	1	1	99.93	0.04	0.003	0.009
2469	CSD-04	10	11	1	1	99.92	0.043	0.003	0.014
2470	CSD-04	11	12	1	1	99.89	0.064	0.004	0.021
2471	CSD-04	12	13	1	0.8	99.92	0.038	0.003	0.007
2472	CSD-04	13	14	1	1	99.73	0.193	0.004	0.011
2473	CSD-04	14	15	1	1	98.68	1.085	0.007	0.023
2474	CSD-01	0	4.5	4.5	0.45	99.89	0.045	0.002	0.007
2475	CSD-01	4.5	6	1.5	0.98	99.51	0.336	0.002	0.029
2476	CSD-01	6	9	3	0.6	99.9	0.045	0.002	0.013
2477	CSD-01	9	10.8	1.8	1.32	99.77	0.162	0.002	0.02
2478	CSD-01	10.8	12	1.2	1	99.68	0.198	0.002	0.052
2479	CSD-01	12	13	1	1	99.57	0.306	0.006	0.035
2480	CSD-01	13	14	1	1	99.78	0.149	0.003	0.013
2481	CSD-01	14	15	1	1	99.68	0.232	0.004	0.013
2482	CSD-01	15	16	1	1	99.63	0.28	0.003	0.01
2483	CSD-01	16	17	1	1	98.52	1.075	0.006	0.114
2484	CSD-01	17	18	1	1	96.87	2.24	0.004	0.097
2485	CSD-01	18	19	1	1	98.11	1.29	0.003	0.113
2486	CSD-01	19	20	1	1	98.09	1.28	0.004	0.084
2487	CSD-01	20	21	1	1	98.53	1.21	0.006	0.031
2488	CSD-01	39	40	1	0.75	96.98	2.06	0.004	0.29
2489	CSD-01	40	40.5	0.5	0.5	93.56	4.12	0.003	0.681
2490	CSD-01	40.5	42.7	2.2	0.95	95.39	3.25	0.003	0.389

K2O %	MgO %	MnO %	Na2O %	TiO2 %	V2O5 %	Cr2O3%	Cr2O3ppm	Cr2O3 ppm	Method
0.01	0.023	<0.001	0.004	0.012	<0.001	0.00015	1.462		1 ME-ICP64
0.007	0.003	<0.001	0.001	0.013	<0.001	0.00015	1.462		1 ME-ICP64
0.018	0.504	0.006	0.001	0.015	0.001	0.00044	4.386		3 ME-ICP64
0.099	0.997	0.015	0.004	0.013	0.001	0.00102	10.234		7 ME-ICP64
0.164	1.265	0.025	0.013	0.012	0.002	0.00102	10.234		7 ME-ICP64
0.011	0.053	0.001	0.004	0.007	<0.001	0.00015	1.462		1 ME-ICP64
0.059	0.095	0.001	0.003	0.008	<0.001	0.00058	5.848		4 ME-ICP64
0.018	0.027	<0.001	0.003	0.007	<0.001	0.00015	1.462		1 ME-ICP64
0.029	0.141	0.001	0.004	0.008	<0.001	0.00044	4.386		3 ME-ICP64
0.024	0.086	0.001	0.004	0.007	<0.001	0.00044	4.386		3 ME-ICP64
0.018	0.063	0.001	0.003	0.008	<0.001	0.00044	4.386		3 ME-ICP64
0.03	0.04	<0.001	0.003	0.007	<0.001	0.00044	4.386		3 ME-ICP64
0.024	0.055	<0.001	0.001	0.01	<0.001	0.00015	1.462		1 ME-ICP64
0.133	0.061	0.001	0.026	0.025	0.001	0.00088	8.772		6 ME-ICP64
0.006	0.005	<0.001	0.003	0.012	<0.001	0.00015	1.462		1 ME-ICP64
0.006	0.076	0.001	0.004	0.008	<0.001	0.00015	1.462		1 ME-ICP64
0.01	0.045	0.001	0.003	0.012	<0.001	0.00058	5.848		4 ME-ICP64
0.007	0.003	<0.001	0.003	0.008	<0.001	0.00044	4.386		3 ME-ICP64
0.007	0.003	<0.001	0.003	0.015	<0.001	0.00015	1.462		1 ME-ICP64
0.006	0.002	<0.001	0.003	0.012	<0.001	0.00015	1.462		1 ME-ICP64
0.004	0.002	<0.001	0.003	0.01	<0.001	0.00044	4.386		3 ME-ICP64
0.004	0.055	0.001	0.004	0.007	<0.001	0.00044	4.386		3 ME-ICP64
0.002	0.003	<0.001	0.003	0.008	<0.001	0.00044	4.386		3 ME-ICP64
0.004	0.003	<0.001	0.004	0.008	<0.001	0.00278	27.778		19 ME-ICP64
0.005	0.007	<0.001	0.007	0.005	<0.001	0.00044	4.386		3 ME-ICP64
0.005	0.003	<0.001	0.005	0.017	<0.001	0.00044	4.386		3 ME-ICP64
0.025	0.007	<0.001	0.004	0.023	<0.001	0.00044	4.386		3 ME-ICP64
0.145	0.022	<0.001	0.009	0.027	0.001	0.00146	14.62		10 ME-ICP64
0.008	0.003	<0.001	0.005	0.038	<0.001	0.00015	1.462		1 ME-ICP64
0.081	0.007	<0.001	0.008	0.022	<0.001	0.0098	97.954		67 ME-ICP64
0.01	0.003	<0.001	0.009	0.017	<0.001	0.00015	1.462		1 ME-ICP64
0.014	0.018	<0.001	0.004	0.01	<0.001	0.00015	1.462		1 ME-ICP64
0.01	0.051	<0.001	0.003	0.007	<0.001	0.00015	1.462		1 ME-ICP64
0.013	0.041	0.001	0.019	0.012	<0.001	0.00044	4.386		3 ME-ICP64
0.022	0.013	<0.001	0.007	0.008	<0.001	0.00058	5.848		4 ME-ICP64
0.046	0.011	<0.001	0.008	0.01	<0.001	0.00044	4.386		3 ME-ICP64
0.043	0.016	<0.001	0.009	0.006	<0.001	0.00015	1.462		1 ME-ICP64
0.094	0.121	0.001	0.035	0.032	0.001	0.00058	5.848		4 ME-ICP64
0.458	0.255	0.004	0.028	0.038	0.002	0.00132	13.158		9 ME-ICP64
0.161	0.279	0.003	0.009	0.031	0.001	0.00088	8.772		6 ME-ICP64
0.285	0.209	0.001	0.015	0.028	0.001	0.00102	10.234		7 ME-ICP64
0.158	0.03	<0.001	0.011	0.02	0.001	0.00058	5.848		4 ME-ICP64
0.467	0.115	0.001	0.035	0.049	0.002	0.00175	17.544		12 ME-ICP64
1.305	0.161	0.003	0.042	0.121	0.004	0.00468	46.784		32 ME-ICP64
0.71	0.15	0.004	0.046	0.049	0.002	0.00219	21.93		15 ME-ICP64

SiO2 %	Al2O3 %	CaO %	Fe2O3 %	K2O %	MgO %	MnO %	Na2O %	TiO2 %
99.85	0.0595	0.0305	0.0215	0.0085	0.013	#DIV/0!	0.0025	0.0125
96.93667	1.437333	0.004667	0.568667	0.093667	0.922	0.015333	0.006	0.013333
99.58375	0.24325	0.003625	0.060125	0.026625	0.07	0.001	0.003125	0.00775
99.84692	0.085462	0.003308	0.025385	0.007	0.016462	0.001	0.003769	0.011154
99.69	0.2135	0.003	0.023125	0.029875	0.02	0.001	0.008375	0.0115
99.69	0.2135	0.003	0.023125	0.029875	0.02	0.001	0.008375	0.0115
98.024	1.419	0.0046	0.0878	0.2312	0.1788	0.00225	0.0196	0.0298
95.31	3.143333	0.003333	0.453333	0.827333	0.142	0.002667	0.041	0.073

V2O5 % Cr2O3 %  
#DIV/0! 1.462

0.001333 8.284667

#DIV/0! 3.47225

#DIV/0! 5.398154

#DIV/0! 14.80275

#DIV/0! 0.001013

0.0012 8.772

0.002667 28.75267