

075

GEOPHOTO RESOURCES CONSULTANTS

Millaquin House
Herschel Street, Brisbane 4000
Telephone 27320



CHEMICAL LABORATORY
4th Floor Red Comb House
Roma Street, Brisbane 4000
Telephone 21 3875

GEOCHEMICAL LABORATORY REPORT

FIELD SHEET No. 007950 PROJECT No. EL.7/68 - DUNDAS GREAT SOUTH COMET MINE

LAB. SHEET No. 1056/2 SAMPLE TYPE: ROCK DATE: 25th July, 1972.

SAMPLE No.	LAB. No.	Pb ppm	Zn ppm	Ag ppm	Cd ppm				
SCM 28A	72-G-326	0.33%	0.25%						
SCM 28B	72-G-327	0.45%	0.20%						
SCM 28C	72-G-328	0.29%	0.70%						
SCM 46A 2	72-G-329	1200	3.4%			185			
SCM 46B 2	72-G-330	0.28%	1.65%			95			
SCM 46C 2	72-G-331	0.57%	1.8%	11		95			
SCM 46D	72-G-332	1450	1550						
SCM 46E	72-G-333	0.25%	1950						
SCM 47A 2	72-G-334	0.45%	5.2%	15		290			
SCM 47B 2	72-G-335	0.30%	3.0%	10		180			
SCM 47C 1	72-G-336	500	3.3%			160			
SCM 48A 2	72-G-337	0.31%	1.35%	10		75			
SCM 48B 2	72-G-338	0.51%	0.68%	10					
SCM 48C 1	72-G-339	0.43%	1.4%			85			
SCM 52A 1	72-G-340	2.55%	1.1%	64		65			
SCM 52B	72-G-341	0.27%	0.35%						
SCM 52C	72-G-342	0.27%	0.27%						
SCM 56A 1	72-G-343	0.43%	0.35%						
SCM 56B 1	72-G-344	1.86%	12.3%	64		580			
SCM 56C 1	72-G-345	3.7%	13.1%	77		630			
SCM 63A 1	72-G-346	0.69%	0.68%	12					
SCM 63B 1	72-G-347	0.89%	2.9%	22		175			
SCM 63C 1.5	72-G-348	0.43%	2.7%	14		170			
SCM 63D 1	72-G-349	3.7%	8.7%	61		380			
SCM 63E 1	72-G-350	0.74%	3.25%	20		170			
SCM 82A 1	72-G-351	600	1600						
SCM 82B 1	72-G-352	0.51%	0.75%						
SCM 82C 1	72-G-353	0.92%	1.65%	16		90			
SCM 83A 1	72-G-354	0.43%	2.0%						
SCM 83B 2	72-G-355	0.84%	4.4%	18		205			
SCM 83C 1.5	72-G-356	1.26%	3.45%	22		195			
SCM 84A 2	72-G-357	0.23%	1.2%			70			
SCM 84B 2	72-G-358	1.63%	3.3%	28		170			
SCM 84C 2	72-G-359	0.50%	2.0%	10		110			
SCM 85A 1.5	72-G-360	0.74%	3.75%	18		205			
SCM 85B 1	72-G-361	0.85%	4.45%	18		245			
SCM 85C 1	72-G-362	1950	2.1%			100			
SCM 88A 1	72-G-363	0.23%	5.2%	12		270			
SCM 88B 1	72-G-364	0.30%	3.2%	10		150			
SCM 88C 1	72-G-365	0.56%	1.5%	12		80			
SCM 92A 1	72-G-366	2.7%	10.1%	48		490			
SCM 92B 1.5	72-G-367	1.62%	9.0%	26		480			
SCM 92C 1.5	72-G-368	1900	0.90%						
SCM 93A 1	72-G-369	2.95%	10.1%	40		550			
SCM 93B 1.5	72-G-370	1.16%	12.9%	32		660			
SCM 93C 1	72-G-371	3.9%	2.3%	42		135			

METHODS:



This laboratory is registered by the National Association of Testing Authorities, Australia. The tests reported herein have been performed in accordance with its terms of registration.

Ray W. M. [Signature]

Chief Chemist