

SAMPLE NO.	MISTY VALLEY LOCATION	DEPTH (m)	ASSAYS (p.p.m.)					
			Sn	Cu	Pb	Zn	Mn	Ag
M.V. 53	M.V. 425 ME	0-0.3	30	15	7	30	< 50	< 50
54	"	0.3-0.6	< 10	10	3	15	"	"
55	"	0.6-1.0	"	16	15	20	"	"
56	450 ME	0-0.3	40	60	< 10	30	< 10	"
57	"	0.3-0.6	25	20	"	10	< 50	"
58	475 ME	0-0.3	< 10	23	"	15	"	"
59	"	0.3-0.45	"	26	"	15	"	"
60	500 ME	0-0.3	"	15	"	15	"	"
61	"	0.3-0.6	25	15	"	10	"	"
62	"	0.6-0.8	25	20	"	9	"	"
63	525 ME	0-0.3	< 10	72	11	31	"	"
64	"	0.3-0.6	30	20	< 10	15	"	"
65	"	0.6-0.8	10	25	4	< 15	< 50	"
66	550 ME	0-0.3		Missing				
67	"	0.3-0.6	< 10	18	< 10	10	< 10	"
68	575 ME	0-0.3	25	170	15	35	"	"
69	600 ME	0-0.3	20	18	< 10	20	"	"
70	625 ME	0-0.3	60	450	60	125	10	"
71	650 ME	0-0.3	20	80	20	55	< 10	"
72	675 ME	0-0.3	175	180	65	60	25	"
73	700 ME	0-0.3	60	7	< 10	7	< 10	"
74	725 ME	0-0.3	< 10	13	"	29	"	"
MV 75	M.V.1 725 ME	0.3-0.6	25	32	10	20	< 10	< 50
76	750 ME	0-0.3	100	64	< 10	130	"	"
77	775 ME	0-0.3	15	24	"	20	"	"
78	800 ME	0-0.15	2000	30	"	35	"	"
79	825 ME	0-0.3	20	50	"	45	"	"
MV 80	850 ME	0-0.3	1300	40	"	26	"	"
81	875 ME	0-0.3	220	15	"	17	"	"
82	"	0.3-0.6	15	< 10	"	45	"	"
83	"	0.6-1.0	70	18	"	11	"	"
84	900 ME	0-0.3	15	15	"	14	"	"
85	"	0.3-0.6	20	< 10	"	25	"	"
86	925 ME	0-0.3	70	30	"	27	"	"
87	950 ME	0-0.3	< 10	20	"	19	"	"
88	"	0.3-0.6	20	15	"	60	"	"
89	975 ME	0-0.3	35	60	"	30	"	"
MV 90	"	0.3-0.45	70	20	"	20	"	"
91	1000 ME	0-0.15	200	30	"	30	"	"
92	1025 ME	0-0.3	80	20	"	14	"	"
93	"	0.3-0.45	80	5	"	20	"	"
94	1050 ME	0-0.3	160	13	"	15	"	"
95	1075 ME	0-0.3	15	31	"	15	"	"
96	"	0.3-0.45	20	16	"	5	"	"