

SAMPLE NO.	MISTY VALLEY LOCATION	DEPTH (m)	ASSAYS (p.p.m.)					
			Sn	Cu	Pb	Zn	Ni	As
4	50 ME	0-0.3	80	20	< 25	20	< 10	< 50
5	25 ME	0-0.15	90	10	"	30	"	100
6								
7								
MV 601	25 ME	0-0.3	40	20	< 25	30	< 10	< 50
2	"	0.3-0.5	50	20	"	30	"	"
3	50 ME	0-0.15	60	10	"	30	"	50
4	75 ME	0-0.3	40	10	"	30	"	< 50
5	"	0.3-0.45	45	10	"	50	10	"
6	100 ME	0-0.3	45	10	"	30	< 10	"
7	"	0.3-0.45	60	20	"	40	10	"
8	125 ME	0-0.3	60	20	25	60	10	50
9	"	0.3-0.45	50	20	< 25	40	< 10	< 50
MV 610	150 ME	0-0.3	50	10	25	30	"	"
1	"	0.3-0.6	70	30	30	40	"	"
2	"	0.6-0.85	80	60	30	50	30	60
3	175 ME	0-0.15	50	10	< 25	40	< 10	< 50
4	200 ME	0-0.3	30	20	"	40	10	"
5	"	0.3-0.6	35	20	50	30	< 10	"
6	"	0.6-1.0	45	20	30	30	"	"
7	"	1.0-1.4	40	10	< 25	20	"	"
8	225 ME	0-0.3	40	20	"	30	10	"
9	"	0.3-0.6	50	30	"	30	< 10	"
MV 620	"	0.6-0.8	70	40	"	30	"	50
1	250 ME	0-0.1	50	30	"	40	"	< 50
2	275 ME	0-0.3	35	40	25	30	20	"
3	"	0.3-0.45	60	40	< 25	40	10	"
4	300 ME	0-0.15	45	40	"	30	20	"
5	325 ME	0-0.2	45	40	"	30	10	"
6	350 ME	outcrop	120	120	"	80	30	60
7	375 ME	0-0.1	40	40	"	30	< 10	< 50
8	400 ME	0-0.15	60	30	"	30	< 10	"
9	425 ME	0-0.3	70	20	"	40	"	50
MV 630	"	0.3-0.6	60	30	"	30	"	60
1	"	0.6-0.9	70	40	"	20	"	90
2	"	0.9-1.2	70	30	"	20	10	80
3	"	1.2-1.4	60	60	"	20	< 10	120
4	450 ME	0-0.15	60	40	"	40	50	< 50
5	475 ME	0-0.3	45	30	"	40	20	50
6	"	0.3-0.6	70	70	"	100	20	70
7	"	0.6-1.0	60	110	"	90	30	60
MV 638	475 ME	1.0-1.2	70	170	< 25	180	70	50
39	500 ME	0-0.15	40	30	30	30	< 10	< 50
40	525 ME	0-0.2	45	50	40	60	10	50
MV 701	MV7 25 ME	0-0.2	20	10	< 25	50	10	< 50