

SAMPLE NO.	MISTY VALLEY LOCATION	DEPTH(m)	ASSAYS (p.p.m.)						
			Sn	Cu	Pb	Zn	Ag	Au	
2	50 ME	0-0.3	45	<10	25	50	<10	80	
3	75 ME	0-0.15	30	10	"	40	"	<50	
4	100 ME	0-0.25	<10	20	"	60	"	"	
5	125 ME	0-0.2	10	40	"	50	"	"	
6	150 ME	0-0.3	<10	20	"	40	"	70	
7	175 ME	0-0.3	60	20	25	30	10	<50	
8	"	0.3-0.6	60	40	30	30	<10	90	
9	"	0.6-0.85	45	40	60	30	10	120	
MV 710	200 ME	0-0.15	30	20	<25	20	<10	50	
11	225 ME	0-0.3	35	20	25	20	"	80	
12	"	0.3-0.45	35	30	<25	20	"	90	
13	250 ME	0-0.3	45	20	"	20	20	60	
14	"	0.3-0.6	45	20	"	20	<10	60	
15	"	0.6-0.9	40	30	"	30	10	60	
16	275 ME	0-0.3	60	30	"	100	70	70	
17	"	0.3-0.5	70	20	"	340	100	70	
18	300 ME	0-0.1	40	20	"	40	10	<50	
19	325 ME	0-0.1	100	10	"	30	10	50	
MV 720	350 ME	0-0.3	35	20	50	50	20	<50	
21	"	0.3-0.5	50	30	25	50	10	70	
22	375 ME	0-0.1	45	30	40	60	30	60	
23	400 ME	0-0.3	70	40	<25	100	40	70	
24	"	0.3-0.35	60	40	25	80	30	80	
25	425 ME	0-0.3	35	50	25	70	10	<50	
6	"	0.3-0.6	30	60	<25	70	20	"	
7	450 ME	0-0.3	20	60	"	60	20	"	
8	"	0.3-0.4	35	70	"	80	30	"	
9	475 ME	0-0.1	30	50	"	60	20	"	
MV 730	500 ME	0-0.2	40	50	"	50	20	"	
1	525 ME	0-0.15	10	50	"	60	20	"	
2	550 ME	0-0.1	35	120	"	60	20	"	
3	575 ME	0-0.1	40	70	50	50	10	"	
4	600 ME	0-0.15	45	30	30	50	20	"	