

083

572064

Sample No	Location + Depth	Seam Fracture #	Cu	Zn	Pb	Mn	As	Pb	W	Sn	
366	M.L. 12	2175mN	+10	240	22	12	4	960	12	95	300
		0-0.3m	-10 +85	210	22	15	3	740	10	130	370
			-85	200	28	15	5	600	10	75	280
367		2175mN	+10	310	28	15	7	840	10	95	310
		0.3-0.6m	-10 +85	240	22	15	3	780	8	90	350
			-85	260	25	<10	3	660	12	50	250
368		2175mN	+10	390	42	"	6	560	6	60	310
		0.6-1.0m	-10 +85	370	35	"	3	620	4	80	290
			-85	450	48	10	3	380	4	35	80
369		2150mN	+10	450	32	10	4	960	12	240	2050
		0-0.3m	-10 +85	460	35	10	<3	950	6	150	1750
			-85	370	42	20	3	800	10	170	1650
370		2150mN	+10	690	32	50	4	1800	8	120	2000
		0.3-0.6m	-10 +85	590	35	35	3	1150	8	200	2000
			-85	430	45	15	4	920	12	180	1600
371		2150mN	+10	860	35	15	5	1200	8	140	1750
		0.6-1.0m	-10 +85	800	32	30	3	1000	8	230	2200
			-85	750	38	20	5	950	16	220	1900
372		2150mN	+10	700	35	<40	3	700	14	35	4400
		1.0-1.1m	-10 +85	720	35	"	<3	710	16	70	3300
			-85	680	42	10	3	700	20	55	3900
373		2125mN	+10	160	32	45	5	2400	8	430	470
		0-0.3m	-10 +85	150	30	50	4	1600	10	500	750
			-85	140	35	50	4	1600	8	740	740
374		2125mN	+10	230	35	45	6	3550	6	560	1050
		0.3-0.6m	-10 +85	190	32	60	3	2000	8	900	900
			-85	200	35	55	3	2100	4	840	740
375		2125mN	+10	430	45	40	5	1850	6	640	1950
		0.6-1.0m	-10 +85	360	40	60	3	2000	8	800	1400
			-85	470	55	65	3	2150	10	700	1350
376		2125mN	+10	740	50	55	3	2200	6	400	2200
		1.0-1.1m	-10 +85	690	480	70	3	2000	12	530	1900
			-85	970	70	65	4	1950	10	430	1700
377		2100mN	+10	85	42	"	3	110	8	20	95
		0-0.3m	-10 +85	55	30	"	3	38	12	<10	48
			-85	60	40	"	4	55	12	10	90