

Sample No.	F ppm	W ppm	Bi ppm	Mo ppm	Au ppm	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Ni ppm
07/0705/01	3600	60	25	10	ND	3.3	-10	30	100	55
02	8.80%	1100	645	10	-0.10	3.3	145	30	185	70
03	4400	ND	115	-10	-0.10	2.2	-10	35	65	65
04	11.50%	775	475	10	0.13	3.3	-10	30	330	55
05	9.0 %	120	95	-10	0.15	2.2	15	25	345	35
06	12.2 %	870	680	10	0.15	3.3	190	25	250	20
07	19.0 %	460	480	-10	0.11	1.8	120	30	360	20
08	12.8 %	2145	285	35	-0.10	2.8	10	30	120	55
09	0.8 %	120	15	ND	-0.10	ND	10	20	25	155
10	8.5 %	1240	235	-10	0.10	2.2	-10	30	430	60
11	8.4 %	3120	50	45	-0.10	2.8	15	30	240	70
12	13.0 %	220	415	20	0.19	2.2	20	35	200	20
13	9.0 %	720	1040	-10	0.16	2.4	115	25	500	25
14	6.6 %	1630	80	-10	0.22	1.7	-10	25	145	75
15	2.0 %	415	60	-10	0.11	3.5	-10	20	340	45
16	3.4 %	3680	435	20	0.11	2.2	145	135	1160	65
17	0.6 %	415	135	-10	-0.10	1.8	45	385	340	145
18	4600	70	165	-10	-0.10	1.1	-10	30	70	65
19	2200	25	125	ND	0.10	1.3	-10	35	115	45
20	2000	160	270	ND	-0.10	1.1	10	25	90	70
21	1400	ND	275	ND	2.90	1.8	-10	85	70	60
22	1100	ND	2635	ND	2.57	4.0	-10	865	50	45
23	500	10	800	ND	0.23	2.4	-10	365	50	45
24	400	ND	30	ND	-0.10	ND	10	25	15	155
07/0705/29				-10	-0.10	0.36	-10	20	140	Sb 10
30				560	-0.10	0.60	-10	10	90	Sb 15

NOTE: -10 means less than 10