GEOEX PTY. LTD.

221153

152

Submitted by G. WESTE
Company COMALCO
Area
Date Submitted 8.9.75
Date Tested 9-11.9.75
Tested by T. Wilson

PHYSICAL PROPERTY ROCK TEST

x	Description WRIGGLITE	Wet Density (gm/cc)	Dimensions: Cross Section X x Y or diam. (sq cm)	Dimensions: Length between measuring electrodes (cm)	Magnetic Susceptibility c.g.s. units	Resistance ohms. (KΩ)	Resistivity Freq 5.0 / 0.31 (Ω metres)	P.F.E. (%) Freq 5.0 / 0.31	Metal Factor
1	Sample too small 197'6" - 200' M2	3.79	3.8	2.9	-	35.6	466.0	26.5	57.0
2	"	3.58	4.0	6.8	47,369.9	509.2	2995.0	16.8	5.6
3	Sample too large	3.44	5.7	3.3	-	58.4	1008.0	24.6	24.0
4	"	3.84	3.92	6.4	87,598.7	176.0	1078.0	35.9	33.0
5	"	3.14	4.5	4.3	5,951.0	2000.0	20930.0	2.0	0.09
6	"	3.77	4.6	6.7	86,322.0	270.0	1853.0	22.1	12.0
7	"	3.57	4.5	7.7	55,485.0	1037.2	6061.0	9.5	1.6

NOTE: 1–7 are different pieces of wrigglite core from ML2 over the interval 197'6 – 200'