

E.L. 7/74 "MOINA"

-3-

Mineral analysis data from bore core samples

Bore No.	Feet		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	F %	Ag ppm	Au ppm	Sb ppm	Ta ppm	V ppm	Co ppm	Ni ppm	Remarks	
	Depth From	To																			
ML 1A	218.00	219.00		15	25	-10		25		55		0.13									
1A	219.00	225.50		35	20	20		-10		75		0.13									
1A	228.00	228.50		15	15	15		-10	-10	45		0.15	-10								
1A	260.00	260.50		35	-10	15		15	-10	80		0.05	-10								
1A	272.50	273.00		90	-10	25		1190	20	120		0.18	1.3								
1A	280.00	280.50		35	-10	(-1) 10	(1)	(5) -10	25	40	1*	0.03	(0.1)-10	(-3)	-30	-100	-10	-5	100		
1A	738.25	738.33		15	-10	-10		-10	10	-10		0.05	-10								
1A	746.50	747.00		15	-10	25		-10	340	-10		0.58	-10								
1A	755.00	755.50		30	10	(5) 35	(50) -10	(5) -10	30	30	1*	0.98	(0.1)-10	(-3)	-30	-100	-10	-5	50		
1A	764.00	764.50		-10	-10	15		-10	-10	10		0.13									
1A	774.50	775.00	See note (3)	500	-10	15		-10	265	30		0.35	0.7								
1A	784.33	784.83		65	-10	10		-10	40	400		0.84	-0.5								
1A	798.33	798.83		25	185	20		-10	20	20		0.56	-0.5								
1A	807.33	807.83		20	89	(3) 20	(10)	(3) -10	25	-10	3*	0.32	(0.1)-10	(-3)	-30	-100	-10	-5	50		
1A	826.00	826.50		15	930	-10		-10	-10	-10		0.58	-10								
1A	835.50	836.00		10	240	10		-10	-10	-10		0.39	-10								
1A	845.00	845.50		-10	180	-10		-10	15	-10		0.49	-10								
1A	854.00	854.50		-10	40	(-1) -10	(3)	(200) -10	-10	-10	3*	0.38	(0.1)-10	(-3)	-30	-100	-10	-5	150		
1A	862.00	862.50		20	25	-10		-10	10	-10		0.50	-10								
1A	866.50	867.00		20	10	-10		-10	20	-10		0.42	-10								
DETECTION LIMIT				(10)	(10)	(10)	(4)	(10)	(10)	(10)		(0.02)	(2)								
METHOD OF ANALYSIS				COM-ALCO AAS	COMALCO COLORI-METRIC	COM-ALCO AAS	AMDEL XRF SCHEME B1	COMALCO AAS			AMDEL SPECTRO	COMALCO FUSION SIE	COM-ALCO AAS	AMDEL FIRE ASSAY	AMDEL SPECTROGRAPHIC SCHEME A1, A2						

NOTES:- (1) Analyses in brackets() are semi-quantitative spectrographic by Amdel.
 (2) Be analyses of bulk samples are by an Amdel chemical method. Values of Be marked * may be too low by a factor of about 10.
 (3) See separate page for analyses of a separate suite of granite-greisen samples after 774 ft.