

E.L. 7/74 "MOINA"

Mineral analysis data from bore core samples

Bore No.	Depth Feet		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	F %	Ag ppm	Au ppb	Sb ppm	Ta ppm	V ppm	Co ppm	Ni ppm	Remarks	
	From	To																			
ML 3A	357.50	359.00		25	280	600		130		115		11.40									
3A	359.00	359.50		30	105	230	1200	60	30	140		12.00	2.3								
3A	360.00	362.00		30	70	1290		95		110		10.50									
3A	362.00	364.00		30	485	640		85		120		11.10									
3A	364.00	364.50		30	75	230	2000	180	30	150		11.90	2.3								
3A	364.50	366.50		20	95	370		75		115		12.20									
3A	366.50	369.50		20	120	200		180		140		11.90									
3A	369.50	370.00		20	40	470	2900	155	15	165		12.00	2.2								
3A	370.00	372.00		20	360	165		500		135		12.80									
3A	372.00	373.00		15	635	340		550		135		6.00									
3A	373.00	373.50		30	330	315	3200	490	195	185	370	11.30	1.6								
3A	373.50	375.50		-10	190	55		1020		95		2.50									
3A	375.50	377.00		25	105	660		50		135		12.70									
3A	377.00	377.50		30	185.5	55	8100	2075	35	200		2.90	1.4								
3A	377.50	380.00		10	130	50		1100		160		2.20									
3A	380.00	381.00		20	105	350		700		190		1.30									
3A	381.00	381.50		35	140	560	2800	380	265	255		1.32	1.6								
3A	381.50	383.00		20	150	400		450		190		2.00									
3A	383.00	385.00		20	120	680		320		205		1.80									
3A	385.00	385.50		35	70	310	5800	90	280	225		1.60	1.4								
3A	385.50	388.00		15	25	450		75		175		2.40									
3A	388.00	390.00		20	130	445		110		225		3.40									
3A	390.00	390.50		20	310	30	6200	500	30	215	35	2.50	1.4								

403.5 Bulked sample XRF Andel 1300 ppm to 342

403.5 Bulked sample XRF Andel 280 ppm to 342

403.5 Bulked sample Chemical Andel 280 ppm to 342

403.5 Bulked sample fire assay K4/2 Andel to 342 0.015 ppm