

221386

E.L. 7/74 "MOINA"

-6-

Mineral analysis data from bore core samples

Bore No.	Depth		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	F %	Ag ppm	Au	Sb ppm	Ta ppm	V ppm	Co ppm	Ni ppm	Remarks	
	From	To																			
ML 3A	490.00	490.50		40	-10	(3) 40	500	25	-10	70	10*	1.00	(-0.1) 1.0	-3 ppm	-30	-100	10	-5	20		
3A	490.50	492.00		20	25	25		-10		65		0.83									
3A	492.50	497.00		20	170	45		300		70		3.5									
3A	495.00	495.50		40	-10	40		15	-10	55		1.21	1.4								
3A	495.50	497.00		20	65	25		10		55		0.77									
3A	497.00	499.00		20	20	25		10		40		0.46									
3A	499.00	499.50		40	3040	30		200	-10	50		1.00	0.9								
3A	499.50	502.00		20	10	25		-10		40		0.31									
3A	502.00	504.00		15	15	25		-10		40		0.32									
3A	504.00	504.50		40	45	35		15	-10	55		0.58	1.5								
3A	504.50	506.50		20	20	25		-10		40		0.34									
3A	506.50	509.00		15	15	25		-10		35		0.17									
3A	509.00	509.50		20	-10	(-1) 30	500	10	-10	25	1*	0.23	(-0.1) 1.0	-3 ppm	-30	-100	20	-5	20		
3A	509.50	511.50		15	-10	25		-10		55		0.19									
3A	510.00	510.50		50	-10	35		-10	-10	40		0.17	1.4								
3A	510.50	512.00		25	55	30		-10		65		0.36									
3A	511.50	514.00		25	70	25		-10		50		0.19									
3A	512.50	514.00		25	485	25		60		70		0.78									
3A	514.50	517.50		20	255	25		30		45		0.37									
3A	515.00	515.50		30	-10	40		15	-10	55		1.00	1.4								
3A	517.50	519.00		25	205	25		110		55		0.74									
3A	519.50	521.50		25	55	25		10		50		1.30									
3A	520.00	520.50		40	50	45		20	-10	50		1.40	1.6								

to 478

to 478

to 478

to 478

Bulked sample XRF Andel 190 ppm

Bulked sample XRF Andel 330 ppm

Bulked sample Chemical Andel 60 ppm

Bulked sample Andel fire assay K4/2 0.12 ppm

Continued...../7.