

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	AAS Au ppm	Au Fire Assay ppm	Remarks
	From	To														
SMD 5	38.10	39.80		34	-10	16	80	-4	28	170	30	0.45				
5	39.80	40.67		6	270	380	660	4	200	1740	250	10.5	-1	0.10	0.075	
5	40.67	42.00		12	490	580	1350	10	75	95	250	17.0				
5	42.00	43.00		14	740	700	860	16	210	100	300	16.5				
5	43.00	44.00		10	1750	320	1400	14	320	70	200	18.0	-1	0.05		
5	44.00	45.00		12	680	620	1050	34	170	65	200	17.0				
5	45.00	46.60		24	900	1100	1500	44	70	70	200	14.0				
5	46.60	47.50		10	170	44	250	-4	22	70	70	4.5				
5	47.50	48.85		6	480	28	500	-4	12	90	100	4.7	-1	0.05		
5	48.85	50.00		14	490	80	1100	-4	10	85	300	15.0				
5	50.00	51.30		65	540	820	1250	16	200	110	250	13.5				
5	51.30	52.80		20	780	760	940	8	150	200	250	12.5				
5	52.80	53.30		12	430	65	760		430	50	250	12.5	-1	-0.05	0.035	
5	53.30	54.50		18	380	140	720	16	75	60	250	9.8				
5	54.50	55.90		20	620	160	880	22	22	65	200	11.0				
5	55.90	56.35		12	760	10	320	22	20	30	100	4.5				
5	56.35	57.45		44	110	700	540	36	15	40	100	2.5				
5	57.45	57.90		12	3350	34	740	18	85	150	250	9.9				
5	57.90	58.70		8	780	180	820	38	140	90	300	10.5				
5	58.70	60.00		12	700	270	1250	34	60	60	200	15.8				
5	60.00	60.85		10	560	220	1250	14	190	75	250	14.5				
5	60.85	62.00		6	1050	8	3800	120	42	48	100	11.0				
5	62.00	72.90		6	470	6	390	30	5	48	100	5.3				
5	72.90	74.40		8	170	24	75	4			100	2.4				
DETECTION LIMIT				(4)	(10)	(4)	(4)	(4)			(1)		(1)	(0.05)	(.005)	
METHOD OF ANALYSIS - All by AMDEL				X-RAY FLUORESCENCE SCHEME B1					CODE C1				CODE C2	AAS CODE C3	Fire Assay Code K4 '2	