

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	Au ppm	Remarks
	From	To													
SMD 6	21.35	22.75		8	130	360	1600	-4	150	270	250	18.0			
6	22.75	23.50		14	580	640	1850	-4	170	310	200	19.0			
6	23.50	24.75		6	450	310	2000	-4	35	120	250	17.5			
6	24.75	26.15		12	640	400	1950	-4	95	100	250	19.4			
6	26.15	28.00		14	540	290	1050	-4	15	90	150	8.4			
6	28.00	29.15		10	720	440	2050	-4	28	130	150	16.0			
6	29.15	29.50		10	720	360	1250	6	38	130	150	28.5			
6	29.50	30.80		12	410	560	1950	-4	50	120	250	19.5			
6	30.80	32.15		14	230	290	760	6	12	50	300	8.6			
6	32.15	33.90		14	1050	880	1950	8	190	120	250	21.5			
6	33.90	34.50		16	380	390	1750	-4	10	42	200	9.2			
6	34.50	35.50		18	660	660	2100	-4	15	100	250	20.0			
6	35.50	36.40		12	700	880	3350	10	35	110	250	16.0			
6	36.40	38.00		12	480	640	2050	6	32	100	250	15.5			
6	38.00	39.00		20	640	210	2550	12	30	100	500	15.0			
6	39.00	40.00		12	860	900	1700	90	90	90	500	24.5			
6	40.00	41.00		12	1550	400	2700	80	35	60	300	21.5			
6	41.00	42.00		4	2650	680	1150	160	160	100	250	30.0			
6	42.00	43.00		6	4600	600	1300	110	50	120	250	30.0			
6	43.00	44.00		10	860	660	1200	75	48	140	250	24.5			
6	44.00	45.00		10	1100	470	1500	90	18	140	300	24.5			
6	45.00	46.00		12	600	700	1100	16	18	120	300	23.0			
6	46.00	47.00		6	980	700	1400	-4	15	150	200	20.5			
6	47.00	48.00		6	740	600	1100	16	18	160	200	20.5			
6	48.00	49.00		-4	940	600	1150	170	8	160	250	25.0			
6	49.00	50.00		8	1050	680	1050	14	18	160	300	24.5			
6	50.00	51.00		4	740	600	1050	24	32	220	150	15.5			
6	51.00	52.00		6	880	470	900	4	8	170	150	17.0			
6	52.00	53.00		-4	860	620	1000	-4	10	200	200	17.5			
6	53.00	54.00		12	840	440	1250	10	85	200	250	17.5			
6	54.00	55.00		-4	1000	390	1200	26	28	140	250	19.0			
6	55.00	56.00		10	1750	600	1650	34	85	110	200	20.5			
6	56.00	57.00		6	700	330	1700	42	28	110	200	16.0			