

E.L. 7/74 "Moina"

Mineral analysis data from bore core samples

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	Au ppm	Remarks
	From	To													
SMD 7	00.00	01.00		16	880	680	2750	22	38	510	100	10.5			
7	01.00	08.00		14	800	420	2350	-4	12	280	100	25.5			
7	08.00	09.62		14	880	640	1400	-4	15	220	100	28.0			
7	09.62	11.00		4	1350	640	1350	16	28	250	100	28.0			
7	11.00	12.00		6	780	420	1650	-4	12	270	250	26.5			
7	12.00	13.00		6	330	390	1900	-4	10	360	200	21.5			
7	13.00	14.00		8	580	440	1550	4	12	370	200	21.5			
7	14.00	16.00		10	840	490	1300		20	370	200	23.5			
7	16.00	17.00		4	290	340	1300	16	10	320	300	17.7			
7	17.00	18.00		6	660	260	1400	6	2	270	200	19.5			
7	18.00	19.00		18	1100	320	1550	12	5	130	300	21.5			
7	19.00	20.00		14	840	540	1600	22	85	370	300	25.0			
7	20.00	21.00		8	800	640	1500	38	10	270	250	28.0			
7	21.00	21.75		6	920	470	2200	28	5	570	300	27.0			
7	21.75	22.65		16	390	130	2400	16	5	120	250	9.9			
7	22.65	24.00		12	1000	580	1800	20	5	170	300	22.5			
7	24.00	25.00		12	1550	420	1800	80	120	9800	200	24.5			
7	25.00	26.00		16	400	940	1300	30	230	740	200	20.5			
7	26.00	27.00		8	680	920	1500	26	440	450	200	21.5			
7	27.00	28.00		8	920	580	2500	60	220	410	250	22.5			
7	28.00	29.00		12	860	460	2250	95	85	310	250	22.0			
7	29.00	30.00		4	840	520	1700	46	110	1870	200	17.0			
7	30.00	31.00		8	1850	350	1400	46	38	180	250	23.0			
7	31.00	32.00		12	500	350	1050	50	110	160	200	23.0			
7	32.00	33.00		18	2150	390	2250	48	200	190	150	19.5			
7	33.00	34.00		-4	1300	240	2300	55	8	150	150	21.5			
7	34.00	35.00		12	720	680	1450	30	32	120	250	23.5			
7	35.00	36.00		14	940	230	2850	46	40	210	150	14.0			
7	36.00	37.00		12	1100	300	1800	70	60	110	200	20.5			
7	37.00	38.00		14	1950	470	880	70	130	110	300	22.0			
7	38.00	39.00		10	4500	500	1050	230	95	110	250	23.0			
7	39.00	40.00		4	3050	620	920	290	50	120	200	22.5			
7	40.00	41.00		8	1400	520	1000	80	55	170	300	21.0			