

E.L. 7/74 "Moina"

- 9 -

Mineral analysis data from bore core samples

| Bore No. | Depth Metres | | Log | Pb ppm | W ppm | Bi ppm | Sn ppm | Mo ppm | Cu ppm | Zn ppm | Be ppm | CaF ₂ % | Ag ppm | Au ppm | Remarks | |
|--------------------|--------------|-------|-----|------------------------------|-------|--------|--------|---------|--------|--------|--------|--------------------|---------|--------|---------|--|
| | From | To | | | | | | | | | | | | | | |
| SMD 8 | 40.00 | 41.00 | | 30 | 15 | 34 | 40 | -4 | 20 | 70 | 50 | 0.35 | | | | |
| 8 | 41.00 | 41.60 | | 6 | -10 | 8 | 95 | 4 | 8 | 220 | 30 | 0.25 | | | | |
| 8 | 41.60 | 42.50 | | 6 | 15 | -4 | 85 | 4 | 20 | 430 | 20 | 0.3 | | | | |
| 8 | 42.50 | 43.20 | | -4 | 20 | 4 | 95 | -4 | 5 | 350 | 30 | 0.25 | | | | |
| 8 | 43.20 | 44.00 | | 50 | 30 | 32 | 140 | -4 | 8 | 570 | 50 | 0.25 | | | | |
| 8 | 44.00 | 45.95 | | 170 | 45 | 140 | 300 | -4 | 10 | 380 | 70 | 0.65 | | | | |
| 8 | 45.95 | 46.35 | | 12 | 140 | 540 | 240 | -4 | 30 | 120 | 80 | 15.5 | | | | |
| 8 | 46.35 | 47.00 | | 16 | 50 | 480 | 390 | 4 | 12 | 120 | 100 | 6.2 | | | | |
| 8 | 47.00 | 48.00 | | 14 | 100 | 230 | 250 | -4 | 40 | 110 | 150 | 4.9 | | | | |
| 8 | 48.00 | 49.60 | | 14 | 70 | 44 | 36 | 4 | 110 | 48 | 70 | 2.2 | | | | |
| 8 | 49.60 | 50.50 | | 10 | 15 | -4 | 6 | 4 | 28 | 22 | 30 | 0.45 | | | | |
| 8 | 50.50 | 51.70 | | -4 | 10 | 4 | 14 | 4 | 28 | 28 | 30 | 0.60 | | | | |
| 8 | 51.70 | 52.50 | | 16 | -10 | 4 | 38 | -4 | 45 | 60 | 40 | 0.65 | | | | |
| DETECTION LIMIT | | | | (4) | (10) | (4) | (4) | (4) | | | (1) | | (1) | (0.05) | | |
| METHOD OF ANALYSIS | | | | X-RAY FLUORESCENCE SCHEME B1 | | | | CODE C1 | | | | CODE C2 | CODE C3 | | | |