

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	Au ppm	Remarks
	From	To													
SMD 9	91.50	92.50		10	240	130	880	6	240	250	300	14.5			221400
9	92.50	94.20		12	310	100	1700	12	320	250	250	11.0			
9	94.20	95.00		14	220	490	120	4	820	360	700	16.0			
9	95.00	96.00		14	390	330	410	6	510	310	400	11.0			
9	96.00	97.00		6	260	380	130	6	470	340	300	15.0			
9	97.00	98.00		14	420	430	100	-4	630	460	700	16.0			
9	98.00	99.00		22	280	580	140	-4	640	360	200	15.5			
9	99.00	100.00		16	400	600	540	-4	380	750	700	15.0			
9	100.00	101.00		-4	290	130	380	-4	250	230	100	6.2			
9	101.00	102.00		12	260	300	75	-4	910	290	200	14.5			
9	102.00	103.00		6	290	270	170	-4	670	300	150	8.7			
9	103.00	104.00		4	290	680	95	-4	880	200	250	7.9			
9	104.00	104.60		8	260	290	860	-4	400	250	200	9.4			
9	104.60	105.20		70	180	75	470	-4	18	1850	80	2.7			
9	105.20	106.50		22	60	12	270	8	2	180	100	1.6			
9	106.50	107.65		16	30	16	480	4	5	130	30	0.65			
9	107.65	108.40		16	15	16	760	-4	8	180	30	0.55			
9	108.40	109.00		44	10	90	860	-4	5	120	50	0.4			
9	109.00	110.00		44	25	65	860	-4	22	260	50	2.0			
9	110.00	111.00		50	25	140	960	-4	8	130	200	6.0			
9	111.00	112.00		50	25	130	960	-4	15	180	200	3.7			
9	112.00	113.15		680	130	1500	640	-4	95	230	150	10.5			
9	113.15	113.75		480	560	800	720		120	740	150	12.5			
9	113.75	115.00		55	180	160	490	-4	10	180	150	9.4			
9	115.00	116.00		50	210	80	800	12	15	210	200	8.0			
9	116.00	117.00		190	200	3400	520	-4	28	65	200	7.2			
9	117.00	118.00		640	180	7900	540	-4	65	200	150	8.1			
9	118.00	118.65		42	100	65	640	8	28	340	300	5.8			
9	118.65	122.00		80	40	65	120	-4	45	340	80	63.5			
9	122.00	123.00		75	120	42	110	-4	28	310	30	44.5			
9	123.00	125.00		10	40	160	340	-4	65	100	200	35.0			
9	125.00	126.00		12	230	6	290	14	15	130	50	3.7			
9	126.00	127.00		14	210	10	180	18	18	90	40	4.4			