

303

Bore No.	Depth From	Metres To	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF <sub>2</sub> %	Ag ppm	Au ppm	Remarks
SMD 10	67.00	68.00	18	360	330	2350	16	32	90	250	13.5			221403
10	68.00	69.00	18	620	460	3300	24	20	95	300	16.0			
10	69.00	70.00	16	1150	700	1450	55	40	95	500	25.9			
10	70.00	71.00	18	780	500	1250	34	40	130	500	25.5			
10	71.00	72.00	18	740	780	1550	60	55	110	500	22.5			
10	72.00	73.25	16	1450	480	1200	42	18	110	300	22.5			
10	73.25	73.60	500	1.31%	5.90%	4.10%	220	200	48	500	11.5			
10	73.60	75.00	32	900	1900	2200	26	65	90	300	15.5			
10	75.00	76.00	20	760	450	1400	24	90	90	500	17.5			
10	76.00	77.00	14	200	140	340	8	60	45	200	4.5			
10	77.00	78.00	24	100	180	920	8	8	70	250	4.4			
10	78.00	79.00	22	170	420	1050	6	10	80	70	5.0			
10	79.00	80.90	22	480	350	1050	38	60	180	500	14.5			
10	80.90	82.20	10	3200	270	2150	150	190	28	250	5.8			
10	82.20	83.35	16	640	220	1200	8	50	65	500	23.0			
10	83.35	84.40	22	180	80	460	6	50	55	200	8.8			
10	84.40	85.85	18	380	260	1050	14	120	60	300	21.5			
10	85.85	86.60	16	130	470	7000	130	710	38	50	14.0			
10	86.60	87.50	14	250	300	660	6	48	65	200	22.5			
10	87.50	88.50	12	240	390	480	4	38	65	200	14.5			
10	88.50	89.50	18	410	320	450	42	25	40	150	8.5			
10	89.50	90.50	6	320	75	230	100	55	70	70	9.8			
10	90.50	91.50	4	280	22	100	95	8	40	70	6.6			
DETECTION LIMIT			(4)	(10)	(4)	(4)	(4)	(2)	(1)	(1)		(1)	(0.05)	
METHOD OF ANALYSIS			AMDEL		X-RAY FLUORESCENCE SCHEME B1			AAS CODE C1		SPECTRO		CODE C2	CODE C3	