

E.L. 7/74 "Moina"

-2-

Mineral analysis data from bore core samples

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	Au ppm	Remarks	
	From	To														
SMD 11	56.00	57.00		20	680	500	1250	46	220	95	300	22.0				
11	57.00	58.00		20	540	410	1350	38	110	110	300	14.5				
11	58.00	59.00		18	1400	390	1150	36	170	75	300	12.5				
11	59.00	60.00		16	900	540	1250	30	200	75	250	16.5				
11	60.00	60.70		10	6500	210	1200	370	80	65	500	23.0				
11	60.70	61.70		12	1000	40	620	80	10	55	70	11.0				
11	61.70	63.10		22	640	360	1600	90	70	48	200	13.0				
11	63.10	64.00		24	1650	560	1250	65	240	60	300	9.1				
11	64.00	65.00		18	1200	240	1700	65	220	65	300	14.0				
11	65.00	66.00		18	1100	280	1000	40	160	55	300	12.5				
11	66.00	67.00		20	470	490	1350	24	220	75	150	8.7				
11	67.00	68.00		16	820	190	2100	40	150	450	200	7.2				
11	68.00	68.50		65	540	260	1000	50	190	100	70	18.5				
11	68.50	69.20		30	50	180	1200	-4	20	90	70	4.2				
11	69.20	69.65		24	720	300	1800	70	270	60	150	11.5				
11	69.65	70.85		90	1100	18	620	85	10	50	150	9.6				
11	70.85	71.85		20	1100	12	920	12	10	65	200	11.0				
11	71.85	73.00		16	2300	36	2950	220	120	65	150	9.2				
11	73.00	74.00		12	900	8	1150	38	80	65	70	8.9				
DETECTION LIMIT				(4)	(10)	(4)	(4)	(4)	(2)	(1)	(1)					
METHOD OF ANALYSIS				ANDEL				X-RAY FLUORESCENCE SCHEME B1			AAS CODE C1		SPECTRO			