

221406

COMALCO EXPLORATION DEPARTMENT
TASMANIAN E.L. 7/74 "MOINA", SHEPHERD & MURPHY MINE AREA
Mineral analysis data from bore core samples

Bore No.	Depth Metres		Log	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF ₂ %	Ag ppm	Au ppm	Remarks	
	From	To														
SMD 12	90.50	91.50		20	15	10	16	-4	15	18	70	0.4				
12	91.50	92.90		12	10	46	190	-4	38	85	50	1.0				
12	92.90	94.00		18	170	460	390	16	240	110	500	11.9				
12	94.00	95.35		12	10	75	34	6	18	25	50	1.5				
12	95.35	96.00		26	10	40	170	12	5	55	150	4.3				
12	96.00	97.00		22	15	130	500	8	8	50	200	10.5				
12	97.00	98.00		26	260	330	980	8	330	90	500	22.0				
12	98.00	99.00		26	170	460	700	10	180	80	300	15.5				
12	99.00	100.00		26	300	580	720	18	230	100	300	20.5				
12	100.00	101.00		24	140	580	540	6	210	85	200	13.5				
12	101.00	102.00		22	270	500	540	-4	480	110	300	19.0				
12	102.00	103.00		38	75	310	430	-4	75	110	200	10.0				
12	103.00	104.00		38	40	400	780	6	220	120	150	7.8				
12	104.00	104.80		30	270	580	960	6	80	100	200	12.5				
12	104.80	106.00		20	15	130	1050	12	20	50	50	3.4				
12	106.00	107.00		24	55	310	380	4	18	48	70	4.4				
12	107.00	108.00		90	400	2300	270	34	50	38	70	4.4				
12	108.00	109.50		20	260	230	780	24	75	45	150	7.7				
12	109.50	110.50		10	55	28	130	-4	45	25	50	1.2				
12	110.50	111.50		10	75	22	38	8	38	22	50	1.8				
DETECTION LIMIT				(4)	(10)	(4)	(4)	(4)	(2)	(1)	(1)					
METHOD OF ANALYSIS				AMDEL				X-RAY FLUORESCENCE SCHEME B1			AAS CODE C1		SPECTRO			