

Despatch

COMALCO EXPLORATION DEPARTMENT  
TASMANIAN S.L. 7/74 "MOINA", SHEPHERD & MURPHY MINE AREA.  
Mineral analysis data from bore core samples

Bore No.	Depth m		Log	F %	Sn ppm	W ppm	Bi ppm	Mo ppm	Be ppm	Cu ppm	Pb ppm	Zn ppm	Cd ppm	In ppm	Ge ppm	Au ppm	Sc ppm	Ce ppm	Y ppm	Ta ppm	Remarks	
	From	To																				
SMD																						
13	7.00	9.00		-0.1	-4	-10	-10	-4	2	30	8	25	-1	4	-2	-0.05	5	-300	10	-100		
13	9.00	11.00		-0.1	-4	20	-10	4	3	42	32	100	-1	-4	-2	-0.05	10	-300	50	-100		
13	35.00	36.15		0.2	50	10	12	-4	40	60	25	270	1	4	-2	-0.05	5	-300	30	-100		
13	36.15	36.95		0.3	240	-10	240	-4	10	1080	22	250	-1	12	-2	4.5	5	-300	30	-100		
13	36.95	37.50		0.2	210	-10	-10	-4	10	140	70	130	-1	4	2	-0.05	10	-300	50	-100		
13	80.00	81.00		0.1	-4	15	-10	-4	3	10	18	420	-1	-4	-2	-0.05	10	-300	50	-100		
13	81.00	82.00		0.1	6	15	-10	-4	5	12	8	1420	2	-4	-2	-0.05	10	-300	50	-100		
13	82.00	83.00		0.1	-4	-10	-10	-4	5	2	8	410	-1	6	-2	-0.05	10	-300	20	-100		
13	83.00	83.70		0.1	-4	-10	-10	-4	10	12	8	290	-1	-4	-2	-0.05	15	-300	50	-100		
13	83.70	84.70		0.2	600	25	15	-4	30	8	18	130	-1	8	-2	-0.05	10	-300	20	-100		
13	84.70	85.50		0.3	490	25	18	-4	30	8	15	140	-1	6	-2	-0.05	5	-300	20	-100		
13	85.50	86.30		0.1	500	85	60	8	30	12	42	260	-1	4	-2	0.10	10	-300	30	-100		
13	86.30	87.35		0.6	720	55	1100	48	30	42	100	820	3	16	4	1.05	5	-300	20	-100		
13	87.35	88.50		0.1	470	10	650	-4	30	570	110	6.3%	230	48	3	0.30	10	-300	30	-100		
13	88.50	89.10		-0.1	360	-20	900	-4	50	640	110	13.8%	620	42	-2	0.50	10	-300	30	-100		
13	89.10	90.00		0.1	190	-50	660	-4	70	860	45	27.5%	1340	90	-2	0.80	5	-300	30	-100		
13	90.00	91.00		0.2	330	-20	1950	-4	40	760	38	14.5%	700	70	-2	1.35	5	-300	20	-100		
13	91.00	92.00		0.1	460	-20	1880	4	40	160	55	5.25%	210	32	5	0.80	15	-300	30	-100		
13	92.00	93.00		-0.1	430	-20	1720	-4	40	360	50	12.5%	490	46	-2	1.30	10	-300	30	-100		
13	93.00	94.00		-0.1	500	-20	1190	-4	10	460	55	11.5%	440	50	-2	0.65	10	-300	30	-100		
13	94.00	95.00		-0.1	520	-10	2100	4	20	340	85	8.5%	380	42	4	1.20	10	-300	20	-100		
13	95.00	96.00		-0.1	360	-20	1890	-4	30	470	55	13.0%	600	26	2	1.80	10	-300	20	-100		
13	96.00	97.00		-0.1	490	-10	250	-4	20	470	25	5.4%	210	20	2	0.35	15	-300	50	-100		
13	97.00	98.25		0.3	380	10	150	-4	80	18	28	4300	15	8	2	0.15	10	-300	10	-100		
13	98.25	99.25		0.6	500	20	90	-4	100	28	18	1.31%	40	10	-2	0.10	10	-300	20	-100		
13	99.25	100.25		0.2	370	-20	470	-4	70	380	38	7.75%	260	55	-2	0.50	5	-300	10	-100		
13	100.25	101.25		0.1	340	-20	320	4	70	910	28	10.4%	390	30	-2	0.30	10	-300	30	-100		
13	101.25	102.25		0.5	390	-10	42	10	30	580	21	7.0%	250	36	-2	0.15	10	-300	30	-100		