

Bore No.	Depth		Log	F	Sn	W	Bi	Mo	Be	Cu	Pb	Zn	Cd	In	Ge	Au	Sc	Ce	Y	Ta	Remarks
	From	To		%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	
SMD 13	102.25	103.25		0.6	440	-10	120	-4	50	310	25	4.65%	160	60	-2	-0.05	10	-300	30	-100	
13	103.25	104.00		0.7	500	10	220	-4	80	55	42	1.63%	55	36	2	-0.05	15	-300	30	-100	
13	104.00	105.00		0.5	560	15	25	-4	50	18	20	230	-1	10	2	-0.05	10	-300	20	-100	
13	105.00	106.00		0.5	580	20	40	-4	80	10	18	220	-1	14	2	-0.05	10	-300	50	-100	
13	106.00	107.00		0.5	520	30	38	4	100	10	18	220	-1	22	-2	-0.05	10	-300	50	-100	
13	107.00	108.00		0.3	490	20	22	-4	70	8	25	150	-1	10	4	-0.05	10	-300	30	-100	
13	108.00	109.00		0.5	580	10	-10	6	50	8	30	120	-1	-4	-2	0.10	10	-300	30	-100	
13	109.00	110.00		0.7	400	35	15	-4	100	8	25	160	-1	10	4	-0.05	20	-300	50	-100	
13	110.00	111.00		0.3	380	25	30	4	50	8	30	120	-1	10	-2	-0.05	10	-300	30	-100	
13	111.00	112.00		0.2	150	40	320	6	80	15	60	180	-1	-4	3	-0.05	20	-300	30	-100	
13	112.00	113.00		5.6	220	120	70	-4	200	18	22	280	-1	-4	-2	0.15	5	-300	30	-100	
13	113.00	114.00		0.5	240	20	55	8	200	8	38	190	-1	-4	-2	-0.05	10	-300	30	-100	
13	114.00	115.00		0.7	310	-10	28	-4	100	8	28	170	-1	-4	-2	-0.05	10	-300	30	-100	
13	115.00	116.00		0.2	210	-10	-10	4	70	8	25	160	-1	14	-2	0.05	10	-300	30	-100	
13	116.00	117.25		0.4	270	40	-10	-4	50	8	30	240	-1	4	-2	-0.05	10	-300	30	-100	
13	117.25	118.25		0.8	200	40	15	-4	70	8	15	160	-1	-4	2	0.10	5	-300	30	-100	
13	118.25	119.30		1.0	280	20	85	28	70	10	38	160	-1	4	-2	0.10	10	-300	50	-100	
13	119.30	120.30		1.0	100	-10	140	10	70	5	28	110	-1	-4	2	0.10	5	-300	50	-100	
13	120.30	121.30		2.1	140	150	18	16	70	2	15	150	-1	12	2	-0.05	5	-300	50	-100	
13	121.30	122.35		1.1	180	25	-10	34	70	5	12	120	-1	10	-2	-0.05	5	-300	50	-100	
13	122.35	123.12		0.8	250	25	-10	12	70	8	15	220	-1	8	-2	-0.05	10	-300	50	-100	
13	123.12	124.00		5.0	180	620	-10	70	500	15	18	250	-1	-4	5	-0.05	20	-300	70	-100	
13	124.00	131.00		0.4	10	30	-10	6	30	35	22	90	-1	-4	-2	0.05	20	-300	50	-100	
13	131.00	132.00		0.7	40	360	-10	6	50	60	18	65	-1	8	-2	-0.05	10	-300	50	-100	
13	132.00	133.00		1.7	8	1850	12	42	1000	32	25	140	-1	-4	-2	-0.05	20	-300	70	-100	
13	133.00	134.00		1.1	55	70	95	32	300	130	22	140	-1	6	3	0.05	20	-300	70	-100	
13	176.00	177.00		-0.1	16	15	-10	120	50	22	-5	42	-1	6	-2	-0.05	5	-300	20	-100	
13	177.00	178.00		-0.1	44	35	-10	8	30	42	60	130	1	-4	-2	-0.05	5	-300	30	-100	

DETECTION LIMIT

(0.1) (4) (10) (10) (4) (1) (2) (5) (1) (1) (4) (2) (0.05) (3) (300) (10) (100)

ALL ANALYSES BY AMDEL METHOD

E 3 SIE B 1 XRF B 1 XRF C 1 AAS B 1 XRF A 1 SPECTRO SEMI-QUANTITATIVE C 1 AAS C 1 AAS C 1 AAS C 1 AAS B 1 XRF B 1 XRF C 3 AAS A 1 SPECTRO SEMI-QUANTITATIVE A 1 A 1 A 1 A 1