

E.L. 7/74 "MOINA"

-2-

Mineral analysis data from bore core samples

Core No.	Depth Metres		Log	CaF <sub>2</sub> %	Sn ppm	W ppm	Bi ppm	Mo ppm	Be ppm	Cu ppm	Pb ppm	Zn ppm	Cd ppm	Sc ppm	Y ppm	Remarks
	From	To														
SMD																
16	114.00	116.00		17.3	1650	540	800	20	300			430		3	10	
16	116.00	118.00		18.9	2000	620	500	10	250			800		3	10	
16	118.00	120.50		19.7	1750	480	300	3	400			340		3	10	
16	120.50	123.00		4.3	1300	140	800	3	100			230		5	30	
16	123.00	125.43		2.6	720	55	500	-3	100			2520		10	30	
16	125.43	128.75		21.8	2650	1150	500	70	200			300		5	20	
16	128.75	131.00		5.3	720	220	300	-3	200			90		5	30	
16	131.00	133.00		2.5	410	1050	100	70	150			55		5	30	
16	133.00	135.00		0.7	430	20	30	-3	70			60		5	30	
16	135.00	137.00		4.4	350	360	30	80	80			75		10	30	
16	154.00	156.00		11.9	260	260	20	30	80			90		15	70	
DETECTION LIMIT					(4)	(10)	(1)	(3)	(1)					(3)	(10)	
ALL ANALYSES BY AMDEL - METHOD				E 3 SIE	B 1 XRF	B 1 XRF	Al/2	Al/2	Al/2			Cl AAS OR Fl/1 AAS for % Zn.		Al/2	Al/2	SPECTRO SEMI- QUANTITATIVE