

COMALCO EXPLORATION DEPARTMENTTASMANIAN E.L. 7/74 "MOINA", SHEPHERD & MURPHY MINE AREAMineral analysis data from bore core samples

Bore No.	Depth Metres		CaF ₂ %	Sn ppm	W ppm	Bi ppm	Mo ppm	Be ppm	Cu ppm	Pb ppm	Zn ppm	Cd ppm	Sc ppm	Y ppm	Remarks
	From	To													
SMD															
17	26.50	28.00	11.9	360	140	700	5	200					5	20	
17	28.00	29.00	11.9	340	280	500	3	250					10	30	
17	29.00	30.00	11.7	340	290	700	5	200					10	30	
17	30.00	31.00	13.1	280	250	500	5	200					5	20	
17	31.00	32.00	14.0	420	270	500	5	300					10	50	
17	32.00	33.00	12.7	250	160	500	3	300					5	50	
17	33.00	34.00	14.7	310	280	500	10	300					10	50	
17	34.00	35.15	4.4	110	140	200	30	80					15	70	
17	35.15	37.00	5.8	110	110	100	-3	100					3	10	
17	37.00	38.90	9.3	170	130	300	5	150					5	30	
17	38.90	39.90	18.1	300	250	500	-3	250					5	10	
17	39.90	40.90	12.9	350	260	500	5	150					10	30	
17	40.90	41.90	12.3	280	270	300	5	150					5	20	
17	41.90	43.90	7.2	200	170	100	-3	150					5	30	
17	43.90	45.90	3.6	65	50	50	-3	100					5	50	
17	45.90	47.90	0.9	24	20	5	5	50					20	100	
17	47.90	49.90	1.5	40	30	30	-3	100					10	50	
DETECTION LIMIT				(4)	(10)	(1)	(3)	(1)					(3)	(10)	
ALL ANALYSES BY AMDEL - METHOD			E 3 SIR	B 1 XRF	B 1 XRF	Al/2 SPECTRO SEMI- QUANTITATIVE	Al/2	Al/2					Al/2 SPECTRO SEMI- QUANTITATIVE	Al/2	