

COMALCO EXPLORATION DEPARTMENTTASMANIAN E.L. 7/74 "MOINA", SHEPHERD & MURPHY MINE AREAAnalyses of split core.

Bore No.	Depth From	Metres To	CaF ₂ %	Sn ppm	W ppm	Bi ppm	Mo ppm	Be ppm	Zn ppm	Ag ppm	Ge ppm	Sc ppm	Y ppm	Sr ppm	In ppm	Au ppm	Remarks
SMD 21	105.70	108.00	2.05	220	-10	70	-3	100	500	0.2	2	5	30	-50	-10	-0.05	
	108.00	110.00	0.80	210	20	70	-3	20	300	0.1	-1	5	50	-50	-10	-0.05	
	110.00	112.50	0.45	370	-10	150	-3	30	200	0.5	-1	3	30	-50	-10	0.10	
	112.50	114.50	3.30	650	35	150	30	150	3000	0.2	1	5	30	-50	-10	-0.05	
	114.50	116.50	6.20	600	20	150	30	100	100	0.1	1	10	70	-50	-10	-0.05	
	116.50	118.50	6.20	610	240	300	50	100	30	-0.1	3	10	70	100	-10	0.05	
	118.50	120.50	6.80	470	20	50	10	100	100	-0.1	-1	5	50	-50	-10	-0.05	
	120.50	122.10	6.20	960	340	300	10	150	80	0.1	2	15	70	50	-10	-0.05	
	122.10	124.50	16.40	1050	1050	500	100	200	200	-0.1	5	5	50	100	-10	-0.05	
<u>DETECTION LIMIT</u>				(4)	(10)	(1)	(3)	(1)	(20)	(0.1)	(1)	(3)	(10)	(50)	(10)		
<u>ALL ANALYSES BY AMDEL - METHOD.</u>			E 3 SIE	B I XRF	B 1 XRF	Al/2 SPECTRO	Al/2	Al/2	Al/2	Al/2	Al/2	Al/2	Al/2	Al/2	Al/2	C 3 AAS	