

COMALCO EXPLORATION DEPARTMENT

TASMANIAN E.L. 7/74 "MOINA", SHEPHERD & MURPHY MINE AREA

Mineral analysis data from bore core samples

Bore No.	Depth Metres		INTERVAL METRES.	Pb ppm	W ppm	Bi ppm	Sn ppm	Mo ppm	Cu ppm	Zn ppm	Be ppm	CaF <sub>2</sub> %	Ag ppm	Au ppm	Remarks
	From	To													
SMD 4	68.37	69.00	0.63 metres	6	540	580	1150	10	130	1240	40	15.6	-1	0.20	<p>SMY. 4                      27 samples                      over 27.63 metres                       To be part                      of 50 kg.                      composite sample                      composed of                      308.7 gms per                      metre of core                      length.</p> <p style="text-align: right;">221496</p>
4	69.00	70.00	1.0	10	820	620	1200	22	150	130	100	21.0	-1	0.20	
4	70.00	70.70	0.7	18	270	340	2200	-4	10	90	50	9.6	-1	0.15	
4	70.70	71.30	0.6	14	70	190	1900	6	5	90	50	8.5	-1	0.15	
4	71.30	72.00	0.7	8	300	330	1600	12	50	180	40	12.5	-1	0.15	
4	72.00	73.00	1.0	4	640	620	1700	38	200	140	50	21.0	-1	0.20	
4	73.00	74.00	1.0	8	1000	780	1550	30	160	130	80	26.0	-1	0.15	
4	74.00	75.00	1.0	16	1750	600	1800	100	240	130	80	26.5	-1	0.20	
4	75.00	76.00	1.0	-4	1750	350	1700	95	150	120	80	24.0	-1	0.15	
4	76.00	77.00	1.0	12	520	540	1650	24	130	100	80	20.0	-1	0.20	
4	77.00	78.00	1.0	8	620	450	1250	55	120	120	50	16.5	-1	0.20	
4	78.00	79.00	1.0	10	1450	580	1400	75	150	90	80	20.0	-1	0.20	
4	79.00	80.00	1.0	10	760	300	2100	65	32	80	80	17.5	-1	0.10	
4	80.00	80.63	0.63	22	840	470	1400	90	250	80	80	20.0	-1	0.10	
4	80.63	81.66	1.03	12	600	6	220	36	10	32	20	4.1	-1	-0.05	
4	81.66	83.70	2.04	20	460	320	1000	26	25	50	50	7.4	-1	-0.05	
4	83.70	85.00	1.3	10	1600	270	1300	60	350	70	40	16.5	-1	-0.10	
4	85.00	86.00	1.0	-4	1500	320	1500	75	220	65	30	15.5	-1	0.10	
4	86.00	87.00	1.0	14	2200	410	1250	75	240	70	40	14.0	-1	0.05	
4	87.00	88.00	1.0	14	860	660	1100	32	350	190	40	12.5	-1	0.10	
4	88.00	89.00	1.0	10	700	350	980	55	210	310	40	9.9	-1	0.10	
4	89.00	90.60	1.6	10	390	230	1150	42	160	95	30	7.5	-1	0.10	
4	90.60	91.25	0.65	18	180	60	1450	8	48	100	80	4.4	-1	-0.05	
4	91.25	92.45	1.20	24	300	75	1150	150	15	110	30	5.8	-1	0.05	
4	92.45	93.80	1.35	18	370	80	980	-4	60	110	30	5.1	-1	-0.05	
4	93.80	94.40	0.6	14	140	14	1050	6	65	60	20	4.5	-1	0.05	
4	94.40	95.90	1.5	12	1300	200	1200	26	80	70	30	8.1	-1	0.10	
4	95.90	97.15		6	400	6	280	10	45	42	20	4.9	-1	-0.05	
4	97.15	98.40		10	270	-4	75	20	40	40	5	1.9	-1	-0.05	